

## QUALITY CERTIFICATE BS EN 10204:2004 3. 1

TO: ACME SOLAR HOLDINGS LIMITED PLOT NO: 152, SECTOR 44, GURGAON 122002, INDIA

DESCRIPTION OF GOODS: HOT ROLLED PLATE

CONTRACT NO: XPIND24010CSL INVOICE NO: XPIND24010CSL-2C

## JIANGYIN XINGCHENG SPECIAL STEEL WORKS CO., LTD.

NO.297, BINJIANG (E) ROAD, JIANGYIN CITY, JIANGSU PROVINCE, CHINA PC 214429





DELIVERY CONDITION Normalizing rolling EDGE All-the-sides cutting							FICATION RADE			2019 2062 E35	50B0		U.T Test BS EN 10160:1999 S2E3  CHEMICAL COMPOSITION (Weight%)											CERTIFICATE NO. LICENSE NO.				Z 20250	2190000	891	
				SI	ZE AND W	EIGHT			1		1							CHEMI	CAL COM	IPOSITIO	N (Weig	ght%)									
.0i	PLATE NO.	HEAT NO.	THICK	WIDTH	LENGTH	PIECES		С	Si	Mn	P	S	A1	Nb	V	Ti	Cr	Ni	Cu	Мо	CEV	В	B N								
				mm			t																								
1	T5117016010	S500057	23	2572	12369	1	5. 744	0. 172	0. 185	1. 399	0.012	0.0016	0. 0328	0.004	0.001	0.0018	0.083	0. 039	0.023	0.014	0. 4289	0. 0004	4 0.0032	2							
$\dashv$						1																									
$\exists$																															
_			<u> </u>		1		1																								
		TENSILE TE	EST T	TENSILE TEST TEN		SILE TEST	TENSI	ILE TEST	IMPACT TEST		IMPACT TEST		IMPACT TEST		IMPACT TEST		U.T Test														
0.	PLATE NO.	ReH(Y.S)	)	Rm (T. S)		A (E. L)	ReH/Rm(Y.R)		Charpy- V_absorbed_energ y-1		Charpy- g V_absorbed_energ y-2		Charpy- V_absorbed_energ y-3		AVG		U.T inspection:														
		MPa		MPa		%		%		J		J		J		J															
		TC t		TC t		TC t	Т	CC t	TL t			*2mm		*2mm		*2mm															
1	T5117016010	386		534		28		72	0°		0	°C 38		℃ 92		℃ 10	Acce	n+ o.d													
1	13117010010	300		994		20		12	20	71	2.	30	1	34	2	10	лссе	pteu													
$\dashv$																							+								
PIE	PAGE TOTAL CCES WEIGHT 1 5.74	(t)	Accepta	able Vis size	sual and	REMARKS	WE HEREE	BY CERTIFY SAMPLE SIZE	THAT THE	MATERIAL ICKNESS, I	HASN'T A	NY IMPER ELY:t≥6	MISSIBLE -8mm\8 <t< td=""><td>DEFECTS.V</td><td>HEN THER ≥12mm, SA</td><td>E IS ANY MPLE SIZE</td><td>COMPLAIN , RESPECT</td><td>, YOU ARE VELY:10&gt;</td><td>E KINDLY ×5×55\10</td><td>REQUESTEI 0×7.5×5</td><td>) TO MARK 5\10×10</td><td>THE STE ×55mm.</td><td>EEL GRADE,</td><td>, HEAT NO,</td><td>PLATE NO,</td><td>SIZE, DELI</td><td>VERY DATE</td><td>E, CAUSES</td><td>AND MATER</td><td>IAL IN TH</td><td>E CONDITION.</td></t<>	DEFECTS.V	HEN THER ≥12mm, SA	E IS ANY MPLE SIZE	COMPLAIN , RESPECT	, YOU ARE VELY:10>	E KINDLY ×5×55\10	REQUESTEI 0×7.5×5	) TO MARK 5\10×10	THE STE ×55mm.	EEL GRADE,	, HEAT NO,	PLATE NO,	SIZE, DELI	VERY DATE	E, CAUSES	AND MATER	IAL IN TH	E CONDITION.
	SAM	MPLE LOCATI =C+Mn/6+(Cr+																		L.		175	OAIC OEEE	131					WARRAI	NTY DEDI	CATED
ISSUED DATE				2025/1	025/1/21			PRINTED BY			CHENYOU					QUALI	ITY MANAGER			an:		zhan	gMin	g ST.	AMP OF D	EPARTME	NT OF	SPE		'IN XINGC EEL WOR	HENG KS CO.,LTD.