



CITIC PACIFIC SPECIAL STEEL

JIANGYIN XINGCHENG SPECIAL STEEL WORKS CO., LTD.

NO.297, BINJIANG (E) ROAD, JIANGYIN CITY, JIANGSU PROVINCE, CHINA PC:214429

QUALITY CERTIFICATE

BS EN 10204:2004 3.1

TO: ACME SOLAR HOLDINGS LIMITED PLOT NO: 152,SECTOR 44, GURGAON 122002, INDIA

DESCRIPTION OF GOODS: HOT ROLLED PLATE

CONTRACT NO: XPIND24010CSL INVOICE NO: XPIND24010CSL-2C



DELIVERY CONDITION Normalizing rolling			SPECIFICATION EN 10025-2:2019			U. T Test BS EN 10160:1999 S2E3			CERTIFICATE NO. Z 202502190000730																							
EDGE All-the-sides cutting			GRADE S355J0+N/IS2062 E350B0						LICENSE NO.																							
NO.	PLATE NO.	HEAT NO.	SIZE AND WEIGHT					CHEMICAL COMPOSITION (Weight%)																								
			THICK	WIDTH	LENGTH	PIECES		C	Si	Mn	P	S	Al	Nb	V	Ti	Cr	Ni	Cu	Mo	CEV	B	N									
			mm	mm	mm	t																										
1	T5115012040	S500091	17.7	2598	11183	1	4.037	0.172	0.194	1.396	0.0195	0.0011	0.0344	0.002	0.001	0.0022	0.086	0.031	0.015	0.011	0.4273	0.0004	0.0028									
2	T5115012050	S500091	17.7	2598	11183	1	4.037	0.172	0.194	1.396	0.0195	0.0011	0.0344	0.002	0.001	0.0022	0.086	0.031	0.015	0.011	0.4273	0.0004	0.0028									
NO.	PLATE NO.		TENSILE TEST	TENSILE TEST	TENSILE TEST	TENSILE TEST	IMPACT TEST	IMPACT TEST	IMPACT TEST	IMPACT TEST	U. T Test																					
			ReH(Y. S)	Rm(T. S)	A(E. L)	ReH/Rm(Y. R)	Charpy- V_absorbed_energy-1	Charpy- V_absorbed_energy-2	Charpy- V_absorbed_energy-3	AVG	U. T inspection:																					
			MPa	MPa	%	%	J	J	J	J																						
			TC t	TC t	TC t	TC t	TL t*2mm	TL t*2mm	TL t*2mm	TL t*2mm																						
							0°C	0°C	0°C	0°C																						
1	T5115012040	385	543	30	71	107	126	146	126	Accepted																						
2	T5115012050	385	543	30	71	107	126	146	126	Accepted																						
PAGE TOTAL			Acceptable Visual and size		REMARKS	WE HEREBY CERTIFY THAT THE MATERIAL HASN'T ANY IMPERMISSIBLE DEFECTS.WHEN THERE IS ANY COMPLAINT, YOU ARE KINDLY REQUESTED TO MARK THE STEEL GRADE, HEAT NO, PLATE NO, SIZE, DELIVERY DATE, CAUSES AND MATERIAL IN THE CONDITION. IMPACT SAMPLE SIZE:PLATE THICKNESS, RESPECTIVELY: t≥6-8mm\8<t<12mm\t≥12mm, SAMPLE SIZE, RESPECTIVELY:10×5×55\10×7.5×55\10×10×55mm.																										
PIECES WEIGHT (t)																																
2 8.074																																
NOTES			SAMPLE LOCATION AND ORIENTATION:T=TOP; B=BOTTOM; L=LONGL; C=TRANS; t =full thickness;t*2mm =2mm from rolled surface to specimen surface; CEV=C+Mn/6+(Cr+Mo+V)/5+(Ni+Cu)/15. Tolerance S355J0+N/IS2062 E350B0、S355N/IS2062 E350C : BS EN 10029:2010 Class C.Flatness:BS EN10029: 2010 class N type L .																													
ISSUED DATE			2025/1/21			PRINTED BY			CHENYOU			QUALITY MANAGER			zhangming			STAMP OF DEPARTMENT OF QUALITY ASSURANCE														