

QUALITY CERTIFICATE

BS EN 10204:2004 3.1

TO: ACME SOLAR HOLDINGS LIMITED PLOT NO: 152,SECTOR 44, GURGAON 122002, INDIA

DESCRIPTION OF GOODS: HOT ROLLED PLATE

CONTRACT NO: XPIND24010CSL INVOICE NO: XPIND24010CSL-2C



DELIVERY CONDITION Normalizing rolling SPECIFICATION EN 10025-2:2019 U. T Test BS EN 10160:1999 S2E3 CERTIFICATE NO. Z 202502190000766
EDGE All-the-sides cutting GRADE S355J0+N/IS2062 E350B0 LICENSE NO.

NO.	PLATE NO.	HEAT NO.	SIZE AND WEIGHT					CHEMICAL COMPOSITION (Weight%)																											
			THICK	WIDTH	LENGTH	PIECES		C	Si	Mn	P	S	Al	Nb	V	Ti	Cr	Ni	Cu	Mo	CEV	B	N												
7	T5115032070	S500093	19.1	2600	11496	1	4.481	0.17	0.175	1.408	0.0181	0.0022	0.0364	0.003	0.002	0.0013	0.069	0.031	0.017	0.004	0.4229	0.0002	0.003												
8	T5115033010	S500093	19.1	2600	11496	1	4.481	0.17	0.175	1.408	0.0181	0.0022	0.0364	0.003	0.002	0.0013	0.069	0.031	0.017	0.004	0.4229	0.0002	0.003												
9	T5115033020	S500093	19.1	2600	11496	1	4.481	0.17	0.175	1.408	0.0181	0.0022	0.0364	0.003	0.002	0.0013	0.069	0.031	0.017	0.004	0.4229	0.0002	0.003												
10	T5115033050	S500093	19.1	2600	11496	1	4.481	0.17	0.175	1.408	0.0181	0.0022	0.0364	0.003	0.002	0.0013	0.069	0.031	0.017	0.004	0.4229	0.0002	0.003												
11	T5115033060	S500093	19.1	2600	11496	1	4.481	0.17	0.175	1.408	0.0181	0.0022	0.0364	0.003	0.002	0.0013	0.069	0.031	0.017	0.004	0.4229	0.0002	0.003												
12	T5115033070	S500093	19.1	2600	11496	1	4.481	0.17	0.175	1.408	0.0181	0.0022	0.0364	0.003	0.002	0.0013	0.069	0.031	0.017	0.004	0.4229	0.0002	0.003												
NO.	PLATE NO.		TENSILE TEST	TENSILE TEST	TENSILE TEST	TENSILE TEST	IMPACT TEST	IMPACT TEST	IMPACT TEST	IMPACT TEST	U. T Test																								
			ReH(Y. S)	Rm(T. S)	A(E. L)	ReH/Rm(Y. R)	Charpy-V_absorbed_energy-1	Charpy-V_absorbed_energy-2	Charpy-V_absorbed_energy-3	AVG	U. T inspection:																								
			MPa	MPa	%	%	J	J	J	J																									
			TC t	TC t	TC t	TC t	TL t*2mm	TL t*2mm	TL t*2mm	TL t*2mm																									
							0℃	0℃	0℃	0℃																									
7	T5115032070	415	558	28.5	74	223	208	196	209	Accepted																									
8	T5115033010	407	553	30.5	73	182	151	175	169	Accepted																									
9	T5115033020	407	553	30.5	73	182	151	175	169	Accepted																									
10	T5115033050	407	553	30.5	73	182	151	175	169	Accepted																									
11	T5115033060	407	553	30.5	73	182	151	175	169	Accepted																									
12	T5115033070	407	553	30.5	73	182	151	175	169	Accepted																									
PAGE TOTAL			Acceptable Visual and size			REMARKS	WE HEREBY CERTIFY THAT THE MATERIAL HASN'T ANY IMPERMISSIBLE DEFECTS.WHEN THERE IS ANY COMPLAINT, YOU ARE KINDLY REQUESTED TO MARK THE STEEL GRADE, HEAT NO, PLATE NO, SIZE, DELIVERY DATE, CAUSES AND MATERIAL IN THE CONDITION. IMPACT SAMPLE SIZE:PLATE THICKNESS, RESPECTIVELY:t≥6-8mm\8<t<12mm\t≥12mm, SAMPLE SIZE, RESPECTIVELY:10×5×55\10×7.5×55\10×10×55mm.																												
PIECES		WEIGHT (t)																																	
6		26.886																																	
NOTES			SAMPLE LOCATION AND ORIENTATION:T=TOP; B=BOTTOM; L=LONG; C=TRANS; t =full thickness;t*2mm =2mm from rolled surface to specimen surface; CEV=C+Mn/6+(Cr+Mo+V)/5+(Ni+Cu)/15. Tolerance S355J0+N/IS2062 E350B0、S355N/IS2062 E350C : BS EN 10029:2010 Class C.Flatness:BS EN10029: 2010 class N type L .																																
ISSUED DATE			2025/1/21			PRINTED BY			CHENYOU			QUALITY MANAGER			zhangming			STAMP OF DEPARTMENT OF QUALITY ASSURANCE																	