



CITIC PACIFIC SPECIAL STEEL

JIANGYIN XINGCHENG SPECIAL STEEL WORKS CO., LTD.

NO.297, BINJIANG (E) ROAD, JIANGYIN CITY, JIANGSU PROVINCE, CHINA PC:214429

QUALITY CERTIFICATE

BS EN 10204:2004 3.1

TO: ACME SOLAR HOLDINGS LIMITED PLOT NO: 152,SECTOR 44, GURGAON 122002, INDIA

DESCRIPTION OF GOODS: HOT ROLLED PLATE

CONTRACT NO: XPIND24010CSL INVOICE NO: XPIND24010CSL-2C



DELIVERY CONDITION Normalizing rolling			SPECIFICATION EN 10025-2:2019			U. T Test BS EN 10160:1999 S2E3			CERTIFICATE NO. Z 202502190001060																								
EDGE All-the-sides cutting			GRADE S355J0+N/IS2062 E350B0						LICENSE NO.																								
NO.	PLATE NO.	HEAT NO.	SIZE AND WEIGHT					CHEMICAL COMPOSITION (Weight%)																									
			THICK	WIDTH	LENGTH	PIECES		C	Si	Mn	P	S	Al	Nb	V	Ti	Cr	Ni	Cu	Mo	CEV	B	N										
			mm			t																											
1	T5115033030	S500093	19.1	2600	11496	1	4.481	0.17	0.175	1.408	0.0181	0.0022	0.0364	0.003	0.002	0.0013	0.069	0.031	0.017	0.004	0.4229	0.0002	0.003										
2	T5115033040	S500093	19.1	2600	11496	1	4.481	0.17	0.175	1.408	0.0181	0.0022	0.0364	0.003	0.002	0.0013	0.069	0.031	0.017	0.004	0.4229	0.0002	0.003										
NO.	PLATE NO.		TENSILE TEST	TENSILE TEST	TENSILE TEST	TENSILE TEST	IMPACT TEST	IMPACT TEST	IMPACT TEST	IMPACT TEST	U. T Test																						
			ReH(Y. S)	Rm(T. S)	A(E. L)	ReH/Rm(Y. R)	Charpy- V_absorbed_energy-1	Charpy- V_absorbed_energy-2	Charpy- V_absorbed_energy-3	AVG	U. T inspection:																						
			MPa	MPa	%	%	J	J	J	J																							
			TC t	TC t	TC t	TC t	TL t*2mm	TL t*2mm	TL t*2mm	TL t*2mm																							
							0℃	0℃	0℃	0℃																							
1	T5115033030	407	553	30.5	73	182	151	175	169	Accepted																							
2	T5115033040	407	553	30.5	73	182	151	175	169	Accepted																							
PAGE TOTAL			PIECES		WEIGHT (t)		Acceptable Visual and size	REMARKS	WE HEREBY CERTIFY THAT THE MATERIAL HASN'T ANY IMPERMISSIBLE DEFECTS.WHEN THERE IS ANY COMPLAINT, YOU ARE KINDLY REQUESTED TO MARK THE STEEL GRADE, HEAT NO, PLATE NO, SIZE, DELIVERY DATE, CAUSES AND MATERIAL IN THE CONDITION. IMPACT SAMPLE SIZE:PLATE THICKNESS, RESPECTIVELY: t≥6-8mm\8<t<12mm\t≥12mm, SAMPLE SIZE, RESPECTIVELY:10×5×55\10×7.5×55\10×10×55mm.																								
			2		8.962																												
NOTES			SAMPLE LOCATION AND ORIENTATION:T=TOP; B=BOTTOM; L=LONGL; C=TRANS; t =full thickness;t*2mm =2mm from rolled surface to specimen surface; CEV=C+Mn/6+(Cr+Mo+V)/5+(Ni+Cu)/15. Tolerance S355J0+N/IS2062 E350B0、S355N/IS2062 E350C : BS EN 10029:2010 Class C.Flatness:BS EN10029: 2010 class N type L .																														
ISSUED DATE			2025/1/21			PRINTED BY			CHENYOU			QUALITY MANAGER			zhangming			STAMP OF DEPARTMENT OF QUALITY ASSURANCE															

