



Mill Test Certificate

IS 2062 : 2011



CM/L-4039956

Certificate No. : 241205-FP01KS-0001A1-0006

Date of Issue : Dec., 26, 2024

Order No. : 01S7113057

PO No. : 01S7113057

Supplier : POSCO INTERNATIONAL CORPORATION

Commodity : STEEL PLATE

Customer : MOUNTING RENEWABLE POWER LIMITED

Spec & Type : IS-E350B0/EN-S355J0N

Size	Product No.	Quantity	Weight (kg)	Heat No.	Country of Melt & Pour	Position	Tensile Test			Tensile Test2			Impact Test		Bend Test	U.S.T	Division	Deoxidation	Chemical Composition								
							YP (MPa)	TS (%)	EL (%)	YP (MPa)	TS (%)	EL (%)	V Notch +0 °C Energy (Joule)	C (%)					Si (%)	Mn (%)	P (%)	S (%)	Cr (%)	Ni (%)	B (ppm)		
33x2980x14051	PP60687802	1	10,844	SU30958	KOR	T	396	559	26	418	568	27	1: 153 2: 168 3: 150 A: 157		Good	L P	C	0.1579 0.1547	0.372 0.368	1.421 1.393	0.0129 0.0110	0.0033 0.0032	0.026 0.022	0.007 0.006	3 2		
33x2980x14051	PP60684902	1	10,844	SU30958	KOR	T	418	558	28	418	568	27	1: 178 2: 179 3: 187 A: 181		Good	L P	C	0.1579 0.1547	0.372 0.368	1.421 1.393	0.0129 0.0110	0.0033 0.0032	0.026 0.022	0.007 0.006	3 2		
*** Sub Total (050) ***		11	119,284 (kg)																CEQ (G) = C + Mn/6 + (Ni + Cu)/15 + (Cr + Mo + V)/5								
*** Heat Treatment ==> Normalizing rolling ***																											
We certified that the material described above fully conforms to IS:2062 : 2011 Chemical composition and Mechanical properties of the product, as tested in accordance with the Scheme of Testing and Inspection contained in the BIS Certification Marks LicenceNo.CM/L-4039956 are as indicated above against each order No. (PLEASE REFER TO IS 2062 : 2011 FOR DETAILS OF SPECIFICATION REQUIREMENTS)																											
*** Lot Total ***		11	119,284 (kg)		Lot No. ==> S1-P5																						
33x2980x14051	PP60598202	1	10,844	SU30880	KOR	T	413	565	27	418	560	27	1: 161 2: 121 3: 162 A: 148		Good	L P	C	0.1557 0.1469	0.377 0.365	1.434 1.400	0.0142 0.0124	0.0042 0.0039	0.039 0.040	0.027 0.024	4 2		
33x2980x14051	PP60597102	1	10,844	SU30880	KOR	T	404	574	24	418	560	27	1: 167 2: 191 3: 172 A: 177		Good	L P	C	0.1557 0.1469	0.377 0.365	1.434 1.400	0.0142 0.0124	0.0042 0.0039	0.039 0.040	0.027 0.024	4 2		
33x2980x14051	PP60596402	1	10,844	SU30880	KOR	T	405	558	25	418	560	27	1: 172 2: 177 3: 135 A: 161		Good	L P	C	0.1557 0.1469	0.377 0.365	1.434 1.400	0.0142 0.0124	0.0042 0.0039	0.039 0.040	0.027 0.024	4 2		

- * Position - T : Top, M : Middle, B : Bottom
- * Tensile Test. Direction : Transversal, Gauge Length : 5.65 √A. (Rectangular), YP Method : Upper Point
- * Tensile Test2. Direction : Transversal, Gauge Length : 5.65 √A. (Rectangular), YP Method : Upper Point
- * Impact Test. Direction : Surface Longitudinal, Full-Size : 10 mmX10 mm
- * U.S.T : Ultrasonic Test.
- * Division - L : Ladle Analysis, P : Products Analysis
- * Supply Condition : As-Rolled unless otherwise Heat Treated.
- * Deoxidation : A, W : Al-Killed. B, R : Rim-Cast. C, V, *Y* : Si+Al-Killed. P, S : Si-Killed



This material has been fully killed and made by basic oxygen process. This material is fine grained steel. This material has been made by vacuum degassing process. No repair welding was performed to the products. Test Certificate is issued according to ISO 10474/EN 10204 3.1. We, POSCO, hereby certify that the products specified in the present MTC have been fully processed in South Korea. (Facility and address information is stated below) We hereby certify that the material herein has been made in accordance with the order and above specification. Applicable code: IS 2062 : 2011, BIS Certification marks Licence No. CM/L-4039956

Legal sanction can be imposed on forging. Improper use of product can cause safety issues.

poscomtc@posco.com
+82-2-3457-0114

Surveyor To :

Kang, Deokgu

