



CITIC PACIFIC SPECIAL STEEL

JIANGYIN XINGCHENG SPECIAL STEEL WORKS CO., LTD.

NO.297, BINJIANG (E) ROAD, JIANGYIN CITY, JIANGSU PROVINCE, CHINA PC 214429

QUALITY CERTIFICATE

BS EN 10204:2004 3.1

TO: ACME SOLAR HOLDINGS LIMITED PLOT NO: 152, SECTOR 44, GURGAON 122002, INDIA

DESCRIPTION OF GOODS: HOT ROLLED PLATE

CONTRACT NO: XPIND24010CSL INVOICE NO: XPIND24010CSL-1C



DELIVERY CONDITION Normalizing rolling SPECIFICATION EN 10025-2:2019 U. T Test BS EN 10160:1999 S2E3 CERTIFICATE NO. Z 202502210001068
EDGE All-the-sides cutting GRADE S355J0+N/IS2062 E350B0 LICENSE NO.

NO.	PLATE NO.	HEAT NO.	SIZE AND WEIGHT					CHEMICAL COMPOSITION (Weight%)																								
			THICK	WIDTH	LENGTH	PIECES		C	Si	Mn	P	S	Al	Nb	V	Ti	Cr	Ni	Cu	Mo	CEV	B	N									
			mm				t																									
			28.3	2632	13634	1	7.972	0.164	0.191	1.392	0.0186	0.0006	0.0425	0.004	0.002	0.0022	0.095	0.078	0.022	0.015	0.4251	0.0003	0.0024									
1	T5115071040	S500106																														
NO.	PLATE NO.	TENSILE TEST		TENSILE TEST		TENSILE TEST		TENSILE TEST		IMPACT TEST		IMPACT TEST		IMPACT TEST		IMPACT TEST		U. T Test														
		ReH(Y. S)		Rm(T. S)		A(E. L)		ReH/Rm(Y. R)		Charpy- V_absorbed_energy-1		Charpy- V_absorbed_energy-2		Charpy- V_absorbed_energy-3		AVG		U. T inspection:														
		MPa		MPa		%		%		J		J		J		J																
		TC t		TC t		TC t		TC t		TL t*2mm		TL t*2mm		TL t*2mm		TL t*2mm																
										0℃		0℃		0℃		0℃																
1	T5115071040	386	529		29.5		73		214		227		252		231		Accepted															
PAGE TOTAL				Acceptable Visual and size		REMARKS		WE HEREBY CERTIFY THAT THE MATERIAL HASN'T ANY IMPERMISSIBLE DEFECTS. WHEN THERE IS ANY COMPLAINT, YOU ARE KINDLY REQUESTED TO MARK THE STEEL GRADE, HEAT NO, PLATE NO, SIZE, DELIVERY DATE, CAUSES AND MATERIAL IN THE CONDITION. IMPACT SAMPLE SIZE: PLATE THICKNESS, RESPECTIVELY: t ≥ 6-8mm \ 8 < t < 12mm \ t ≥ 12mm, SAMPLE SIZE, RESPECTIVELY: 10 × 5 × 55 \ 10 × 7.5 × 55 \ 10 × 10 × 55mm.																								
PIECES	WEIGHT (t)																															
1	7.972																															
NOTES		SAMPLE LOCATION AND ORIENTATION: T=TOP; B=BOTTOM; L=LONG; C=TRANS; t =full thickness; t*2mm =2mm from rolled surface to specimen surface; CEV=C+Mn/6+(Cr+Mo+V)/5+(Ni+Cu)/15. Tolerance S355J0+N/IS2062 E350B0、S355N/IS2062 E350C : BS EN 10029:2010 Class C. Flatness: BS EN10029: 2010 class N type L .																														
ISSUED DATE		2025/1/21				PRINTED BY				CHENYOU				QUALITY MANAGER				zhangming				STAMP OF DEPARTMENT OF QUALITY ASSURANCE				WARRANTY DEDICATED JIANGYIN XINGCHENG SPECIAL STEEL WORKS CO.,LTD. INSPECTION						