



CITIC PACIFIC SPECIAL STEEL

JIANGYIN XINGCHENG SPECIAL STEEL WORKS CO., LTD.

NO.297, BINJIANG (E) ROAD, JIANGYIN CITY, JIANGSU PROVINCE, CHINA PC:214429

QUALITY CERTIFICATE

BS EN 10204:2004 3.1

TO: ACME SOLAR HOLDINGS LIMITED PLOT NO: 152,SECTOR 44, GURGAON 122002, INDIA

DESCRIPTION OF GOODS: HOT ROLLED PLATE

CONTRACT NO: XPIND24010CSL INVOICE NO: XPIND24010CSL-2C



DELIVERY CONDITION Normalizing rolling SPECIFICATION EN 10025-2:2019 U. T Test BS EN 10160:1999 S2E3 CERTIFICATE NO. Z 202502190000920
EDGE All-the-sides cutting GRADE S355J0+N/IS2062 E350B0 LICENSE NO.

NO.	PLATE NO.	HEAT NO.	SIZE AND WEIGHT						CHEMICAL COMPOSITION (Weight%)																													
			THICK	WIDTH	LENGTH	PIECES		C	Si	Mn	P	S	Al	Nb	V	Ti	Cr	Ni	Cu	Mo	CEV	B	N															
1	T5117068020	S500067	26.8	2573	12782	1	6.919	0.166	0.185	1.388	0.0111	0.0016	0.0355	0.0022	0.001	0.0022	0.078	0.03	0.018	0.019	0.4201	0.0005	0.0028															
2	T5117068040	S500067	26.8	2573	12782	1	6.919	0.166	0.185	1.388	0.0111	0.0016	0.0355	0.0022	0.001	0.0022	0.078	0.03	0.018	0.019	0.4201	0.0005	0.0028															
3	T5117074010	S500068	26.8	2573	12782	1	6.919	0.164	0.181	1.396	0.0165	0.0017	0.0378	0.002	0.001	0.0016	0.079	0.031	0.021	0.013	0.4187	0.0004	0.0021															
4	T5117074020	S500068	26.8	2573	12782	1	6.919	0.164	0.181	1.396	0.0165	0.0017	0.0378	0.002	0.001	0.0016	0.079	0.031	0.021	0.013	0.4187	0.0004	0.0021															
5	T5117074040	S500068	26.8	2573	12782	1	6.919	0.164	0.181	1.396	0.0165	0.0017	0.0378	0.002	0.001	0.0016	0.079	0.031	0.021	0.013	0.4187	0.0004	0.0021															
NO.	PLATE NO.	TENSILE TEST	TENSILE TEST		TENSILE TEST		TENSILE TEST		IMPACT TEST		IMPACT TEST		IMPACT TEST		IMPACT TEST		U. T Test																					
		ReH (Y. S)	Rm (T. S)		A (E. L)		ReH/Rm (Y. R)		Charpy-V_absorbed_energy-1		Charpy-V_absorbed_energy-2		Charpy-V_absorbed_energy-3		AVG		U. T inspection:																					
		MPa	MPa		%		%		J		J		J		J																							
		TC t	TC t		TC t		TC t		TL t*2mm		TL t*2mm		TL t*2mm		TL t*2mm																							
									0℃		0℃		0℃		0℃																							
1	T5117068020	394	531		31		74		236		233		215		228		Accepted																					
2	T5117068040	394	531		31		74		236		233		215		228		Accepted																					
3	T5117074010	393	529		31.5		74		193		200		222		205		Accepted																					
4	T5117074020	393	529		31.5		74		193		200		222		205		Accepted																					
5	T5117074040	393	529		31.5		74		193		200		222		205		Accepted																					
PAGE TOTAL																																						
PIECES		WEIGHT (t)		Acceptable Visual and size		REMARKS		WE HEREBY CERTIFY THAT THE MATERIAL HASN'T ANY IMPERMISSIBLE DEFECTS.WHEN THERE IS ANY COMPLAINT, YOU ARE KINDLY REQUESTED TO MARK THE STEEL GRADE, HEAT NO, PLATE NO, SIZE, DELIVERY DATE, CAUSES AND MATERIAL IN THE CONDITION. IMPACT SAMPLE SIZE:PLATE THICKNESS, RESPECTIVELY:t≥6-8mm\8<t<12mm\t≥12mm, SAMPLE SIZE, RESPECTIVELY:10×5×55\10×7.5×55\10×10×55mm.																														
5		34.595																																				
NOTES		SAMPLE LOCATION AND ORIENTATION:T=TOP; B=BOTTOM; L=LONG; C=TRANS; t =full thickness;t*2mm =2mm from rolled surface to specimen surface; CEV=C+Mn/6+(Cr+Mo+V)/5+(Ni+Cu)/15. Tolerance S355J0+N/IS2062 E350B0、S355N/IS2062 E350C : BS EN 10029:2010 Class C.Flatness:BS EN10029: 2010 class N type L .																																				
ISSUED DATE		2025/1/21					PRINTED BY					CHENYOU					QUALITY MANAGER					zhangMing					STAMP OF DEPARTMENT OF QUALITY ASSURANCE					WARRANTY DEDICATED JIANGYIN XINGCHENG SPECIAL STEEL WORKS CO.,LTD. INSPECTION						