

QUALITY CERTIFICATE

BS EN 10204:2004 3.1

TO: ACME SOLAR HOLDINGS LIMITED PLOT NO: 152,SECTOR 44, GURGAON 122002, INDIA

DESCRIPTION OF GOODS: HOT ROLLED PLATE

CONTRACT NO: XPIND24010CSL INVOICE NO: XPIND24010CSL-2C



DELIVERY CONDITION Normalizing rolling SPECIFICATION EN 10025-2:2019 U. T Test BS EN 10160:1999 S2E3 CERTIFICATE NO. Z 202502190001024
EDGE All-the-sides cutting GRADE S355J0+N/IS2062 E350B0 LICENSE NO.

NO.	PLATE NO.	HEAT NO.	SIZE AND WEIGHT					CHEMICAL COMPOSITION (Weight%)																										
			THICK	WIDTH	LENGTH	PIECES		C	Si	Mn	P	S	Al	Nb	V	Ti	Cr	Ni	Cu	Mo	CEV	B	N											
1	T5117053020	S500065	25.8	2573	12679	1	6.607	0.165	0.183	1.41	0.0155	0.0023	0.0329	0.0024	0.002	0.002	0.075	0.028	0.02	0.0393	0.4265	0.0004	0.0026											
2	T5117053030	S500065	25.8	2573	12679	1	6.607	0.165	0.183	1.41	0.0155	0.0023	0.0329	0.0024	0.002	0.002	0.075	0.028	0.02	0.0393	0.4265	0.0004	0.0026											
3	T5117053050	S500065	25.8	2573	12679	1	6.607	0.165	0.183	1.41	0.0155	0.0023	0.0329	0.0024	0.002	0.002	0.075	0.028	0.02	0.0393	0.4265	0.0004	0.0026											
4	T5117054010	S500065	25.8	2573	12679	1	6.607	0.165	0.183	1.41	0.0155	0.0023	0.0329	0.0024	0.002	0.002	0.075	0.028	0.02	0.0393	0.4265	0.0004	0.0026											
5	T5117054020	S500065	25.8	2573	12679	1	6.607	0.165	0.183	1.41	0.0155	0.0023	0.0329	0.0024	0.002	0.002	0.075	0.028	0.02	0.0393	0.4265	0.0004	0.0026											
6	T5117054040	S500065	25.8	2573	12679	1	6.607	0.165	0.183	1.41	0.0155	0.0023	0.0329	0.0024	0.002	0.002	0.075	0.028	0.02	0.0393	0.4265	0.0004	0.0026											
NO.	PLATE NO.	TENSILE TEST	TENSILE TEST		TENSILE TEST		TENSILE TEST		IMPACT TEST		IMPACT TEST		IMPACT TEST		IMPACT TEST		U. T Test																	
		ReH(Y.S)	Rm(T.S)		A(E.L)		ReH/Rm(Y.R)		Charpy-V_absorbed_energy-1		Charpy-V_absorbed_energy-2		Charpy-V_absorbed_energy-3		AVG		U. T inspection:																	
		MPa	MPa		%		%		J		J		J		J																			
		TC t	TC t		TC t		TC t		TL t*2mm		TL t*2mm		TL t*2mm		TL t*2mm																			
									0℃		0℃		0℃		0℃																			
1	T5117053020	410	542		29.5		76		194		236		231		220		Accepted																	
2	T5117053030	410	542		29.5		76		194		236		231		220		Accepted																	
3	T5117053050	410	542		29.5		76		194		236		231		220		Accepted																	
4	T5117054010	412	545		28.5		76		232		235		233		233		Accepted																	
5	T5117054020	412	545		28.5		76		232		235		233		233		Accepted																	
6	T5117054040	412	545		28.5		76		232		235		233		233		Accepted																	
PAGE TOTAL			Acceptable Visual and size				REMARKS	WE HEREBY CERTIFY THAT THE MATERIAL HASN'T ANY IMPERMISSIBLE DEFECTS.WHEN THERE IS ANY COMPLAINT, YOU ARE KINDLY REQUESTED TO MARK THE STEEL GRADE, HEAT NO, PLATE NO, SIZE, DELIVERY DATE, CAUSES AND MATERIAL IN THE CONDITION. IMPACT SAMPLE SIZE:PLATE THICKNESS, RESPECTIVELY:t≥6-8mm\8<t<12mm\t≥12mm, SAMPLE SIZE, RESPECTIVELY:10×5×55\10×7.5×55\10×10×55mm.																										
PIECES	WEIGHT (t)																																	
6	39.642																																	
NOTES			SAMPLE LOCATION AND ORIENTATION:T=TOP; B=BOTTOM; L=LONG; C=TRANS; t =full thickness;t*2mm =2mm from rolled surface to specimen surface; CEV=C+Mn/6+(Cr+Mo+V)/5+(Ni+Cu)/15. Tolerance S355J0+N/IS2062 E350B0、S355N/IS2062 E350C : BS EN 10029:2010 Class C.Flatness:BS EN10029: 2010 class N type L .																															
ISSUED DATE			2025/1/21				PRINTED BY				CHENYOU				QUALITY MANAGER				zhangming				STAMP OF DEPARTMENT OF QUALITY ASSURANCE				WARRANTY DEDICATED JIANGYIN XINGCHENG SPECIAL STEEL WORKS CO.,LTD. INSPECTION							