

CRYSTAL-Flex-Skim

Polymer Modified Cementitious Finish Skim Coat.

CRYSTAL-Flex-Skim A high-performance, polymer-enhanced Cementitious skim coat designed to deliver an ultra-smooth, durable finish on interior and exterior surfaces. Formulated with advanced polymers and selected fillers, it offers superior adhesion, flexibility, and crack resistance compared to conventional cement finishes.

ADVANTAGE

- Enhanced bonding to concrete, plaster, masonry, and cement boards
- Smooth, refined finish suitable for paint and decorative coatings
- Improved flexibility to reduce shrinkage and hairline cracks
- Excellent workability with extended open time
- High durability and abrasion resistance
- Low dust formulation with consistent setting

USES

CRYSTAL-Flex-Skim is a specialized, polymer-modified skim coat designed to correct minor surface imperfections in concrete, plaster, mortar, and stone masonry. This cosmetic repair compound effectively fills pinholes, surface blemishes, and fine irregularities, creating a smooth and uniform finish. It is especially suitable for light restoration and surface refinement of precast concrete elements, columns, beams, and exposed concrete surfaces, where a high-quality aesthetic finish is required prior to painting or protective coatings.

MIXING

CRYSTAL-Flex-Skim should be blended with clean water & Special Polymer utilizing a power drill whisk. Begin by pouring the necessary amount of water into an appropriate container, followed by the gradual addition of **CRYSTAL-Flex-Skim** while stirring consistently until a uniform texture is attained. It is essential to scrape the container's sides to guarantee thorough blending of the powder for a consistent mixture. Allow the blend to rest for 4 to 5 minutes before giving it a final mix of 20 to 30 seconds, preparing the plaster for application.

Technical Properties

Physical Properties	Typical Value
Form	White powder
Composition	Cement selected aggregates & additives
Color	White/Grey/Light grey/ Customer Choice
Pot Life	30 Minutes
Coverage	18.58 m ² /25 kg bag at 1 mm thickness
Substrate Temperature	+10°C min./+ 50°C max.
Ambient Air Temperature	+10°C min./+ 50°C max.
Compressive Strength	≥20.0 N/mm ² in 24 Hours ≥35.0 N/mm ² in 7 Days ≥50.0 N/mm ² in 28 Days
Flexural Strength	28 days ≥ 12 MPa
Tensile Strength	28 days ≥ 9 MPa
Tensile Adhesion Strength	14 MPa
Minimum Thickness	1 mm
Maximum Thickness	3 mm

BD Marketing by LIQUIMIX.

Crystal-Flex-Skim

Polymer Modified Cementitious Finish Skim Coat

SURFACE PREPARATION

The substrate must be sound, clean, and dry, free from contaminants such as dust, dirt, oil, grease, curing compounds, coatings, or any other surface treatments that may impair adhesion. Where substrate conditions are uncertain, it is recommended to carry out a trial application beforehand.

Dry concrete, render, or CRYSTAL-Flex-Skim surfaces should be adequately pre-wetted prior to application. This prevents premature moisture loss, enhances adhesion, and ensures optimal performance of the product.

All cracks, voids, and surface irregularities must be properly repaired and leveled before application.

Adhering to these preparation guidelines will ensure a smooth application process and a durable, high-quality finish with long-term performance.

APPLICATION

Prior to applying CRYSTAL-Flex-Skim, it is essential to thoroughly clean the surface to remove any substances like laitance, curing compounds, shuttering oil, or grease that could hinder adhesion. Ensuring the surface is free from loose particles is crucial. Before application, saturate the surface with water for a minimum of 2-4 hours.

For every 25 kg bag, utilize 6.5 to 7 liters of water, adjusting based on the desired consistency. Employ a heavy-duty drill machine equipped with a paddle attachment, operating at a slow speed. Mix the components for approximately 3 minutes until a uniformly blended consistency is achieved. Partial mixing may be considered, ensuring the accurate maintenance of the water-to-powder ratio.

A blend of components is applied to the primed surface using a steel trowel. It is essential to meticulously work the material into any pinholes and imperfections on the surface. Allow it to partially set before applying final touches with a sponge or steel trowel. Consider lightly sprinkling water on the material before the last smoothing with a trowel or sponge.

CURING

For CRYSTAL-Flex-Skim, it's recommended to cure it post formwork removal by utilizing Curing Compound.

REMARKS

- Refrain from applying CRYSTAL-Flex-Skim on painted or gypsum surfaces.
- Application of CRYSTAL-Flex-Skim on extremely porous or dry substrates might result in a chalky or dusty surface, which is not suitable for painting or subsequent applications.
- Before applying a protective layer over CRYSTAL-Flex-Skim, it is crucial to conduct a compatibility test on the coating, specifically assessing adhesion strength

BD Marketing by LIQUIMIX.

Crystal-Flex-Skim

Polymer Modified Cementations Finish Skim Coat

PACKAGING

CRYSTAL-Flex-Skim is available in 25kg bags.

SHELF LIFE

12 Months from date of Manufacture if stored in Unopened Packaging. Protect from Rain, Direct Sunlight, Heat and Frost

CLEANING OF EQUIPMENT

It's crucial to clean all tools and application equipment with water immediately after use. If materials are allowed to harden or cure, they can only be removed through mechanical means.

HEALTH AND SAFETY

For complete details on health, safety, handling, and usage, please obtain the **CRYSTAL-Flex-Skim** Material Safety Data Sheet (MSDS) from our office or website.

Reviewing the MSDS is essential to ensure safe handling and application of the product. It provides comprehensive information on potential hazards, recommended precautions, and proper safety measures. Accessing and understanding this document demonstrates a responsible approach to workplace safety and helps protect both users and the surrounding environment.

For your safety and best practices, always refer to the MSDS before use

The rights of the buyer with regard to the quality of our materials are based on our terms and conditions of sale and delivery. Our technical advice team will be happy to advise you in the case of requirements that exceed the scope of the application described here. In order to be binding, a legally binding written confirmation is required. The product description does not release the user from a duty of care. Lay a test area in the event of uncertainty. This version becomes invalid in the event of a new version being issued.

BD Marketing by LIQUIMIX.