

WHERE TO USE

To protect fresh concrete from rapid water evaporation caused by wind or sunlight and to reduce Surface cracking

TECHNICAL CHARACTERISTICS

Lique Cure-E25 is a white water emulsion of special resins which forms an even elastic film on concrete that is impermeable to water and air. Lique Cure-E25 provides reliable protection against rapid evaporation of water in concrete, whether exposed to direct sunlight or under severe rapid drying conditions caused by wind, low humidity, or high ambient or concrete temperatures.

SOME APPLICATION EXAMPLES

- Lique Cure-E25 is especially recommended for protecting concrete structures such as:
- Industrial floor
- Exterior paving (road, parking lots)
- Airport runways
- Renders
- Dam faces
- Bridges
- Canals
- Reservoirs

| OFFERING ADVANTAGES |

- Improves curing of concrete, enhances hydration process and provides more durable concrete.
- Better development of mechanical strength: the absence of moisture in curing concrete can result a loss of strength of up to 50%.
- Better resistance to wear.
- Less surface dusting.
- Fast and easy application.
- Spray application is possible.

STANDARD COMPLIANCE

Lique Cure-E25 gives 75% or greater curing efficiency when tested to BS7542 and complies with BS8110 Part-1, clause 6.6.3(c) and ASTM C309.

USER GUIDE

Lique Cure-E25 should be stirred before use to ensure even dispersal of the pigment. Should be applied to the surface of the concrete after initial evaporation. For industrial paving, Lique Cure-E25 must be applied after the concrete has started to set.

For formed concrete Lique Cure-E25 must be applied immediately after stripping the formwork, in such cases surface must be damp and not completely dry.

RECOMMENDATIONS

Lique Cure-E25 interferes with the bonding of any other niching product. Its use is therefore not recommended for concrete curing or renders when levelling or painting is required (unless thoroughly cleaned with a bush hammer or by sanding to remove the product).

If applied on horizontal surfaces such as roads, parking lots and airport runways, in an amount higher than species, and if not removed, the surface could be slippery for rubber type vehicles. To ensure complete removal the usage of high-pressure steam, water jet or light sandblasting is recommended.

PREPARING THE PRODUCT

Carefully mix Lique Cure-E25 before applying. Lique Cure-E25 must be used without any other dilution.

CLEANING

Spray tools must be cleaned with water before Lique Cure-E25 dries.

PACKAGING

Lique Cure-E25 is supplied in 20 kg, 200 kg & 250 Kg Drums.

APPLYING THE PRODUCT

Apply Lique Cure-E25 in one spray coat with approx. 1 atmosphere of pressure in a thin and even layer. After approx. 2-3 hours at +20°C Lique Cure-E25 will be resistant to rain and washing.

CONSUMPTION

Lique Cure-E25 coverage is 3.5-5.0 m² /liter.

STORAGE

Lique Cure-E25 may be stored for 12 months in closed containers; protected from frost and from exposure to direct sunlight. The storage temperature must be between +5°C and +30°C.

SAFETY INSTRUCTIONS FOR PREPARATION AND APPLICATION

Lique Cure-E25 is not considered as dangerous according to the current regulation regarding the classification of mixtures. It is however recommended to use protection gloves and goggles and to take the usual precautions for handling chemicals.

For further and complete information about the safe use of our product please refer to the latest version of our Material Safety Data Sheet.

TECHNICAL DATA (Typical Values)

PRODUCT IDENTIFICATION

Consistency	aid
Color	white
Density (g/cm ³)	0.97 ± 0.02
Main action	surface concrete protection against rapid water evaporation

APPLICATION DATA

Application temperature	from +5°C to +30°C
Tack-free time at +20°C	2-3 hours

IMPORTANT NOTES: Whilst we try to ensure that any advice, recommendations or information given in our literature is accurate and correct, we have no control over the circumstances in which our product is used. It is therefore important that installers satisfy themselves that the product and conditions are suitable for the envisaged application. No warranty can be given or responsibility accepted other than, that the product supplied by us will meet our written specification. The installer should ensure that our latest product data and safety information sheets have been consulted prior to use