

DESCRIPTION

Lique Hydro-guard 3x is a next-generation, two-component-enhanced, high-performance elastomeric waterproofing system. Engineered with an advanced ultra-flexible polymer-modified cementitious matrix, it provides superior protection for concrete and masonry surfaces against extreme hydrostatic pressure and structural movement.

KEY USES

This seamless membrane is specifically designed for areas requiring maximum water tightness and durability:

- **Roofing Systems:** Exposed roofs and podium decks.
- **Wet Areas:** Comprehensive sealing for bathrooms, kitchens, and balconies.
- **Water Containment:** Potable water tanks, swimming pools, and industrial reservoirs.

PERFORMANCE ADVANTAGES

- **Ultra-Low VOC:** Environmentally friendly and safe for enclosed spaces.
- **Advanced Adhesion:** Superior bonding to damp substrates without the need for a primer.
- **Dynamic Crack Bridging:** High elasticity allows the membrane to bridge structural cracks up to 1.5 mm.
- **Traffic Ready:** Durable enough to withstand foot traffic once fully cured.
- **Potable Water Safe:** Tested for compatibility with drinking water sources.

Technical Properties

TECHNICAL DATA (typical values)		
Property	Test Method	Typical Values
Pot Life at 27°C	-	Approx. 1.5 hours
Adhesion to Substrate	ASTM D4541	>1.5~N/mm ²
Tensile Strength	ASTM D412	>1.20~N/mm ²
Elongation at Break	ASTM D412	>200%
Shore A Hardness	ASTM D2240	82.00
Crack Bridging	ASTM C1305	Up to 1.5 mm
Water Permeability	EN12390 (Part 8)	Nil (Negative & Positive Pressure)
Foot Traffic	-	After Cure

APPLICATION GUIDELINES

1. Surface Preparation

All surfaces must be structurally sound and clean. Remove all oil, grease, wax, and debris. Deeply disintegrated concrete should be repaired using an approved repair mortar system before application.

2. Mixing

- Pour the Lique Hydro-guard 3x liquid into a clean mixing container.
- Add the powder component gradually while mixing with a slow-speed drill (350-450 rpm).
- Mix for 4-5 minutes until a smooth, lump-free consistency is reached.

3. Application Method

- **Pre-Wetting:** Dampen the surface with clean water before application for optimal results.
- **Coating:** Apply using a stiff brush, roller, or airless spray equipment.
- **Thickness:** Apply in two coats of 500 μ m each to achieve a total dry film thickness of 1.0 mm.
- **Curing:** Allow the first coat to reach a "thumb-print" dry state before applying the second coat.

SUPPLY & COVERAGE

Packaging: 25 kg kits (15 kg powder / 10 kg liquid).

Coverage: Approximately 16~m² per 25 kg pack at 1.0 mm thickness. Note: Practical coverage may vary based on substrate porosity and application technique.

Storage & Safety

Shelf Life: 12 months in original, unopened packaging when stored in dry conditions.

Safety: Non-toxic but alkaline. Use gloves, goggles, and a dust mask during mixing and application. Flush with water immediately in case of contact with eyes or skin.