

DESCRIPTION

Lique Plastorix -500 is based on Sulphonate Naphthalene Polymers and supplied as a Dark brown liquid. Lique Plastorix -500 has been specially formulated to give high water reductions up to 25 % without loss of workability or to produce high quality concrete of reduced permeability.

USES

- Site Mixed Concrete
- To produce concrete with extreme workability characteristics
- Pumped concrete
- Precast/ pre stress concrete
- To maintain minimum water cement ratio in concrete
- To produce high grade concrete M30 and above by high water reduction in the concrete mix design
- High performance grout and wet shotcrete mixes

ADVANTAGES

- High early strength accelerated construction
- Controlled set times
- Lower Concrete Viscosity
- Improved cohesion and particle dispersion minimizes segregation & bleeding and improved pumpability
- Improved density and surface finish
- Feasible to use to make good far face concrete
- Chloride free dose not attack reinforcement and pre stressed cable.
- Reduce porosity of the Concrete and increased durability.

TECHNICAL SUPPORT

Lique Mix provides a technical advisory service for onsite assistance and advice on mix design, admixture selection, evaluation trials and dispensing equipment.

TECHNICAL DATA

Appearance	Dark Brown
pH	Minimum 6.0 * / Maximum 7.8*
Specific Gravity	1.21 + 0.02 at 250 C
Viscosity	450+200 cPs
Salt Scaling Resistance	90%-95%

DOSAGE

The optimum dosage is best determined by site trials with the concrete mix which enables the effects of workability, strength gain or cement reduction to be measured. Site trials with Lique Plastorix -500 conforms to ASTM should always be compared with mix containing no admixture. As a guide, the rate of addition is generally in the range of 400 ml to 1200 ml per 100 kg cement. For good quality workable concrete the ideal dose of Lique Plastorix -500 lies from 0.7% to 1.2% by weight of cement used in the mix design

STANDARD COMPLIANCE

Lique Plastorix -500 complies with IS 9103:1999 & EN 934-2:T3.1/3.2. conforms to ASTM C-494, Type 'A', and Type 'F'.

PACKAGING

Lique Plastorix -500 is packaged depending on customer's demand. We are already supplied with Plastisol -P200 in 4kg, 10kg, 20kg, 25kg, 200kg & 250 kg plastic drum.

HEALTH AND SAFETY

Lique Plastorix -500 does not fall into the hazard classifications of current regulations. However, it should not be swallowed or Lique Plastorix -500 allowed to come into contact with skin and eyes.

COMPATIBILITY

Lique Plastorix -500 is compatible with most admixtures used in the production of quality Concrete including normal, other mid-range and high-range water-reducing admixture, air entrainers, accelerators, retarders, extended set control admixtures, corrosion inhibitors and shrinkage reducers and all types of water integral admixtures. Lique Plastorix -500 is also compatible with slag and pozzolans such as fly ash, metakaolin and silica fume.

APPLICATION

- LNG reservoir, Transit railroad, Highway, Subway, Tunnel, Bridge
- Self-compacting concrete High-rise buildings with high durability
- Off-shore & marine structure
- Pre-cast & Prestressed elements
- Improve density and surface finish.
- Reduced shrinkage and creep

CAUTION

Do not allow product to freeze or be stored in temperature below freezing

- Non-flammable & Non-toxic.
- When contact with skin or clothing, wash with water

SHELF LIFE AND STORAGE

Lique Plastorix -500 has a minimum shelf life of 12 months from the date of manufacture when stored under normal temperature. Lique Plastorix -500 must be stored normal where temperature do not drop below +5°C. If product has frozen, thaw +5°C or above and completely reconstitute using mild mechanical agitation. Store under Failure to comply with the recommended deterioration of the product or packaging.