

Rietveld Refinement of FCC Ni (Log Intensity Scale)
Yobs.
Ycalc.
Ybkg.
Rwp/GoF = 6.680/0.313
Fm-3m cubic phase (Ni) | Size: 0.130μ (iso.) | Strain: 1133.429 (iso.)
Lattice: a/b/c=3.5225/3.5225/3.5225 (α/β/γ=90.00/90.00/90.00)
Intensity
Ni
Scattering vector q (Å−1)