

ALCANTARA®

Alcantara® Bord FR

Code 5056

Application

Marine Wall Covering

Main Characteristics

COMPOSITION	ALCANTARA®	Polyester Polyurethane	70 ± 3 % 30 ± 3 %
FR CONTENT			(*) 30 ± 3 %
THICKNESS			0.4 ± 0.05 mm
UNIT WEIGHT		UNI EN 29073-1	150 ± 50 g/m2
WIDTH			≥ 142 cm
BREAKING LOAD	Lenghtwise Crosswise	UNI EN 29073-3	≥ 60 N ≥ 40 N
FLAME RESISTANCE		IMO RES A653 (ISO 5658) Calorific value (ISO 1716) Smoke Density (ISO 5659/2)	Complies ≤ 44.9 MJ/m2 ≤ 200

COLOR FASTNESS (***)

TO LIGHT	Xenotest Beta-240 h	UNI EN ISO 105 B02	≥ 5 blue scale (1-8)
TO RUBBING	Dry Wet	UNI EN ISO 105 X12	≥ 4 grey scale (1-5) ≥ 3 grey scale (1-5)
TO WATER	Tone Change Staining	EN ISO 105 E01	≥ 4 grey scale (1-5) ≥ 3.5 grey scale (1-5)

(*) Referred to ALCANTARA®

(**) Slight change in the appearance of product surface

(***) Slight shade variations from one production batch to another one are possible on these products

GENERAL WASHING

