

ALCANTARA®

ALCANTARA® EXO

Cod. 5143

Application

Upholstery Outdoor

Main Characteristics

COMPOSITION	ALCANTARA®	Polyester	71 ± 3 %
	Backing	Polyurethane Polyester	29 ± 3 % 100%
THICKNESS			≤ 1.30 mm
UNIT WEIGHT		UNI EN 29073-1	≥ 310 g/m ²
WIDTH			≥ 142 cm
DIMENSIONAL STABILITY	Water 40°C	UNI EN ISO 5077 + 6330	± 3 %
BREAKING LOAD	Lenghtwise	UNI EN 29073-3	≥ 600 N/5cm
	Crosswise		≥ 400 N/5cm
ELONGATION AT 50 N	Lenghtwise	UNI EN ISO 13934-1	≥ 2.5 %
	Crosswise		≥ 6 %
TEAR STRENGTH	Lenghtwise	UNI EN ISO 13937-3	≥ 30 N
	Crosswise		
MARTINDALE ABRASION 12kPa		EN ISO 12947-4	(*) ≥ 20000 cycles
	END POINT	EN ISO 12947-2	≥ 150000 cycles
SLIPPAGE RESISTANCE OF YARNS AT SEAM	Lenghtwise	EN ISO 13936-2	≤ 6 mm
	Crosswise		
RESISTANCE TO PILLING	2000 cycles	EN ISO 12945-2	≥ 4/5
WATER IMPERMEABILITY		EN 20811	≥ 2 meters (water)
VAPOUR PERMEABILITY		UNI 4818-26	≥ 300 g/m ² /day

Color Fastness (**)

TO LIGHT	Xenotest Beta Q-Sun	UNI EN ISO 105 B02 ASTM G154-06 cycle 2	≥ 7 blue scale (1-8) ≥ 3 grey scale (1-5)
TO DOMESTIC WASHING	Tone change Staining	UNI EN ISO 105 C06	≥ 4 grey scale (1-5) ≥ 3 grey scale (1-5)
TO DRY CLEANING	Tone change Staining	AATCC 132	≥ 4 grey scale (1-5) ≥ 3 grey scale (1-5)
TO RUBBING	Dry Wet	UNI EN ISO 105 X12	≥ 4 grey scale (1-5) ≥ 3 grey scale (1-5)
TO WATER	Tone change Staining	EN ISO 105 E01	≥ 4 grey scale (1-5) ≥ 3.5 grey scale (1-5)

General Washing



(*) Slight change in the appearance of product surface

(**) Slight shade variations from one production batch to another one are possible on these products