

ALCANTARA®

ALCANTARA® 0.8 Regular

Cod. 5015 (BP)

Application

Apparel Accessories

Main Characteristics

COMPOSITION	ALCANTARA®	Polyester	68 ± 3 %
		Polyurethane	32 ± 3 %
Biobased material content		ASTM D 6866-20	≥ 12 pMC
THICKNESS			0.83 ± 0.1 mm
UNIT WEIGHT		UNI EN 29073-1	230 ± 30 g/m2
WIDTH			≥ 142 cm
DIMENSIONAL STABILITY	Water 40°C	UNI EN ISO 25077 + 6330	≤ 3 %
BREAKING LOAD	Lenghtwise Crosswise	UNI EN 29073-3	≥ 225 N ≥ 175 N
ELONGATION AT 50 N	Lenghtwise Crosswise	UNI EN 29073-3	≥ 2.5 % ≥ 14 %
TEAR STRENGTH	Lenghtwise Crosswise	EN ISO 13937-1	≥ 5 N ≥ 3.5 N
ABRASION RESISTANCE	Schiefer	ASTM-D4158	≥ 150 cycles

Color Fastness (*)

TO LIGHT	Xenotest Beta - 36h	UNI EN ISO 105 B02	≥ 5.5 blue scale (1-8)
TO DOMESTIC WASHING	Tone change Staining	UNI EN ISO 105 C06	≥ 4 grey scale (1-5) ≥ 3 grey scale (1-5)
TO DRY CLEANING	Tone change Staining	AATCC 132	≥ 4 grey scale (1-5) ≥ 3 grey scale (1-5)
TO RUBBING	Dry Wet	UNI EN ISO 105 X12	≥ 4 grey scale (1-5) ≥ 3 grey scale (1-5)
TO PERSPIRATION	Acid Alkaline	UNI EN ISO 105 E04	≥ 4.5 grey scale (1-5) ≥ 4.5 grey scale (1-5)

General Washing



(*) Slight shade variations from one production batch to another one are possible on these products
In case of items manufactured using different materials, always verify the compatibility of the same

