

ALCANTARA®

ALCANTARA® 0.4 Thin

Cod. 5030 Rev. May 2022

Application

Consumer Electronics

Main Characteristics

COMPOSITION	ALCANTARA®	Polyester Polyurethane	70 ± 3 % 30 ± 3 %
THICKNESS			0.40 ± 0.05 mm
UNIT WEIGHT		UNI EN 29073-1	130 ± 30 g/m2
WIDTH			≥ 142 cm
TENSILE STRENGTH	Lenghtwise Crosswise	ASTM D 5035	≥ 60 N ≥ 40 N
TEAR STRENGTH	Lenghtwise Crosswise	ASTM D 2261	≥ 3.5 N ≥ 2 N
MARTINDALE ABRASION	25K cycles - 9kpa	ISO 12947-4	≥ 3.5

Color Fastness (*)

TO LIGHT	96 hours	ASTM D4459	≥ 4 grey scale (1-5)
TO RUBBING	Dry Wet	UNI EN ISO 105 X12	≥ 4 grey scale (1-5) ≥ 4 grey scale (1-5)
TO PERSPIRATION	Acid Basic	UNI EN ISO 105 E04	≥ 4 grey scale (1-5) ≥ 4 grey scale (1-5)

(*) Slight shade variations from one production batch to another one are possible on these products
In case of items manufactured using different materials, always verify the compatibility of the same

