

(19)



(11)

EP 3 597 703 B1

(12)

EUROPEAN PATENT SPECIFICATION

(45) Date of publication and mention
of the grant of the patent:
06.10.2021 Bulletin 2021/40

(51) Int Cl.:
C08L 79/04 ^(2006.01) **C08L 51/04** ^(2006.01)
C08K 3/36 ^(2006.01) **C08J 5/24** ^(2006.01)

(21) Application number: **18767255.5**

(86) International application number:
PCT/JP2018/007445

(22) Date of filing: **28.02.2018**

(87) International publication number:
WO 2018/168461 (20.09.2018 Gazette 2018/38)

(54) CYANATE ESTER RESIN COMPOSITION AND PREPREG

CYANATESTERHARZZUSAMMENSETZUNG UND PREPREG

COMPOSITION DE RÉSINE D'ESTER DE CYANATE ET PRÉIMPRÉGNÉ

(84) Designated Contracting States:
**AL AT BE BG CH CY CZ DE DK EE ES FI FR GB
GR HR HU IE IS IT LI LT LU LV MC MK MT NL NO
PL PT RO RS SE SI SK SM TR**

(30) Priority: **13.03.2017 JP 2017046905**

(43) Date of publication of application:
22.01.2020 Bulletin 2020/04

(73) Proprietor: **The Yokohama Rubber Co., Ltd.
Minato-ku
Tokyo 105-8685 (JP)**

(72) Inventors:
• **IWATA, Mitsuhiro
Hiratsuka-shi
Kanagawa 254-8601 (JP)**

• **KAMIMURA, Yukihiro
Hiratsuka-shi
Kanagawa 254-8601 (JP)**
• **ITO, Tomohiro
Hiratsuka-shi
Kanagawa 254-8601 (JP)**

(74) Representative: **Dilg, Haeusler, Schindelmann
Patentanwalts-gesellschaft mbH
Leonrodstraße 58
80636 München (DE)**

(56) References cited:
**WO-A1-2016/060166 JP-A- S62 146 927
JP-A- 2009 013 254 JP-A- 2013 064 136
JP-A- 2016 210 993 US-A1- 2012 111 621
US-A1- 2013 045 650**

Note: Within nine months of the publication of the mention of the grant of the European patent in the European Patent Bulletin, any person may give notice to the European Patent Office of opposition to that patent, in accordance with the Implementing Regulations. Notice of opposition shall not be deemed to have been filed until the opposition fee has been paid. (Art. 99(1) European Patent Convention).

EP 3 597 703 B1

Description

Technical Field

5 **[0001]** The present invention relates to a cyanate ester resin composition and a prepreg.

Background Art

10 **[0002]** Fiber-reinforced composite materials with thermosetting resins including epoxy resins as a matrix are known. For example, Patent Document 1 discloses an epoxy resin composition containing an epoxy resin as a matrix, a thermoplastic resin for viscosity adjustment, a filler, and a curing agent, and a prepreg obtained by combining the composition and a reinforcing fiber. Such a prepreg is used in a wide range of fields including structural materials such as aircrafts and vehicles, reinforcing of concrete structures, sports fields such as golf clubs, tennis rackets, and fishing rods because of its lightness and excellent mechanical properties.

15 **[0003]** One of the characteristics required for the prepreg used in such applications includes heat resistance. Therefore, various fiber-reinforced composite materials having a resin with higher heat resistance than epoxy resins as a matrix have been investigated.

Citation List

20

Patent Document

[0004] Patent Document 1: JP 2011-99094 A

25 Summary of the Invention

Technical Problem

30 **[0005]** Resins that may substitute for epoxy resins include cyanate ester resins. Cyanate ester resins have superior heat resistance than epoxy resins, and can withstand heat up to near 300°C, for example.

[0006] However, cyanate ester resins have the problem that the thermoplastic resin for viscosity adjustment is difficult to dissolve, the viscosity adjustment of the resin composition is difficult, and the resin has a high viscosity at room temperature but has a low viscosity during curing heating. Due to this problem, when the prepreg is heat cured, the resin composition flows out of the reinforcing fiber, and resin defects occur in the obtained fiber-reinforced composite material, and the thickness is non-even. In order to suppress resin flow during curing, the viscosity of the resin composition needs to be higher, but in this case, the viscosity of the resin composition at room temperature is too high, so the workability during prepreg molding will be negatively affected.

35 **[0007]** Therefore, an object of the present invention is to provide a cyanate ester resin composition that can suppress the resin flow during heating and curing without adding a thermoplastic resin for viscosity adjustment, eliminate resin defects and uneven thickness, and have excellent workability, and to provide a prepreg using the same.

40

Solution to Problem

45 **[0008]** As a result of diligent research, the present inventors discovered that the problem can be solved by adding a curing agent or a curing accelerator, silica microparticles, and core-shell rubber particles to a cyanate ester resin and limiting the compounding ratio of silica microparticles and core-shell rubber particles with respect to cyanate ester resin to a specified ratio, and thus completed the present invention.

[0009] The present invention is described as follows.

[0010]

50

1. A cyanate ester resin composition, containing: a cyanate ester resin (A); a curing agent or a curing accelerator (B); silica microparticles (C); and core-shell rubber particles (D); in which the resin composition includes: from 1 to 5 parts by mass of the silica microparticles (C) and from 2 to 10 parts by mass of the core-shell rubber particles (D) based on 100 parts by mass of the cyanate ester resin (A), and a mass ratio of the silica microparticles (C) to the core-shell rubber particles (D) is from 1/1 to 1/5 as (C)/(D).

55

2. The cyanate ester resin composition according to 1, in which a $\tan \delta$ at a strain 1% is less than 1 and a $\tan \delta$ at a strain 100% is 1 or greater when viscoelasticity is measured at a temperature of 70°C and a frequency 1 Hz on a parallel plate.

3. The cyanate ester resin composition according to 1, in which the cyanate ester resin (A) is a novolac type cyanate ester resin.
4. The cyanate ester resin composition according to 1, in which a compounded amount of the silica microparticles (C) per 100 parts by mass of the cyanate ester resin (A) is from 2 to 4 parts by mass.
5. The cyanate ester resin composition according to 1, in which a compounded amount of the core-shell rubber particles (D) per 100 parts by mass of the cyanate ester resin (A) is from 4 to 8 parts by mass.
6. The cyanate ester resin composition according to 1, in which a mass ratio of the silica microparticles (C) to the core-shell rubber particles (D) is from 1/1.5 to 1/4 as (C)/(D).
7. A prepreg containing the cyanate ester resin composition described in any one of 1 to 6 and a reinforcing fiber.
8. The prepreg according to 7, in which a content of the cyanate ester resin composition in the prepreg is from 30 to 60 mass%.

Advantageous Effects of Invention

[0011] According to the present invention, because the curing agent or the curing accelerator (B), the silica microparticles (C), and the core-shell rubber particles (D) are added to the cyanate ester resin (A), and the compounding ratio of the silica microparticles (C) and the core-shell rubber particles (D) to the cyanate ester resin (A) is limited into a specified ratio, the cyanate ester resin composition that can suppress the resin flow during heating and curing without adding a thermoplastic resin for viscosity adjustment, eliminate resin defects and uneven thickness, and have excellent workability can be provided.

[0012] In addition, the cyanate ester resin composition of the present invention in which a $\tan \delta$ at a strain 1% is less than 1 and a $\tan \delta$ at a strain 100% is 1 or greater when viscoelasticity is measured at a temperature of 70°C and a frequency 1 Hz on a parallel plate has excellent suppression of the resin flow during heating and curing, the elimination of resin defects and uneven thickness, and workability.


[0013] Furthermore, the prepreg formed from the cyanate ester resin composition and the reinforcing fiber has excellent heat resistance, and also has excellent mechanical strength because resin defects and uneven thickness are also suppressed.

Description of Embodiments

[0014] Hereinafter, embodiments of the present invention will be described in more detail.

(A) Cyanate ester resin

[0015] The cyanate ester resin (A) used in the present invention is not particularly limited. Generally, the cyanate ester resin is represented by the following formula:



(R represents a divalent or higher organic group having an aromatic ring, and n represents an integer of 2 or greater).

[0016] Examples of such cyanate ester resins include novolac type, bisphenol A type, bisphenol E type, and bisphenol F type cyanate ester resins. Among them, novolac type cyanate ester resins are preferred.

[0017] Commercially available novolac type resins can be used, and examples thereof include PRIMASET PT-30 and PRIMASET PT-60 available from LONZA Japan.

(B) Curing agent or curing accelerator

[0018] The curing agent or curing accelerator (B) used in the present invention is not particularly limited as long as it is capable of promoting thermal curing of the cyanate ester resin, but examples include metal complexes such as cobalt or copper, alcohols, acids, amines, bases, and the like.

(C) Silica microparticles

[0019] The silica microparticles (C) are preferably hydrophilic silica microparticles. Examples include non-crystalline synthetic silica such as precipitated silica, gel-method silica, pyrolyzing silica, and fused silica; crystalline synthetic silica; and natural silica.

[0020] The average primary particle size of the silica microparticles (C) is preferably from 5 nm to 100 nm.

(D) Core-shell rubber particles

[0021] The core-shell rubber particles (D) used in the present invention are known, and can be, for example, particles obtained by graft polymerization of a shell component polymer that is different from the core component on the surface of the particulate core component containing a crosslinked rubberlike polymer as a main component.

[0022] Examples of the core component include butadiene rubber, acrylic rubber, silicone rubber, butyl rubber, NBR, SBR, IR, and EPR.

[0023] Example of the shell component includes a polymer obtained by polymerizing a monomer selected from acrylic acid ester-based monomers, methacrylic acid ester-based monomers, aromatic vinyl monomers, and the like.

[0024] The average particle size of the core-shell rubber particles (D) is, for example, from 10 nm to 10 μm , and preferably from 100 nm to 500 nm.

Compounding ratio

[0025] The cyanate ester resin composition of the present invention is required that from 1 to 5 parts by mass of silica microparticles (C) and from 2 to 10 parts by mass of core-shell rubber particles (D) is included based on 100 parts by mass of the cyanate ester resin (A), and a mass ratio of silica microparticles (C) to core-shell rubber particles (D) is from 1/1 to 1/5 as (C)/(D).

[0026] (C) In a case where the compounding ratio of the silica microparticles (C) is less than 1 part by mass or the compounding ratio of the core-shell rubber particles (D) is less than 2 parts by mass, the suppression of the resin flow is insufficient, and the effect of the present invention cannot be achieved.

[0027] (C) In a case where the compounding ratio of the silica microparticles (C) exceeds 5 parts by mass, or the compounding ratio of the core-shell rubber particles (D) exceeds 10 parts by mass, the viscosity of the resin composition increases, the workability is negatively affected, and the mechanical properties (mainly elastic modulus) of the cured product will decline.

[0028] (C) In a case where the mass ratio of the silica microparticles (C) to the core-shell rubber particles (D) is greater than 1/1 as (C)/(D), that is, when the compounded amount of the component (D) is smaller than that of the component (C), the resin flow is insufficient, and the effect of the present invention cannot be achieved.

[0029] (C) In a case where the mass ratio of the silica microparticles (C) to the core-shell rubber particles (D) is less than 1/5 as (C)/(D), that is, when the compounded amount of the component (D) is too high with respect to that of the component (C), the resin flow suppression effect will be too high, so the workability during prepreg molding will be negatively affected.

[0030] In the present invention, the compounded amount of the silica microparticles (C) per 100 parts by mass of the cyanate ester resin (A) is more preferably from 2 to 4 parts by mass, and the compounded amount of the core-shell rubber particles (D) is more preferably from 4 to 8 parts by mass, and the mass ratio of the silica microparticles (C) to the core-shell rubber particles (D) is more preferably from 1/1.5 to 1/4 as (C)/(D).

[0031] Since in the cyanate ester resin composition of the present invention, a $\tan \delta$ at the strain 1% is less than 1 and a $\tan \delta$ at a strain 100% is 1 or greater when viscoelasticity is measured at a temperature of 70°C and a frequency 1 Hz on a parallel plate, the resin has excellent suppression of the resin flow during heating and curing, the elimination of resin defects and uneven thickness, and workability. Note that the measurement of viscoelasticity can be measured by using the trade name ARES manufactured by TA Instruments. Furthermore, the viscoelasticity described above can be achieved by appropriately setting the compounded amount of the silica microparticles (C) and the core-shell rubber particles (D) to the cyanate ester resin as described above.

[0032] The cyanate ester resin composition of the present invention can include other additives as needed. Examples of the additives include fillers, anti-aging agents, solvents, flame retardants, reaction retarders, antioxidants, pigments (dyes), plasticizers, thixotropic agents, UV absorbers, surfactants (including leveling agents), dispersants, dewatering agents, adhesion promoters, and anti-static agents.

[0033] The prepreg of the present invention comprises the cyanate ester resin composition of the present invention and the reinforcing fiber. Specifically, the prepreg of the present invention is obtained by impregnating the reinforcing fiber with the cyanate ester resin composition of the present invention.

[0034] The reinforcing fiber used in the prepreg of the present invention is not particularly limited, and examples thereof include known products. Of these, from the perspective of strength, the reinforcing fiber is preferably at least one selected from the group consisting of carbon fiber, glass fiber, and aramid fiber.

[0035] The form of the fiber is not particularly limited, and examples thereof include roving, fiber obtained by lining up roving, woven fabric, nonwoven fabric, knitted fabric, and tulle.

[0036] A method of manufacturing the prepreg of the present invention is not particularly limited. Examples thereof include wet methods using a solvent and hot-melt methods (solvent-free methods). From the perspective of being able to reduce drying time, an amount of the solvent used is preferably from 80 to 200 parts by mass per 100 parts by mass

of the solid content of the cyanate ester resin composition.

[0037] In the prepreg of the present invention, the content of cyanate ester resin composition is preferably from 30 to 60 mass% in the prepreg from the perspective of the mechanical properties of the resulting fiber-reinforced composite material.

[0038] Use of the prepreg of the present invention is not particularly limited. For example, a known fiber-reinforced composite material can be obtained by curing the prepreg of the present invention. Specific examples of uses include aircraft parts (e.g. fairings, flaps, leading edges, floor panels, propellers, fuselages, and the like); two-wheel vehicle parts (e.g. motorcycle frames, cowls, fenders, and the like); automobile parts (e.g. doors, bonnets, tailgates, side fenders, side panels, fenders, energy absorbers, trunk lids, hard tops, side mirror covers, spoilers, diffusers, ski carriers, engine cylinder covers, engine hoods, chassis, air spoilers, propeller shafts, and the like); vehicle exterior plating (e.g. lead car noses, roofs, side panels, doors, truck bed covers, side skirts, and the like); railroad vehicle parts (e.g. luggage racks, seats, and the like); aero parts (e.g. side skirts and the like mounted on automobiles and rigid vehicles such as interior design elements, inner panels, outer panels, roofs, and floors of wings on wing trucks, and the like); use as housings (e.g. notebook computers, portable phones, and the like); medical uses (e.g. X-ray cassettes, table tops, and the like); audio product uses (e.g. flat speaker panels, speaker cones, and the like); sports goods uses (e.g. golf club heads, face masks, snowboards, surf boards, protectors, and the like); and general industrial uses (e.g. flat springs, windmill blades, and elevators (compartment panels, doors)).

[0039] Additionally, a fiber-reinforced composite material can be fabricated by layering the prepreg of the present invention and another member (e.g. a honeycomb core). Examples of the fiber-reinforced composite material that can be fabricated by layering the prepreg of the present invention and another member include honeycomb sandwich panels.

Example

[0040] The present invention will be described in further detail by way of examples and comparative examples.

[0041] The following materials were used in the examples below.

(A) Cyanate ester resin: PRIMASET PT-30 and PRIMASET PT-60 manufactured by LONZA Japan (novolac type cyanate ester resin)

(B) Curing agent or curing accelerator: DICY - 15 (dicyandiamide) available from Mitsubishi Chemical Corporation

(C) Silica microparticles: CAB-O-SIL M5 (hydrophilic fumed silica) available from Cabot Corporation

(D) Core-shell rubber particles: MX-154 (Epoxy Resin/Core-Shell Rubber Particle Master Batch, containing 40 mass% of butadiene-based core-shell rubber particles)

[0042] Various cyanate ester resin compositions were prepared by kneading each of the materials using a kneader at 70°C according to the compounding ratio (parts by mass) shown in Table 1 below.

[0043] The following measurements were performed on the various cyanate ester resin compositions obtained.

[0044] Viscoelasticity: The $\tan \delta$ at strain 1% or 100% was measured on a parallel plate under conditions of a temperature of 70°C and a frequency of 1 Hz using ARES available from TA Instruments.

Molding prepreg

[0045] The cyanate ester resin composition film (resin weight 104 g/m²) was impregnated into the glass fiber fabric (fiber basis weight 156 g/m²) to mold a prepreg. The cyanate ester resin composition in the molded prepreg is 40 mass%.

[0046] Resin flow: The prepreg was cut into 100 mm × 100 mm, and four sheets of cut prepreps were laminated, and pressed at a temperature of 180°C and a pressure of 3 kgf/cm² for 30 min. The weight of the resin cured product protruded from the fiber was measured, and the resin flow was calculated using the following equation.

$$\text{Resin flow (\%)} = (\text{weight of protruded resin cured product}) / (\text{weight of laminate before pressing}) \times 100$$

[0047] Workability: The workability when preparing the cyanate ester resin composition film and when impregnating the glass fiber fabric was evaluated according to the following evaluation criteria.

Good: Good film preparing and good impregnability to glass fiber fabric

Poor: Prepreg cannot be molded due to difficulty in preparing the film

[0048] Dimensional Stability: The prepreg was cut into 300 mm × 300 mm, ten sheets of cut prepreps were laminated,

EP 3 597 703 B1

and cured in an autoclave at 180°C for 2 hours to obtain a fiber-reinforced composite material. The thickness of the obtained fiber-reinforced composite material was measured. When the difference between the maximum thickness and the minimum thickness was 5% or less of the maximum thickness, the dimensional stability was determined to be good. [0049] The results are shown in Table 1.

5

10

15

20

25

30

35

40

45

50

55

[Table 1]

(Part by mass)										
Material	Product name	Example 1	Example 2	Example 3	Example 4	Comparative Example 1	Comparative Example 2	Comparative Example 3	Comparative Example 4	
(A) Cyanate ester resin	PT-30	100	70	70	70	100	100	70	70	
	PT-60	-	30	30	30	-	-	30	30	
(B) Curing agent or curing accelerator	DICY-15	1	1	1	1	1	1	1	1	
(C) Silica microparticles	CAB-O-SIL M5	2	2	4	2	2	-	1	6	
(D) Epoxy resin/core-shell rubber particle master batch	MX-154	10	10	10	25	-	10	2.5	30	
Core-shell rubber particles in the master batch		4	4	4	10	-	4	1	12	
Viscoelasticity (strain 1%)	-	0.10	0.22	0.08	0.16	40.23	2.25	23.92	0.07	
Viscoelasticity (strain 100%)	-	1.05	2.57	1.11	1.89	42.68	4.10	27.14	0.63	
Resin Flow (%)	-	8.3	12.4	9.0	11.2	24.5	18.4	20.5	4.3	
Workability	-	Good	Good	Good	Good	Good	Good	Good	Poor	
Dimensional Stability (%)	-	4.3	4.8	3.9	4.6	12.9	10.3	9.5	-	

[0050] From the results shown in Table 1, it was found that the cyanate ester resin composition of each Examples in which the curing agent or the curing accelerator (B), the silica microparticles (C), and the core-shell rubber particles (D) are added to the cyanate ester resin (A), and the compounding ratio of the silica microparticles (C) and the core-shell rubber particles (D) to the cyanate ester resin (A) is limited into a specified ratio of the present invention can suppress the resin flow during heating and curing without adding a thermoplastic resin for viscosity adjustment, eliminate resin defects and uneven thickness, and has excellent workability. Additionally, since in the cyanate ester resin composition of each Examples, a $\tan \delta$ at a strain 1% is less than 1 and a $\tan \delta$ at a strain 100% is 1 or greater when viscoelasticity is measured at a temperature of 70°C and a frequency 1 Hz on a parallel plate, the resin composition is solid-like at low strain ($\tan \delta$ of less than 1) and can suppress the resin flow during heating and curing, and is liquid-like at high strain ($\tan \delta$ of 1 or greater) and has good workability during film applying and impregnating.

[0051] In contrast, in Comparative Example 1, the results of resin flow and dimensional stability were negatively affected because the core-shell rubber particles (D) were not added.

[0052] In Comparative Example 2, the results of resin flow and dimensional stability were negatively affected because the silica microparticles (C) were not added.

[0053] In Comparative Example 3, the results of resin flow and dimensional stability were negatively affected because the compounded amount of the core-shell rubber particles (D) was less than the lower limit specified in the present invention.

[0054] In Comparative Example 4, the results of workability was negatively affected because the compounded amount of the silica microparticles (C) and the compounded amount of the core-shell rubber particles (D) are both beyond the upper limit specified in the present invention.

Claims

1. A cyanate ester resin composition, comprising:

a cyanate ester resin (A);
a curing agent or a curing accelerator (B);
silica microparticles (C); and
core-shell rubber particles (D), wherein

the resin composition includes from 1 to 5 parts by mass of the silica microparticles (C) and from 2 to 10 parts by mass of the core-shell rubber particles (D) based on 100 parts by mass of the cyanate ester resin (A), and a mass ratio of the silica microparticles (C) to the core-shell rubber particles (D) is from 1/1 to 1/5 as (C)/(D).

2. The cyanate ester resin composition according to claim 1, wherein a $\tan \delta$ at a strain 1% is less than 1 and a $\tan \delta$ at a strain 100% is 1 or greater when viscoelasticity is measured at a temperature of 70°C and a frequency 1 Hz on a parallel plate.

3. The cyanate ester resin composition according to claim 1, wherein the cyanate ester resin (A) is a novolac type cyanate ester resin.

4. The cyanate ester resin composition according to claim 1, wherein a compounded amount of the silica microparticles (C) per 100 parts by mass of the cyanate ester resin (A) is from 2 to 4 parts by mass.

5. The cyanate ester resin composition according to claim 1, wherein a compounded amount of the core-shell rubber particles (D) per 100 parts by mass of the cyanate ester resin (A) is from 4 to 8 parts by mass.

6. The cyanate ester resin composition according to claim 1, wherein a mass ratio of the silica microparticles (C) to the core-shell rubber particles (D) is from 1/1.5 to 1/4 as (C)/(D).

7. A prepreg comprising the cyanate ester resin composition described in any one of claims 1 to 6 and a reinforcing fiber.

8. The prepreg according to claim 7, wherein a content of the cyanate ester resin composition in the prepreg is from 30 to 60 mass%.

Patentansprüche

1. Cyanatesterharzzusammensetzung, umfassend:

ein Cyanatesterharz (A);
ein Härtungsmittel oder einen Härtungsbeschleuniger (B);
Silica-Mikropartikel (C); und
Kern-Schale-Kautschukpartikel (D), wobei

die Harzzusammensetzung von 1 bis 5 Massenteile die Silica-Mikropartikel (C) und von 2 bis 10 Massenteile die Kern-Schale-Kautschukpartikel (D), basierend auf 100 Massenteilen des Cyanatesterharzes (A), einschließt, und ein Massenverhältnis der Silica-Mikropartikel (C) zu den Kern-Schale-Kautschukpartikeln (D) von 1/1 bis 1/5 (C)/(D) beträgt.

2. Cyanatesterharzzusammensetzung nach Anspruch 1, wobei ein $\tan \delta$ bei einer Dehnung von 1 % kleiner als 1 ist und ein $\tan \delta$ bei einer Dehnung von 100 % 1 oder größer ist, wenn die Viskoelastizität bei einer Temperatur von 70 °C und einer Frequenz von 1 Hz auf einer parallelen Platte gemessen wird.

3. Cyanatesterharzzusammensetzung nach Anspruch 1, wobei das Cyanatesterharz (A) ein Cyanatesterharz vom Novolaktyp ist.

4. Cyanatesterharzzusammensetzung nach Anspruch 1, wobei ein Mischanteil der Silica-Mikropartikel (C) pro 100 Massenteile des Cyanatesterharzes (A) von 2 bis 4 Massenteile beträgt.

5. Cyanatesterharzzusammensetzung nach Anspruch 1, wobei ein Mischanteil der Kern-Schale-Kautschukpartikel (D) pro 100 Massenteile des Cyanatesterharzes (A) von 4 bis 8 Massenteile beträgt.

6. Cyanatesterharzzusammensetzung nach Anspruch 1, wobei ein Massenverhältnis der Silica-Mikropartikel (C) zu den Kern-Schale-Kautschukpartikeln (D) von 1/1,5 bis 1/4 (C)/(D) beträgt.

7. Prepreg, umfassend die Cyanatesterharzzusammensetzung nach einem der Ansprüche 1 bis 6 und eine Verstärkungsfasern.

8. Prepreg nach Anspruch 7, wobei ein Gehalt der Cyanatesterharzzusammensetzung in dem Prepreg von 30 bis 60 Massen-% beträgt.

Revendications

1. Composition de résine ester de cyanate, comprenant :

une résine ester de cyanate (A) ;
un agent de durcissement ou un accélérateur de durcissement (B) ;
des microparticules de silice (C) ; et
des particules de caoutchouc à noyau-enveloppe (D), dans laquelle

la composition de résine inclut de 1 à 5 parties en masse des microparticules de silice (C) et de 2 à 10 parties en masse des particules de caoutchouc à noyau-enveloppe (D) sur la base de 100 parties en masse de la résine ester de cyanate (A), et
un rapport massique des microparticules de silice (C) aux particules de caoutchouc à noyau-enveloppe (D) va de 1/1 à 1/5 en tant que (C)/(D).

2. Composition de résine ester de cyanate selon la revendication 1, dans laquelle une $\tan \delta$ à une déformation 1 % est inférieure à 1 et une $\tan \delta$ à une déformation 100 % vaut 1 ou plus lorsque la viscoélasticité est mesurée à une température de 70 °C et à une fréquence 1 Hz sur une plaque parallèle.

3. Composition de résine ester de cyanate selon la revendication 1, dans laquelle la résine ester de cyanate (A) est une résine ester de cyanate de type novolac.

EP 3 597 703 B1

4. Composition de résine ester de cyanate selon la revendication 1, dans laquelle une quantité mélangée des micro-particules de silice (C) pour 100 parties en masse de la résine ester de cyanate (A) va de 2 à 4 parties en masse.
5. Composition de résine ester de cyanate selon la revendication 1, dans laquelle une quantité mélangée des particules de caoutchouc à noyau-enveloppe (D) pour 100 parties en masse de la résine ester de cyanate (A) va de 4 à 8 parties en masse.
6. Composition de résine ester de cyanate selon la revendication 1, dans laquelle un rapport massique des microparticules de silice (C) aux particules de caoutchouc à noyau-enveloppe (D) va de 1/1,5 à 1/4 en tant que (C)/(D).
7. Préimprégné comprenant la composition de résine ester de cyanate décrite dans l'une quelconque des revendications 1 à 6 et une fibre de renforcement.
8. Préimprégné selon la revendication 7, dans lequel une teneur de la composition de résine ester de cyanate dans le préimprégné va de 30 à 60 % en masse.

REFERENCES CITED IN THE DESCRIPTION

This list of references cited by the applicant is for the reader's convenience only. It does not form part of the European patent document. Even though great care has been taken in compiling the references, errors or omissions cannot be excluded and the EPO disclaims all liability in this regard.

Patent documents cited in the description

- JP 2011099094 A [0004]