

TABLE OF CONTENTS

S-420 PRIME COAT AND SHOP FINISH PAINTING

	Page No.
1. SCOPE OF WORK	S.420-2
2. DEFINITIONS.....	S.420-7
2.1 Contact Surfaces:	S.420-7
2.2 Inaccessible Surfaces:	S.420-7
2.3 Dft:	S.420-7
3. CODES AND STANDARDS.....	S.420-8
4. MATERIALS	S.420-8
4.1 General Provisions	S.420-8
4.2 Rustinhibiting Temporary Protection.....	S.420-9
5. DETAILED REQUIREMENTS FOR PAINTING STRUCTURES.....	S.420-10
5.1 Shop Prime Coat Painting	S.420-10
5.2 Field Prime Coat Painting	S.420-10
5.3 Field Touch-Up Painting	S.420-10
5.4 Field Touch-Up For Galvanizing.....	S.420-11
5.5 Painting Of Aluminum Contact Surfaces.....	S.420-11
6. CLEANING AND PAINTING OF EQUIPMENT AND PIPING.....	S.420-12
6.1 General	S.420-12
6.2 Cleaning And Painting Of Indoor Equipment	S.420-12
6.3 Cleaning And Painting Of Outdoor Equipment.....	S.420-13
6.4 Cleaning And Painting Of All Electrical Equipment Cubicles, Panels & Indoor Enclosures.....	S.420-13
6.5 Piping Surfaces	S.420-14
7. PERFORMANCE	S.420-14
7.1 Surface Preparation	S.420-14
7.2 Paint Application	S.420-16
8. INSPECTION	S.420-18
9. QUALITY ASSURANCE/QUALITY CONTROL (QA/QC).....	S.420-18

S.420 PRIME COAT AND SHOP FINISH PAINTING

1. SCOPE OF WORK

- 1.1 Prime coat and related painting work covered by this specification shall include Bidder's providing all material, equipment, painting and other services required for his work as indicated in Part 4, Subsections 1.2 "Summary of Work" and S-001" General Technical Requirement of Structure, Civil and Building Works" but not be limited to the following:
- 1.1.1 Painting for structural steel, gallery steel, miscellaneous steel, auxiliary steel equipment and similar ferrous metals:
- Surface preparation (shop and field)
 - Shop prime coat painting
 - Shop or field second coat painting for inaccessible surfaces
 - Shop second coat painting
 - Field prime coat painting
 - Field touch-up painting
- 1.1.2 Field touch-up for galvanizing
- 1.1.3 Painting of aluminum contact surfaces.
- 1.2 The extent of prime coat and related painting shall be as indicated in Table S-420-1 and clause 6 herein, unless otherwise indicated.

Table S-420-1 Extent of Prime Coat and Related Painting

Item	Surface Preparation	Painting	Paint System (see Table S-420-2)
1. Structural and miscellaneous ferrous steel members			
a. All surfaces including columns, beams, girder, girts, hangers, struts, tie rods, plates, handrails, posts, risers, stair, stringers, washers, etc. unless otherwise indicated	Solvent & Near White Blast Cleaning	1 shop prime coat of paint 1 shop intermediate coat	420 - A 420 - B
b. Inaccessible steel surfaces and girts	Solvent & Near White Blast Cleaning	1 shop prime coat and 2 shop intermediate coats of paint	420 - A for prime coat and 420 - B for second coats
c. Milled, embedded, contact and welded surface, etc. C.1 Milled and machined surfaces (as on base plates) C.2 Anchor bolts, bolts, nuts C.3 Embedded surfaces	None (Unless otherwise indicated herein) Solvent & Near White Blast Cleaning	No painting (milled surface protected with lacquer. All other surfaces protected with antirust compound unless otherwise indicated herein) 1 shop prime coat of paint	 420 - A

Table S-420-1 Extent of Prime Coat and Related Painting (continued)

Item	Surface Preparation	Painting	Paint System (see Table S-420-2)
C.4 Contact surfaces (as surfaces under column and beam cover plates, faying surfaces under connection angles, splice plates)	Solvent & Near White Blast Cleaning for faying surfaces & splices plates	1 shop prime coat of paint 1 shop prime coat of paint	420 - A (Base material : 60 micron and Gusset plate : 15 micron)
C.5 Top flanges of beams and girders to support metal decking or welding studs	Solvent & Near White Blast Cleaning.		420 - A
C.6 Welded surfaces (a 75 mm wide strip on each side of a joint to be field welded)	Solvent & Near White Blast Cleaning.		
d. Marred painted areas, bolt heads, nuts, washers, unprotected fasteners, field welds, and adjacent unpainted areas and strips, unless otherwise indicated	Solvent & Cleaning and Hand Tool Cleaning; if required Power Tool Cleaning	1 or 2 field touch-up coats of matching paint	421 - H for prime coat, and 421 B for second coat
e Marred galvanized areas and field welds on galvanized surfaces	Hand or Power Tool Cleaning	1 field touch-up coat of paint	420 - E

Table S-420-1 Extent of Prime Coat and Related Painting (continued)

Item	Surface Preparation	Painting	Paint System (see Table S-420-2)
2. Stainless steel, unless otherwise indicate	None	No painting	
3. Surfaces to be in contact with aluminum; or aluminum surfaces:			
a. Surfaces of non-aluminum metals incompatible with aluminum, to be in contact with aluminum; or aluminum surfaces to be in contact with incompatible non-aluminum metal surfaces.	Solvent & Commercial Blast Cleaning	1 shop of field prime coat & 1 field second coat of paint for ferrous metals, and 2 coats of paint for non-ferrous metals	420-C for prime coat, 420-D for second coat
b. Concrete and masonry surfaces to be in contact with aluminum; or aluminum surfaces to be in contact with other structures	As specified in manufacturers standards.	2 field coats of paint	420-F
4. Welded steel ducts	Solvent Cleaning and Near White Blast Cleaning on exterior surfaces of the duct to be painted unless otherwise indicated	1 shop prime coat of paint, on exterior surfaces of the duct if there is no lagging outside these surfaces	420 - A

Table S-420-1 Extent of Prime Coat and Related Painting (continued)

Item	Surface Preparation	Painting	Paint System (see Table S-420-2)
5. Metal doors and door channel frames			
5.1 Channel frames	Solvent & Commercial Blast Cleaning	1 Prime coat, 1 intermediate coat and field touch up paint	420-A and 420-B
5.2 Exterior doors (galvanized)	Solvent Cleaning	1 prime coat, 1 intermediate coat and field touch up paint	420-G and 420-B
5.3 Interior doors (sheet metal)	Solvent Cleaning and Hand Tool Cleaning	1 prime Coat.	420-H
6. Exposed steel piping for plumbing	Solvent Hand-Power Tool & Commercial Blast Cleaning	1 prime coat, 1 intermediate coat and touch-up with paint on outside surfaces, touch-up 75 mm wide welding bands	420-A and 420-B
7. Curb angle surfaces in contact with concrete	Hand Tool Cleaning	1 field coat	Termastic 100 (200 microns dry film thickness)

8. Electrical and Mechanical Equipment , Panel, Piping, etc.	Solvent & Near White Blast Cleaning	1 shop prime coat of paint	420 - A
		1 shop intermediate coat	420 - B
		1 shop finish coat	Polyurethane at 50 to 75 microns, unless otherwise recommended by manufacturer.

2. DEFINITIONS

2.1 CONTACT SURFACES:

Surfaces of ferrous metals which are permanently in contact with other surfaces of the same materials after shop assembly or field erection, such as contact surfaces at cover plates or connection angles on column, beams and girders, etc.

2.2 INACCESSIBLE SURFACES:

Surfaces of ferrous metals, which are made inaccessible for painting (other than contact surfaces) after shop assembly or field erection of the steel or metals, such as the surfaces in a members composed of two angles back to back with gusset plates between them, where these surfaces will be exposed to the weather for their service life..

2.3 DFT:

Dry film thickness expressed in microns.

3. CODES AND STANDARDS

3.1 The Bidder shall comply with the requirements of Part 4, Subsection 2.5 “Codes and Standards”.

3.2 The codes and standards of the following organizations extracted from the Part 4, subsection 2.5 “ Codes and Standards “ are specifically applicable to the design, applicable and testing of the work included in this Specification:

AISC American Institute of Steel Construction

SSPC Steel Structures Painting Council, U.S.A

JIS Japanese Industrial Standards

3.2.1 Evaluation of the Condition of Steel

SSPC Guide to Vis 1, “Pictorial Surface Preparation Standards for Painting Steel Structures”, and SSPC Vis 1.

3.2.2 Preparation Methods

- SSPC-SPI-Solvent Cleaning,
- SSPC-SP2-Hand Tool Cleaning (by wire brush)
- SSPC-SP3-Power Tool Cleaning (by power brush or power sander)
- SSPC-SP10-Near-White Blast Cleaning,

3.2.3 Paint Application

- SSPC-PA1 “Shop, Field and Maintenance Painting”
- SSPC-PA2 “Measurement of Dry Film Thickness with Magnetic Gages”

4. MATERIALS

4.1 GENERAL PROVISIONS

4.1.1 Paints, including types, colors, products and manufacturers shall be as specified in Table S-420-2 Paint System and Clause 6 or approved equivalent and shall be suitable for the environmental conditions. Use of all components of the same manufacturer’s system is mandatory.

4.1.2 Paints shall be delivered to the place of use in unbroken containers bearing the paint manufacturer’s brand name and identification number.

- 4.1.3 Each coat of paint shall be of a different discernible color.
- 4.1.4 Most of the surfaces shall receive the field finish paint as specified in S-430.
- 4.1.5 Mating and contact surfaces except faying surfaces for friction bolt shall be protected from corrosion by ensuring that the two surfaces brought into contact with each other are prepared and painted with the full specified system. Those surfaces which are brought together in the shop shall be brought together while the last coat of paint is still wet.
- 4.1.6 Unless otherwise specified, surfaces where the friction bolt is provided shall receive no paint coating. All corrosion and any products which would affect the efficiency of the joint, in particular grit, grease, and oil, shall be removed from the surfaces prior to bolting together. The edges of such joints shall be suitably sealed with paint coating.

4.2 RUSTINHIBITING TEMPORARY PROTECTION

Steel surface left unpainted in the shop shall be coated with a corrosion resistant material as approved by the Owner.

Table S-420-2 Paint System

System Designation	Type/Color of Paint	Use	Thickness
420-A	- Inorganic zinc (85 to 89 % zinc by weight) - green or grey	Prime coat for steel	50 to 75 microns dry film thickness
420-B	- Two component polyamide epoxy carboline - brown color	Intermediate coat for steel	125 to 175 microns dry film thickness
420-C	Alkyd paint/brown	Prime coat steel or aluminum	50 microns dry film thickness each coat
420-D	Alkyd paint/black	Second coat, unless otherwise indicated	50 microns dry film thickness
420-E	Zinc-rich paint/gray	Touch-up for galvanized base metal	75 microns dry film thickness
420-F	Acrylic latex paint; primer white, second coat color selected	1 or 2 coats for aluminum and bare substrate in contact	100 to 150 microns dry film thickness each coat

System Designation	Type/Color of Paint	Use	Thickness
420-G	Zinc chromate vinyl butyral/green	Wash prime for galvanized surfaces prior to painting	10 to 15 microns dry film thickness
420-H	Two component epoxy mastic primer	For steel surfaces where blast cleaning is not practical	125 to 175 microns dry film thickness

5. DETAILED REQUIREMENTS FOR PAINTING STRUCTURES

5.1 SHOP PRIME COAT PAINTING

(including shop prime, intermediate and a third coat painting for inaccessible surfaces and girts):

5.1.1 Extent of structural steel and other ferrous metal surfaces to be painted in shop and to be left unpainted in shop, after completion of the surface preparation specified in Clause 7.1 shall be as indicated in Table S-420-1.

5.1.2 Milled surfaces and other machine finished surfaces shall be protected against corrossions by using lacquer, unless otherwise indicated.

5.2 FIELD PRIME COAT PAINTING

(including field prime, intermediate and a third coat painting for inaccessible surfaces):

5.2.1 Field prime coat painting shall consist of one complete coat of paint applied in the field to all bare structural steel or other ferrous metal surfaces after specified surface preparation has been completed.

5.2.2 For inaccessible surfaces after field erection, a third coat of paint shall be provided conforming to Table S-420-1

5.3 FIELD TOUCH-UP PAINTING

5.3.1 Field touch-up painting shall consist of one prime coat and one intermediate coat of paint and shall be applied to the following surfaces after completion of specified surface preparation:

- Surfaces where the shop coat of paint has been marred, scratched or otherwise damaged, due to shipping, handling, erection, installation, weathering etc.
- Bolt heads, nuts, washer, and adjacent surfaces left unpainted in the shop.
- Surfaces of field welds, and adjacent surfaces left unpainted in the shop.
- Surfaces of any ferrous fasteners not otherwise protected.
- Exposed fabrication, erection of shipping marks shall be cleaned off and the areas touch-up painted to match the adjacent surfaces.
- For any surfaces which have receive two coats, field touch-up painting shall consist of two coats also as indicated in Table S-420-1.

5.4 FIELD TOUCH-UP FOR GALVANIZING

- 5.4.1 The following area shall be touched-up with one coat of zinc-rich paint:
Galvanized surfaces (furnishing and/or installed by the Bidder) which have been marred due to handling, shipping, erection, weathering, etc. and field welds made on hot-dipped galvanized surfaces:
Paint Systems 420-E indicated in TableS-420-2 shall be used.

5.5 PAINTING OF ALUMINUM CONTACT SURFACES

The intent of this painting requirements is that aluminum surfaces to be in contact with other surfaces shall have two acceptable complete coats of paints at the time the aluminum is installed. This painting shall be provided as follows:

5.5.1 Aluminum to be in Contact with Ferrous Metals

To prevent galvanic action where aluminium surfaces shall be in contact with ferrous metals (other than galvanized steel), those ferrous metal surfaces shall receive one field coat of paint in additional to the shop or field prime coat. Paint Systems 420-C for prime coat, and 420-D for second coat as indicated in Table S-420-2 shall be applied.

5.5.2 Aluminum to be in Contact with Nonferrous Metals

Where aluminum surfaces will be in contact with copper, lead or other non-ferrous metals not compatible with aluminum, the contact surfaces of these

metals shall receive two coats of paint. Paint System 420-C for prime coat, and 420-D for second coat as indicated in Table S-420-2, shall be used.

Nonferrous metals compatible with aluminium, such as stainless steel, zinc, white bronze, etc., to be contact with aluminum, will not require painting.

5.5.3 Aluminum to be Contact with Concrete and Masonry

Where aluminium surfaces shall receive two field coats of paint. Where aluminum surfaces will be in contact with concrete or masonry the aluminum surfaces or the surfaces of the concrete or masonry to be in contact, shall receive two field coats of paint. Paint System 420-F as indicated in Table S-420-2, shall be applied.

5.5.4 Aluminum to be Contact with Foregoing Materials

Aluminum surfaces may be painted with two coats of specified paints, instead of painting the surfaces of the other materials to be in contact, where desirable, where required, or where requested. Paint system 420-C for prime coat and 420-D for second coat, or 420-F both coats, as indicated in Table S-420-2, shall be applied.

6. CLEANING AND PAINTING OF EQUIPMENT AND PIPING

6.1 GENERAL

Equipment shall be divided into there categories:

6.1.1 Equipment except the electrical equipment in Clause 6.1.3 which will be installed indoors and therefore not exposed to the weather.

6.1.2 Equipment, including outdoor transformers and switchgear enclosures except the electrical equipment in Clause 6.1.3 which will be installed outdoor and therefore exposed to the weather.

6.1.3 All electrical cubicles, panels and indoor enclosures.

6.2 CLEANING AND PAINTING OF INDOOR EQUIPMENT
(SEE CALUSE 6.1.1)

6.2.1 All ferrous equipment surfaces shall be cleaned and painted as suggested below. The Bidder shall design the paint system to be compatible with the ma-

terials to be coated, the temperature of the surfaces, service conditions and which can resist the tropical conditions and salty air environment.

- 6.2.1.1 Surface preparation: SSPC-SP10, Near-White Metal Blast Cleaning.
- 6.2.1.2 Shop coat:
Prime coat : 420-A (Inorganic zinc), 50 to 75 microns DFT
Second coat: 420-B (Two component polyamide epoxy carboline), 125 to 175 microns DFT
- 6.2.1.3 Finish: field or shop applied polyurethane at 50 to 75 microns.
- 6.2.2 The paint system applied shall be as per manufacturer's standard.
- 6.2.3 Equipment which is fully fabricated and assembled prior to shipment to the construction site, can be completely painted in the shop. However, if the equipment has to be assembled in the field and will require major touch-up, then this equipment shall be only prime and intermediate coat applied in the shop and finish paint applied at the field.

6.3 CLEANING AND PAINTING OF OUTDOOR EQUIPMENT (SEE CLAUSE 6.1.2)

All ferrous equipment surfaces for equipment installed outdoors, use the same painting systems as outlined for structural steel in Table S-420-1 and finish paint applied as per Technical Specification S-420. The complete painting system on equipment fully fabricated and assembled prior to shipment to the construction site shall be applied. However, if the equipment has to be assembled in the field and will require major touch-up, then this equipment shall receive only primer paint and intermediate coats in the shop.

6.4 CLEANING AND PAINTING OF ALL ELECTRICAL EQUIPMENT CUBICLES, PANELS & INDOOR ENCLOSURES (SEE CLAUSE 6.1.3)

- 6.4.1 All ferrous equipment surfaces of the above electrical equipment unless noted otherwise shall be cleaned and painted (prime & finish) at the manufacturing plant per their standards. However the paint shall be suitable for the specified environmental conditions.

- 6.4.2 The Bidder shall be required to submit a detailed painting procedure for this equipment for the approval of the Owner.
- 6.4.3 The procedure must include surface preparation, paint process and physical characteristics, application method and type of paint to be used.
- 6.4.4 Type of paint selected must comply with a recognized international standard.
- 6.4.5 The interior all cubicles, panels and enclosures shall be painted with white anti-condensation paint.
- 6.4.6 The Owner will select the color of the finish paint.

6.5 PIPING SURFACES

- 6.5.1 Insulated pipe surfaces: These surfaces shall only receive manufacturer's suggested painting for temporary protection prior to insulation.
- 6.5.2 Un insulated pipe surfaces and instrumentation: These surfaces where applicable, shall be painted in the same way as the equipment for indoor and outdoor exposure.

7. PERFORMANCE

7.1 SURFACE PREPARATION

- 7.1.1 Surface preparations for painting concrete, masonry or wood to be in contact with aluminum shall be as specified in the manufacturer's standard.
- 7.1.2 Surface preparation of painting all structural steel surfaces as indicated in Table S-420-1 and other metals, including galvanizing, aluminum etc. shall be as follows, unless otherwise indicated:

7.1.2.1 For Prime Coat:

- a. Surface shall first be cleaned according to SSPC-SPI Solvent Cleaning and if required, SSPC-SP2 Hand Tool Cleaning and SSPC-SP3 Power Tool Cleaning shall be applied prior to blast cleaning.
- b. Unless otherwise indicated, surfaces shall then be commercial blast cleaned, according to requirements of Table S-420-1, to produce a

general surface appearance corresponding to SSPC Standard Vis 1, pictorial surface preparation standards.

- c. Where specifically indicated, steel surfaces shall be Near-White Blast Cleaned, according to SSPC-SP10 to 62.50 microns profile.
- d. The blast cleaning equipment shall slightly roughen the surface to provide an anchor pattern as recommended by the paint/coating manufacturer. The anchor pattern shall be sharp and a polished surface will not be permitted.
- e. Blast cleaning equipment shall be suitable for the use, and shall be as recommended by the paint/coating manufacturer.
- f. Only the best quality, dry, uncontaminated sand, grit, or shot shall be used in blast cleaning. Blasting sand shall be dry and of a size recommended by the paint/coating manufacturer.
Blasting grit shall be crushed and made of cast iron, malleable iron or synthetic grits other than sand, of a size recommended by the paint/coating manufacturer.
- g. After completion of blast cleaning in any area, all traces of sand, grit or shot, and dust shall be removed from the surfaces by using moisture free and oil free compressed air or by vacuum cleaning. Brushing shall not be used.
- h. Extreme care shall be taken to avoid contaminating the blast cleaned surfaces with fingerprints or with detrimental material from workers, clothes or from any other sources.

7.1.2.2 **For Second Coat or Touch-Up Paint**

- a. Before applying second coat, all surfaces shall be cleaned to remove oil, grease, soil and other contaminants by SSPC-SP1 solvent Cleaning.
- b. Before applying touch-up paint, loose mill scale, loose rust and loose paint shall be removed by SSPC-SP2 Hand Tool Cleaning. If required, SSPC-SP3 Power Tool Cleaning shall be applied.

7.1.2.3 Metal Patching

If it is necessary to patch or fill scratches or gauges in equipment base plates, metal housing, etc., a metal putty shall be used. Metal putty shall be applied in strict accordance with manufacturer's directions, and shall be leveled and smoothed after application.

7.2 PAINT APPLICATION

7.2.1 Conformance

Application of paints shall conform to the applicable requirements of SSPC Paint Application Specification No.1 "Shop, field and Maintenance Painting", to manufacturer's instructions and to the requirements of this Clause 7.2.

7.2.2 Time Restrictions

Application of the prime coat shall normally be made over a blast cleaned area within 8 hours after completion of blast cleaning. This time restriction may be modified to more or less than 8 hours, depending on the temperature and humidity control exercised. The main criterion shall be that no rust bloom forms on the surface prior to application of the prime coat. If any rust bloom does form, the surface shall be blast cleaned again before application of the prime coat.

7.2.3 Temperature Restrictions

7.2.3.1 Paint shall not be applied to steel which is at a temperature of over 50⁰C unless the paint is specifically formulated for application at that temperature. When steel is painted in hot weather, precautions shall be taken to ensure that the specified dry film thickness of paint is achieved.

7.2.4 Moisture and Humidity Restrictions

7.2.4.1 Paint shall not be applied where exposed to rain, fog, or mist, or when the relative humidity is such as to cause condensation of paint on metal surface due to variation in metal temperatures and surrounding air temperatures.

7.2.4.2 All surfaces shall be perfectly dry before and while being painted and for 24 hours after painting.

7.2.5 Method of Application

7.2.5.1 Application of paint shall primarily be made by using proper size grade of brushes, except where spray equipment or rollers can be used to advantage. Spray equipment, if used, shall be accurately and fully controlled at all times so as to prevent damage to adjacent surfaces

7.2.5.2 Where two or more coat of paint is specified, the following shall be applied:

- a. The second coat of paint shall not be applied until the prime coat has been completed and checked. If the second coat is applied before the check of the prime coat, it will be assumed that the prime coat has not been applied, and by the direction of the Owner, the applied prime coat shall be entirely removed and the painted area shall be repaired from the beginning.
- b. Sufficient time for drying shall be allowed between coats.

7.2.6 Minimum Thickness of paint

7.2.6.1 The prime coat and second coat of paint shall be applied so as to result in a minimum dry film thickness as specified in Table S-420-2.

7.2.6.2 Verification of coat thickness may be made by the Owner at his option, based on measuring average wet film thickness, using a wet film gauge. The gauges shall be furnished by the Bidder.

7.2.6.3 The paint manufacturers shall accordingly be required by the Bidder to furnish the Bidder with the wet film thickness required, for each type of paint and method of application, to obtain the specified dry film thickness. These wet film thicknesses shall be based on applying the paint directly from the original containers with no thinners added.

7.2.6.4 If the Bidder intends to use thinners, he shall inform the Owner and the paint manufacturer of his intended methods of application. The paint manufacturer shall then reevaluate the paint and furnish the Owner and the Bidder with the new film thickness required.

7.2.6.5 Dry film thickness (DFT) may also be verified by the Owner for verification of paint thickness, and the dry thickness will be tested using an electrometer gauge or a Nordson Micro gauge. SSPC Method PA 2 will be adopted to determine the DFT by using these gauges.

- a. If the required minimum dry film thickness is not attained, additional coats of paint shall be applied to obtain the specified thickness, under direction of the Owner.

8. INSPECTION

- 8.1 All works covered by this specification will be subject to inspection by the Owner, and any work not conformed to this specification shall be satisfactorily redone by the Bidder without any additional cost to the Owner.
- 8.2 The Owner may make random spot checks of materials, equipment etc. which have been painted, by removing painted film to bare metal with acetone and examining the painted surface with a 5 power magnifying glass observe the absence or presence of rust under the prime coat. The presence of rust or rust stains under such swatches shall be sufficient cause for rejecting the work, and the Bidder shall repair and repaint the work in the field at his own expense.
- 8.3 Each paint application such as primer coat and intermediate coat shall be free from dry spray, overspray, pinholes, and discontinuities. Areas where these detrimental conditions occur shall be redone by the Bidder at no additional cost to the Owner before applying the next coat.

9. QUALITY ASSURANCE/QUALITY CONTROL (QA/QC)

- 9.1 Quality assurance/quality control shall conform to the requirements of Part 4, Subsection “quality Assurance/Quality Control”.
- 9.2 The quality control procedures and documentation include but not be limited to the following:
 - 9.2.1 Packaging and shipping
 - 9.2.2 Shop cleaning and painting procedures
 - 9.2.3 Field cleaning and painting procedures
 - 9.2.4 Thickness of painting

(Last page of S-420)