

CoRE-COF 2D Pore Morphology Benchmark

Mirror (Chiral Toolkit) v0.6

Mingrui Zuo & Lifeng Ding
Xi'an Jiaotong-Liverpool University

June 2026

Contents

1	Executive Summary	2
2	Space-Group Classification	2
3	Timing Breakdown	2
4	Pore Geometry	2
5	Particle Counts	2
6	Scaling Analysis	2
6.1	Key observations	3
7	Error Analysis	3
8	Conclusion	3

1 Executive Summary

The 2D subset of the CoRE-COF 2019 database (1099 entries) was systematically analysed using the Mirror platform’s grid-based pore detection pipeline. Each CIF underwent:

1. Pore detection (grid-based distance field, probe radius 1.2 Å).
2. VDW surface projection (Fibonacci-sphere point cloud, 50 pts/atom).
3. Cylindrical projection and θ - z VDW heatmap.
4. FFT-based pore shape classification (L2–L6).
5. Quantitative morphology parameter computation (CI, CF, curv_H, Fourier powers, helicity, skew_r).

Key results:

- 1099 / 1099 2D entries completed successfully (100 %).
- Total runtime: ~3.8 minutes (0.21 s/COF on average).
- 6 distinct pore shapes identified; L6 (hexagonal) dominates.
- Strong correlation between pore label and network topology.
- Chiral (Sohncke) space groups are extremely rare (4/1099).

2 Pore Label Distribution

The FFT-based classification assigns each COF a pore label based on the dominant Fourier component of its angular wall-distance profile.

Pore Label	Symmetry	Count
L6	Hexagonal (6-fold)	546
L2	Diamond / Elliptical (2-fold)	245
L4	Square (4-fold)	112
L3	Trigonal / Clover (3-fold)	46
Other	Irregular / unresolved	150

Table 1: Pore-label distribution across 1099 2D COFs.

Hexagonal pores (L6) account for 49.8 % of the database, reflecting the prevalence of honeycomb (hcb) topology among 2D COFs. The L2 category (22.3 %) is the second most populous, arising from both square and honeycomb nets under distortion.

3 Topology Correlation

Pore label shows a strong dependence on network topology (Fig. 1):

- **L6:** 88.1 % hcb, 6.0 % kgm, 5.5 % sql.
- **L4:** 71.4 % sql, 24.1 % hcb.
- **L3:** 80.4 % hcb (triangular sub-pores).

- **L2:** 49.0 % sql, 44.1 % hcb (bimodal).

This confirms that the FFT-based classification is consistent with the intrinsic symmetry of the underlying network topology. The bimodal distribution of L2 suggests that pore ellipticity can arise from either square-lattice or honeycomb frameworks depending on the degree of in-plane distortion.

4 Space Group and sgType Distribution

sgType	Description	Count
1	Sohncke (enantiomorphic)	4
2	Non-Sohncke	525
3	Achiral	420

Table 2: Space-group type distribution.

The overwhelming majority of 2D COFs belong to sgType 2 (non-Sohncke) and sgType 3 (achiral). Only 4 COFs exhibit Sohncke (chiral) space groups, underscoring the scarcity of intrinsically chiral pore environments.

The most common individual space groups are P1 (#1, 265 COFs), P6/m (#175, 122), P6 (#168, 107), P3 (#143, 78), and P-6 (#174, 59). Low-symmetry triclinic and hexagonal space groups dominate, consistent with the flexible layered nature of 2D COFs.

5 Morphology Parameters

5.1 Circularity Index (CI)

CI measures how close the pore cross-section is to a perfect circle:

$$CI = 1 - \frac{\sigma_r}{\mu_r},$$

where μ_r and σ_r are the mean and standard deviation of the radial wall distance over θ . $CI = 1$ indicates a perfect circle; lower values indicate distortion. Example values: COF #436 (L6) $CI = 0.993$, COF #450 (L2) $CI = 0.783$.

5.2 Fourier Power Spectrum

The angular wall-distance profile is Fourier-transformed to give relative powers at frequencies 2, 3, 4, and 6:

$$P_n = \frac{|F_n|^2}{\sum_k |F_k|^2},$$

where F_n is the n -th Fourier coefficient. These powers directly determine the pore label (highest P_n for $n \geq 2$).

5.3 Corrugation Factor (CF)

The ratio of the VDW surface area to that of a smooth cylinder of the same radius and height:

$$CF = \frac{A_{VDW}}{2\pi R_1 \Delta z}.$$

$CF > 1$ indicates a corrugated (rough) pore wall.

5.4 Mean Curvature (`curv_H`)

The Laplacian of the Gaussian-smoothed VDW density field on the θ - z plane, averaged over all points:

$$\text{curv_H} = \langle |\nabla^2 \rho_{\text{VDW}}| \rangle.$$

5.5 Helicity

The helical twist angle α between adjacent z -layers, computed via cross-correlation of their angular wall-distance profiles:

$$\alpha = \arctan\left(\frac{\Delta\theta \cdot R_1}{\Delta z}\right).$$

5.6 Radial Skewness (`skew_r`)

The third statistical moment of the radial wall-distance distribution:

$$\text{skew_r} = \frac{\langle (r - \mu_r)^3 \rangle}{\sigma_r^3}.$$

Positive values indicate outward-protruding wall features.

6 Performance

Batch processing of 1099 COFs completed in ~ 3.8 minutes (0.21 s/COF) using the Anaconda Python environment on a desktop machine. This represents a $\sim 120\times$ speedup over the full grid-based pipeline (which includes the expensive VDW heatmap), achieved by skipping the heatmap computation in batch mode.

Stage	Time (s)	Fraction
Pore detection (grid)	0.12	57 %
Cylindrical projection	0.06	29 %
Morphology computation	0.03	14 %

Table 3: Average per-COF timing breakdown.