



Av. del Aluminio, 23 nido C - 3
33490 AVILES (ASTURIAS) SPAIN.
Teléfono: 985.514.745
E-mail: carigue@carigue.es

KAPTON/GLASS (GK) is a flexible laminate made from Kapton® HN quality polyimide film and a glass cloth. Is manufactured in different Kapton® HN polyimide film and glass cloth combinations. Is a thermal class 200 (200°C) generally used in the following applications: Bottom and slot lining insulation in low voltage motors, and especially in traction motors, phase and coil head insulation in electric motors subjected to constant changes in temperature, railway and metro traction motors, etc.

We want it in rolls of 50m² x 914mm with the following characteristics:

KAPTON+GLASS (GK)		
Type		GK 2228
Nominal thickness	mm	0.120
Tolerance	mm	±0.02
KAPTON HN thickness	µm	75
Weight/m ² glasscloth	g/m ²	24
Glasscloth thickness	µm	30
Total weight/m ²	g/m ²	146
Voltage breakdown	KV	13