



Product Data Sheet

OILKEY JET-GREASE GS-400LCG

EP2 lithium complex grease

Features**1. Excellent high-temperature oxidation stability**

A highly refined base oil and carefully selected additives give a grease that withstands long-term use with little oxidative degradation even at high temperatures.

2. Excellent load-carrying capacity and wear resistance

Special additives provide excellent load-carrying capacity and wear resistance.

3. Excellent water resistance

A base oil with excellent demulsibility gives the grease outstanding water resistance.

4. Excellent rust prevention

Strong adhesion and the grease film protect machinery from metal corrosion.

Applications

Construction machinery, agricultural machinery, industrial machinery in general, and heavy vehicles of all kinds.

Operating temperature range

−30 °C to +150 °C

Typical properties

Test method	Property	Typical value
—	NLGI grade	2
—	Appearance	Tacky grease
—	Colour	Red
—	Thickener type	Lithium complex
—	Base oil	Mineral
ASTM D445	Base-oil viscosity @ 40 °C, cSt	150
ASTM D445	Base-oil viscosity @ 100 °C, cSt	10.7
ASTM D217	Worked penetration, dmm	265–295
ASTM D2265	Dropping point, °C	260 min.
ASTM D2270	Viscosity index	21
IP 239	Four-ball weld load, 10 s, kgf	560
IP 239	Four-ball wear scar, 40 kg / 1 h, mm	0.55
ASTM D217	Extended worked penetration, 10,000 strokes, dmm	298 (+18)
ASTM D217	Extended worked penetration, 100,000 strokes, dmm	313 (+34)
ASTM D1831	Roll stability, 2 h @ 35 °C	303 (+24)
IP 121	Oil separation, 42 h @ 40 °C, % (5 max.)	1.0
IP 121	Oil separation, 168 h @ 40 °C, % (5 max.)	2.3
ASTM D4048	Copper corrosion, 24 h @ 100 °C	Pass
ASTM D6138	EMCOR corrosion, distilled water	0, 0
ASTM D1743	Corrosion	Pass
ASTM D1264	Water washout, 1 h @ 38 °C, %	2.3

OILKEY CORPORATION

Head Office: 4-4-18 Makitsukadai, Minami-ku, Sakai, Osaka 590-0114, Japan Sakai Sales Office: 617 Taiheiji (2F), Nishi-ku, Sakai, Osaka 593-8314, Japan
 TEL +81-72-284-1711 FAX +81-72-298-7790 <http://www.oilkey.co.jp> English edition, translated from the original Japanese document.



Test method	Property	Typical value
ASTM D1264	Water washout, 1 h @ 79 °C, %	5.0
ASTM D8206	Oxidation stability, time to 10% loss @ 150 °C, min	236
DIN 51805-2	FFK flow pressure, -30 °C, hPa	800
—	Operating temperature, °C	-30 to +150

OILKEY CORPORATION

Head Office: 4-4-18 Makitsukadai, Minami-ku, Sakai, Osaka 590-0114, Japan Sakai Sales Office: 617 Taiheiji (2F), Nishi-ku, Sakai, Osaka 593-8314, Japan
TEL +81-72-284-1711 FAX +81-72-298-7790 <http://www.oilkey.co.jp> *English edition, translated from the original Japanese document.*