



オイルキー株式会社 ☐ 本社 〒590-0114 大阪府堺市南区槇塚台 4-4-18 [URL://www.oilkey.co.jp](http://www.oilkey.co.jp) メール:oilkey@oilkey.co.jp
☒ 堺営業所 〒593-8314 堺市西区太平寺 617 (2F) Tel 072-284-1711 Fax 072-298-7790

Product Data Sheet (代表性状)

OILKEY JET-GREASE GS-400LCG EP2 LITHIUM COMPLEX GREASE

オイルキー ジェットグリース GS-400LCG 複合リチウムグリース

<特長>

1. 優れた高温酸化安定性

高度に精製されたベースオイルと厳選された添加剤により高温時でも酸化劣化の少ない長期使用に耐え得るグリースです。

2. 優れた耐荷重性、耐摩耗性

特殊添加剤により、耐荷重性、耐摩耗性に優れています。

3. 優れた耐水性

抗乳化性に優れたベースオイルを使用しているため、耐水性に優れています。

4. 優れた防錆性

強固な付着性とグリース膜で金属腐食から機械を保護。

<用途>

建設機械、農業機械、産業機械全般及び各種重車両。

<使用温度範囲>

-30℃～150℃

Product Data Sheet (代表性状)

OILKEY JET-GREASE GS-400LCG EP2 LITHIUM COMPLEX GREASE

オイルキー ジェットグリース GS-400LCG 複合リチウムグリース

Product Data Sheet 代表性状		
TEST METHOD 試験方法	DESCRIPTION 試験項目	SPECIFICATIONS 代表値
	NLGI Grade (番手)	2
	APPEARANCE (外観)	TACKY GREASE (粘着性)
	COLOR (色)	RED (赤色)
	THICKENER TYPE (増ちょう剤)	LITHIUM COMPLEX (複合リチウム)
	BASE OIL (基油)	MINERAL (鉱油)
ASTM D445	BASE OIL VISCOSITY @40°C cSt (基油粘度)	150
ASTM D445	BASE OIL VISCOSITY (基油粘度) cSt @ 100°C	10.7
ASTM D217	WORKED PENETRATION dmm (混和ちょう度)	265-295
ASTM 2265	DROPPING POINT °C (滴点)	260以上
ASTM 2270	VISCOSITY INDEX (基油指数)	21
IP 239	FOUR BALL WELD LOAD, 10s kgf (四球式耐荷重能)	560
IP 239	FOUR BALL WEAR SCAR, 40KG 1 HOUR (四球式耐摩耗)	0.55
ASTM D217	EXTENDED WORKED PENETRATION dmm (長時間作業浸透)	
	10,000 STROKES (ストローク)	298 (+18)
	100,000 STROKES	313 (+34)
ASTM D1831	ROLL STABILITY - 2 HOURS@35°C ロール安定性	303 (+24)
IP 121	OIL SEPARATION (%) (離油度)	5 MAX (上限)
	42 HOURS@40°C	1.0
	168 HOURS @ 40°C	2.3
ASTM D4048	COPPER CORROSION 24 HOURS @ 100°C (銅板腐蝕)	合格
ASTM D6138	CORROSION EMCOR DISTILLED WATER (腐食試験)	0,0
ASTM D1743	CORROSION (腐食試験)	合格
ASTM D1264	WATER WASHOUT % (水洗耐水度)	
	1 HOUR @38°C	2.3
	1 HOUR @79°C	5.0
ASTM D8206	OXIDATION STABILITY min (酸化安定度)	
	TIME TO 10% LOSS @ 150°C (10%の損失の時間@150°C)	236
DIN 51805-2	FFK FLOW PRESSURE -30°C hPa (FFK流圧)	800
	OPERATING TEMPERATURE (動作温度)	-30°C~150°C