

Product Data Sheet

OILKEY JET-GREASE LG

Lithium grease

Features**1. Excellent high-temperature oxidation stability**

A highly refined base oil and carefully selected additives give a grease that withstands long-term use with little oxidative degradation even at high temperatures.

2. Excellent load-carrying capacity and wear resistance

Special additives provide excellent load-carrying capacity and wear resistance.

3. Excellent water resistance

A base oil with excellent demulsibility gives the grease outstanding water resistance.

Applications

Construction machinery, agricultural machinery, industrial machinery in general, and heavy vehicles of all kinds.

Operating temperature range

−20 °C to +130 °C

Typical properties

Test method	Property	Typical value
—	NLGI grade	2
JIS K 2220	Thickener	Lithium soap
JIS K 2220 7	Worked penetration, 25 °C	272
JIS K 2220 8	Dropping point, °C	190
JIS K 2220 9	Copper corrosion (100 °C, 24 h)	Pass
JIS K 2220 10	Evaporation loss (99 °C, 22 h), mass %	0.5
JIS K 2220 11	Oil separation (100 °C, 24 h), mass %	2.3
JIS K 2220 12	Oxidation stability (99 °C, 100 h), kPa	20
JIS K 2220 15	Worked stability	319
JIS K 2220 16	Water washout (38 °C, 1 h), mass %	2.7
JIS K 2220 20	Timken load capacity, kg	18.1
JIS K 2283	Base-oil kinematic viscosity (40 °C), mm ² /s	125
ASTM D2596	Four-ball weld load, N	1,961
ASTM D2266	Four-ball wear scar, mm	0.46
Visual	Appearance	Pale yellow, buttery

OILKEY CORPORATION

Head Office: 4-4-18 Makitsukadai, Minami-ku, Sakai, Osaka 590-0114, Japan Sakai Sales Office: 617 Taiheiji (2F), Nishi-ku, Sakai, Osaka 593-8314, Japan
 TEL +81-72-284-1711 FAX +81-72-298-7790 <http://www.oilkey.co.jp> English edition, translated from the original Japanese document.