Prediction of Concrete Compressive Strength Using Concrete Mixture Characteristics

Mohamed Alsaleh
Department of Civil and Environmental Engineering
University of Illinois Urbana-Champaign
Urbana, IL, USA
alsaleh4@illinois.edu

Jingchun Wang
Department of Civil and Environmental Engineering
University of Illinois Urbana-Champaign
Urbana, IL, USA
jw198@illinois.edu

Khwanjira Phumphid
Department of Civil and Environmental Engineering
University of Illinois Urbana-Champaign
Urbana, IL, USA
kp70@illinois.edu

Rae Zhu
Department of Civil and Environmental Engineering
University of Illinois Urbana-Champaign
Urbana, IL, USA
rzhu15@illinois.edu

***Abstract*—This project aims to investigate the relationships between concrete mixture characteristics, age, and compressive strength using exploratory data analysis and predictive modeling. Multiple statistical and machine-learning approaches will be evaluated to estimate concrete compressive strength and identify influential mixture characteristics. The findings are expected to provide insights into concrete strength development and inform future mixture design adjustments.**

***Index Terms*—Concrete Compressive Strength, Machine Learning, Regression, Feature Importance**

I. Dataset Description

A. Dataset Source and Overview

This project will use the Concrete Compressive Strength dataset available through the UCI Machine Learning Repository [1]. The dataset was originally provided by Prof. I-Cheng Yeh of Chung-Hua University. The data were developed from laboratory measurements of concrete mixtures, where the actual compressive strength of each mixture was determined at a specified age. The dataset is provided in raw, unscaled form and is available as an Excel file (Concrete_Data.xls), which can be downloaded from the UCI Machine Learning Repository website and is identified by the DOI 10.24432/C5PK67.

The dataset contains 1,030 observations and nine quantitative variables. Eight variables describe the concrete mixture composition and age and are used as input variables. The ninth variable, concrete compressive strength, is the output variable. The dataset contains no missing values.

B. Dataset Variables

Table I summarizes the nine variables included in the dataset. The amounts of the seven mixture components are given in kilograms per cubic meter of concrete, the specimen age is given in days, and the compressive strength is given in MPa. Because this project aims to predict compressive strength from the mixture composition and age, the primary response variable will be **concrete compressive strength in MPa**, while the remaining eight variables will be considered potential predictors.

TABLE I
Description of dataset variables.

Variable	Unit	Description	Role
Cement	kg/m^3	Amount of cement in the concrete mixture	Input
Blast Furnace Slag	kg/m^3	Amount of blast furnace slag in the mixture	Input
Fly Ash	kg/m^3	Amount of fly ash in the mixture	Input
Water	kg/m^3	Amount of water in the mixture	Input
Superplasticizer	kg/m^3	Amount of superplasticizer in the mixture	Input
Coarse Aggregate	kg/m^3	Amount of coarse aggregate in the mixture	Input
Fine Aggregate	kg/m^3	Amount of fine aggregate in the mixture	Input
Age	days	Age of the concrete specimen at testing	Input
Concrete Compressive Strength	MPa	Measured compressive strength of the concrete	Output

C. Exploratory Data Analysis

Fig. 1 shows the distribution of concrete compressive strength across different specimen ages. Overall, the median value of compressive strength increases with age, especially during the early stage. For example, the median compressive strength increases from approximately 16 MPa at 3 days to 34 MPa at 28 days, and continue to increase to 52 MPa at 56 days. However, the compressive strength varies within each age group. This variation existing within each age group suggests that curing age alone cannot fully explain the differences in compressive strength.




Fig. 1. Distribution of compressive strength by specimen age.

In addition, the strength distributions across the different age groups do not necessarily show a consistent upward trend. For example, the 91-day group has a much higher median strength than the 90-day group. This difference does not necessarily indicate a sudden rise in strength, because the specimens tested at these ages may have different mixture compositions. The sample sizes are not consistent either: 425 specimens were tested at 28 days, while only 22 were tested at 91 days. Therefore, comparisons across age groups may not be entirely valid, and the effects of mixture composition should also be considered.

Fig. 2 presents the pairwise relationships and Spearman's rank correlation coefficients among the selected variables. Specimen age has the strongest positive correlation with compressive strength (ρ=0.60), followed by cement content (ρ=0.48) and high-performance water-reducing agent(superplasticizer) content (ρ=0.35). In contrast, water content showed a negative correlation with compressive strength (ρ=-0.31), suggesting that mixtures with higher water content tend to have lower strength.

The relationships among the mixture components are also important. For example, fly ash and superplasticizer show a positive correlation (ρ = 0.45), while water and superplasticizer show a negative correlation (ρ = −0.69). These relationships indicate that some predictors are associated with each other, which should be considered when developing predictive models. Furthermore, the relationship between age and strength is described more accurately by the Spearman correlation coefficient (ρ = 0.60) than by the Pearson correlation coefficient (r = 0.33), indicating that this relationship may be monotonic but nonlinear.

Fig. 3 illustrates the relationship between binder composition and 28-day concrete compressive strength using a ternary diagram of cement, blast furnace slag, and fly ash proportions. Comparing specimens at the same testing age allows the relationship between binder composition and compressive strength to be examined without differences in specimen age affecting the comparison.

The figure shows that some mixtures with higher cement proportions achieve relatively high compressive strength. However, high strength is also observed in mixtures containing slag or fly ash, suggesting that partially replacing cement with these materials does not necessarily result in lower strength. Considerable variation in compressive strength is observed even among mixtures with similar binder proportions. This indicates that binder composition alone cannot fully explain the differences in strength. Other factors, such as water content, total binder content, and chemical admixtures, may also contribute to the observed variation. Therefore, multiple mixture characteristics should be considered when developing predictive models for concrete compressive strength.




Fig. 2. Pairwise relationships and Spearman rank correlations among mixture variables, age, and compressive strength.




Fig. 3. Binder composition and 28-day compressive strength.

Fig. 4 shows the relationship between the water-to-binder ratio and the concrete compressive strength, with specimen age represented by color. A clear decreasing trend can be observed, as mixtures with lower water-to-binder ratios typically achieve higher compressive strengths. For example, specimens with water-to-binder ratios below approximately 0.35 exhibit strengths ranging from about 20 to over 80 MPa, while most specimens with ratios above 0.70 have strengths below 30 MPa. This relationship is consistent with the role of water in cement-based materials. This pattern is consistent with the understanding that excessive water relative to binder content can increase porosity and reduce concrete strength.

However, differences still exist among specimens with similar water-to-binder ratios. The color distribution indicates that specimens tested at later ages generally show achieve strength than those tested at earlier ages with comparable water-to-binder ratios. This indicates that both specimen age and water-to-binder ratio are associated with compressive strength. Other mixture characteristics may also explain some of the remaining variation. Therefore, the relationship should be interpreted as an association rather than evidence of a causal effect from this dataset alone.




Fig. 4. Compressive strength versus water-to-binder ratio by specimen age.

Fig. 5 provides a more detailed analysis of strength development by tracking the change in strength over time for different concrete mixtures. Unlike Fig. 1, Fig. 5 (a) examines measurement data for the same mix design at multiple ages. The strength of most mixtures increases rapidly during the early curing period, and the rate slows down later. Mixtures with lower water-to-binder ratios usually can achieve higher compressive strengths.

Fig. 5 (b) provides a more detailed comparison by normalizing the compressive strength of each mixture relative to 28-day strength. The normalized strength increases from approximately 0.46 at day 3 to 0.63 at day 7, and further to 0.82 at day 14. By approximately 90 days, the median reaches 1.25 indicating that the typical strength is about 25% higher than the corresponding 28-day value among the mixtures represented at that age. However, the shaded percentile ranges show variation in strength development across different mixtures. Therefore, while the general trend suggests increasing strength with age, the rate of development varies among mixture designs.

Based on exploratory data analysis, the compressive strength of concrete depends on multiple factors rather than any single mix design characteristic. The age of the test specimens and the cement content are positively correlated with strength, while the water content and the water-to-binder ratio are negatively correlated.

II. Proposed Analysis

The objective of this project is to investigate the relationships among concrete mixture characteristics, age, and compressive strength and to develop predictive models for concrete compressive strength. The first stage of the analysis will use exploratory data analysis to examine the variable distributions and relationships among the mixture components, age, and compressive strength. Appropriate graphical and statistical methods will be used to explore these relationships, while feature importance analysis will help identify which mixture characteristics are most strongly associated with compressive strength.

The second stage of the project will apply multiple predictive modeling approaches introduced in the course. These may include statistical regression methods and machine-learning models, as appropriate based on the methods covered during the semester. The models will be developed using the eight input variables and evaluated using appropriate prediction-performance measures. Their predictive capabilities will then be compared to determine how different statistical and machine-learning approaches perform in estimating con-




Fig. 5. Strength development of individual concrete mixtures.

crete compressive strength. This analysis is useful because compressive strength is an important indicator of concrete performance, while strength development depends on several interacting mixture characteristics and the age of the concrete. Comparing multiple predictive approaches can also provide insight into whether more flexible machine-learning methods offer improved predictive performance compared with conventional statistical regression models. Furthermore, identifying the most influential mixture characteristics can provide insights into the factors associated with concrete strength and help guide future mixture design adjustments to improve concrete performance.

III. Predictive Modeling

We will compare four models for concrete compressive strength: multiple linear regression, polynomial regression with ridge regularization, a regression tree, and random forest (RF). All models will use the seven mixture ingredients and age to predict strength in MPa. The aim is to assess whether more flexible models improve predictions for mixtures absent from the training data. The resulting models could support preliminary mixture assessment within the conditions represented by the dataset.

Multiple linear regression will provide the baseline. The polynomial model will include the eight original predictors, their squared terms, and pairwise interactions. A ridge penalty will limit coefficient size to reduce overfitting. The regression tree will divide observations through successive rules, while RF will average predictions from 500 trees built with random variation in observations and candidate predictors [2]. All models will be implemented in Julia.

The same data split will allocate approximately 80% of observations to training and 20% to testing. Records with identical quantities of the seven ingredients will stay together, including measurements at different ages. These mixture groups will be assigned intact, so the final percentages may differ slightly from 80/20. This approach will assess predictions for unseen recipes and prevent the same recipe from appearing in both sets. Repeated records will be reviewed before the split, and any corrections will apply to all models.

The three tunable models will use grid search with 20 predefined parameter configurations each. Every configuration will be assessed through the same five validation folds within the training set, with mixture groups kept intact. The proposed grids are:

- **Polynomial regression with ridge regularization:** 20 penalty values spaced evenly on a logarithmic scale from 0.0001 to 10,000.
- **Regression tree:** maximum depths of 3, 5, 8, 12, or no depth limit, combined with minimum leaf sizes of 2, 5, 10, or 20 observations.
- **RF:** maximum depths of 10 or no depth limit, minimum leaf sizes of 2 or 5 observations, and 2, 3, 4, 6, or 8 candidate predictors per split. The number of trees will remain fixed at 500.

These grids provide the same number of candidate evaluations for each tunable model, although the parameters and their ranges differ by model. Ordinary linear regression has no comparable tuning parameter and will be evaluated on the same validation folds. Data partitions and random seeds will be recorded and reused.

All models will use the same eight source predictors and untransformed strength values. Polynomial terms will be fixed before tuning. For the regression models, input columns will be standardized using means and standard deviations calculated from each training fold. The corresponding validation fold will receive the same transformation. Polynomial terms will be standardized after expansion. Trees will use unscaled inputs because their split rules do not require standardization. After tuning, scaling parameters will be recalculated from the full training set and applied unchanged to the test set.

Mean validation root mean squared error (RMSE) will determine the settings for each model and the preferred model. All four models will then be fitted to the full training set and evaluated once on the same test observations. Test RMSE, mean absolute error (MAE), and R^2 will be reported, with RMSE and MAE expressed in MPa. Predicted-versus-observed and residual plots will show where errors occur. Test results will not guide further tuning or changes to preprocessing.

SHapley Additive exPlanations (SHAP) will explain RF predictions [3], with approximate Shapley values calculated through ShapML.jl. Training observations will provide the reference data, and explanations will cover test observations after model settings are fixed. Mean absolute SHAP values will rank predictor contributions. A summary plot and dependence plots for the leading predictors will show contributions to higher or lower predicted strength relative to the reference prediction. These results explain model behavior and do not establish causal effects. Correlated ingredients may affect how contributions are shared.

The model's predictive ability will be limited by the range and distribution of the available data. Predictions for mix proportions or curing ages that are poorly represented in the dataset may be less reliable. The interpretation of the model's performance should be limited to dataset.

A. *Data Preparation and Partitioning*

Before modeling, the 1,030 records were checked for repeated entries. Twenty-five records were exact copies of another record in all nine variables and were removed, leaving 1,005 records from 428 unique mixtures. Nine combinations of mixture and age contain two records with different strength values. These records were kept because they represent separate test results rather than repeated entries.

The cleaned records were divided into training and test sets by mixture, as planned. Whole mixtures were assigned to the test set in random order until 20% of the records were reached (random seed 492). The training set contains 804 records from 341 mixtures, and the test set contains 201 records from 87 mixtures, with no mixture appearing in both sets. The training mixtures were then assigned to five validation folds of 160 or 161 records each. The strength distributions of the two sets are similar (mean of 35.4 MPa for training and 34.9 MPa for testing; two-sample Kolmogorov–Smirnov test, p =

0.94). The assignment of every record is stored in `data/concrete_split.csv`, and the same file is used for all four models.

B. Multiple Linear Regression

Multiple linear regression (MLR) was fitted by ordinary least squares in Python. Following the plan, the baseline model used the eight source predictors. The inputs were standardized with the means and standard deviations of each training fold, so each coefficient represents the change in predicted strength (MPa) for an increase of one standard deviation in that predictor.

The exploratory analysis suggested two relationships that a linear model cannot represent with the source predictors alone. First, strength increases with age in a monotonic but nonlinear way (Fig. 1, Fig. 5), so a straight-line age term is expected to fit poorly. Second, strength decreases with the water-to-binder ratio (Fig. 4), which is a ratio of four inputs rather than a linear combination of them. Therefore, four alternative feature sets were compared with the baseline: (1) age replaced by its natural logarithm, ln(age); (2) ln(age) together with the water-to-binder ratio, w/b = water/(cement + slag + fly ash); (3) the second set without the two aggregate variables, as a test of feature selection; and (4) the second set with ln(strength) as the response, with predictions transformed back to MPa. All feature sets were evaluated on the same five validation folds, and the set with the lowest mean validation RMSE was selected. The test set was used only once, after this selection.

Fig. 6 (a) and Table II summarize the comparison. The baseline model had a mean validation RMSE of 10.5 ± 0.7 MPa. Replacing age with ln(age) reduced this value to 7.4 ± 0.5 MPa, a reduction of 29%, and the improvement appeared in every validation fold. Adding w/b gave only a small further reduction (7.39 MPa), and this reduction was not consistent across folds. Removing the aggregates increased the error slightly (7.55 MPa), so the aggregate variables were kept. Transforming the response was not helpful: the ln(strength) model had a higher and less stable validation RMSE (9.4 ± 1.7 MPa). This is likely because fitting on the logarithmic scale gives less weight to errors at high strengths, which are the largest errors when measured in MPa. Based on the selection rule, the ln(age) + w/b feature set was chosen. On the test set, it achieved an RMSE of 6.8 MPa, an MAE of 5.2 MPa, and an R^2 of 0.81, compared with 10.4 MPa, 8.1 MPa, and 0.56 for the baseline. For reference, predicting the training mean for every specimen gives a test RMSE of 15.7 MPa.

TABLE II
PERFORMANCE OF MULTIPLE LINEAR REGRESSION FEATURE SETS (p: NUMBER OF PREDICTORS; RMSE AND MAE IN MPa; VALIDATION VALUES ARE MEAN ± SD OVER FIVE FOLDS).

Feature set	**p**	**Validation RMSE**	**Test RMSE**	**Test MAE**	**Test R^2**
Baseline	8	10.53 ± 0.72	10.39	8.10	0.56
ln(age) replaces age	8	7.43 ± 0.50	6.81	5.30	0.81
ln(age) + w/b (selected)	**9**	**7.39 ± 0.50**	**6.77**	**5.25**	**0.81**
ln(age) + w/b, no aggregates	7	7.55 ± 0.54	6.56	5.14	0.83
ln(strength) response	9	9.41 ± 1.70	8.92	6.19	0.68
Mean-only predictor	0	–	15.72	12.80	0.00

Fig. 6 (b) compares the standardized coefficients of the baseline and selected models. The 95% confidence intervals are based on heteroscedasticity-robust (HC3) standard errors, because the spread of the residuals increases with predicted strength (Breusch–Pagan test, $p < 0.001$). In both models, cement, slag, and fly ash have positive coefficients, and cement has the largest effect among the ingredients. In the baseline model, an additional 1 kg/m^3 of cement is associated with 0.12 MPa higher strength, while an additional 1 kg/m^3 of water is associated with 0.11 MPa lower strength. In the selected model, ln(age) has the second-largest coefficient after cement (10.2 and 11.2 MPa per standard deviation, respectively) and the narrowest confidence interval. However, when w/b is included, the water coefficient is no longer significantly different from zero, because the effect of water is now shared with w/b. The variance inflation factors (VIF) also increase from a maximum of 8.0 in the baseline model to 24.5 for cement and 19.0 for w/b in the selected model. Therefore, the coefficients of the selected model should not be interpreted one at a time. The positive coefficients of the aggregates should also be interpreted with caution. Because the ingredient amounts together make up one cubic meter of concrete, these coefficients may reflect differences in the overall mixture design rather than a direct strengthening effect of the aggregates. This collinearity is one reason for the ridge penalty used in the polynomial model.

Fig. 7 shows where the errors occur on the test set. The baseline model overpredicted the strength of young specimens (mean residual of −10.9 MPa at 3–7 days) and underpredicted specimens tested at 56–100 days (+8.2 MPa). This is the pattern expected when a curved strength-gain relationship is described by a straight line. The ln(age) term removed most of this pattern (−1.8 and +1.9 MPa for the same age groups). Two systematic errors remain. First, the 14 test specimens tested at 180–365 days were overpredicted by 6.4 MPa on average, because ln(age) keeps increasing while the measured strength levels off after about 90 days (Fig. 5). Second, specimens stronger than 60 MPa were underpredicted by 5.0 MPa on average, with an RMSE of 10.5 MPa. In addition, the residuals are not normally distributed (Shapiro–Wilk test, $p < 0.001$), and their spread increases with predicted strength (Fig. 7 (c)).

To check whether these results depend on the particular split, the baseline and selected models were refitted on 200 alternative mixture-grouped 80/20 splits. The selected model had a median test RMSE of 7.2 MPa (5th–95th percentile: 6.4–8.1 MPa), compared with 10.5 MPa (9.6–11.3 MPa) for the baseline, and it was more accurate in all 200 splits. The test RMSE of 6.8 MPa from the main split is therefore slightly better than typical. The baseline model was also evaluated with ordinary random five-fold cross-validation, which ignores the mixture groups. The result (10.46 MPa) was almost identical to the grouped result (10.53 MPa). This suggests that grouping has little effect for a linear model, which cannot memorize individual recipes. More flexible models may behave differently, which is why the grouped split is kept for all models.

The selected MLR model reduces the error of the mean-only predictor by 57%, and 59% and 83% of the test




Fig. 6. Feature-set comparison and standardized coefficients of multiple linear regression.




Fig. 7. Test-set diagnostics of the baseline and selected multiple linear regression models.

predictions fall within ±5 MPa and ±10 MPa of the measured strength, respectively. However, an RMSE of 6.8 MPa is about 20% of the median 28-day strength in the dataset (34 MPa, Fig. 1), and the largest errors occur for high-strength mixtures and long curing ages. Therefore, the MLR model is useful for describing general trends and as a baseline for the other models, but it is not accurate enough to select a mixture that must meet a specific target strength. The diagnostics suggest that accuracy could be improved by an age term that levels off at long ages, by interaction terms between age and mixture composition, and by models that can represent nonlinear effects, such as the polynomial and tree-based models. Reading guides for Fig. 6 and Fig. 7 are provided as text files with the same names in the `modeling/mlr/figures/` folder.

References

[1] I.-C. Yeh, "Concrete Compressive Strength." [Online]. Available: https://archive.ics.uci.edu/dataset/165/concrete+compressive+strength

[2] L. Breiman, "Random Forests," *Machine Learning*, vol. 45, pp. 5–32, 2001, doi: 10.1023/A:1010933404324.

[3] S. M. Lundberg and S.-I. Lee, "A Unified Approach to Interpreting Model Predictions," in *Advances in Neural Information Processing Systems*, 2017, pp. 4765–4774.