

Type

UL Listed Anti fungal Acrylic duct Sealant

Description

Premier 32-17 UL is fire resistive, aqua based, indoor /outdoor vapor barrier sealant for low, medium, and high pressure or high velocity-metal, fiber glass and flexible heating and air conditioning air ducts. It is highly elastic in nature. It has excellent adhesion to metal, aluminum, etc. It acts as tough and flexible adhesive and sealant, forming a durable seal against air leakage.

Premier 32-17 UL meets the requirements for LEED IEQ 4.2, Low Emitting Material, Paints and Coatings. (VOC 0.01g/l)

Premier 32-17 UL is produced under the classification and follow up service of Under Writers Laboratory, Inc.

Premier 32-17 UL contains no asbestos, lead, mercury or mercury compounds

Recommended Use

Premier32-17 UL is highly recommended in application where fibrous glass and other type of insulations are bonded to the interior or exterior of metal duct system. It is ideal for sealing ASJ, FRK and FSK jackets and board facings at joints, laps and over staple and weld pin puncture and for sealing flexible air duct to rigid connectors.

Features

It is highly antifungal and resistant to mold, mildew, water, extreme temperature changes and aging. Resistant to oil, grease and mildly resistant to diluted alkalis and acids.

Form Supplied

Cartridge

DATA REPRODUCED FROM UNDERWRITERS LABORATORIES, INC. BUILDING MATERIALS DIRECTORY

COATING GENERAL PURPOSE	R-27945
	Surface Burning Inorganic Characteristics (ASTM E 84) 1/4inch (6.4 mm) Reinforced cement board
Surface Flame Spread	0
Smoked Developed	0

Specification

Property	Value	Unit of Measurement	Method
Specific Gravity	1.50 ±0.10	kg/Lt.	ASTM D1475-98
Solid Percentage	69±3	%	ASTM D2369
Skin Formation Time	9	Minutes	XSTM 09
Viscosity Flow	Non Sag Paste		
Hardness	75-85	Shore A	ASTM D2240
Tensile Strength	5-8	kg/cm2	XSTM 11
Service Temperature	-50 to 150	°C	XSTM 07
Water Permeance	0.40-0.50 (9mm)	Perms	ASTM E96

Other Data*

Appearance
Cure System
Full cure
Coverage

Clear / White / Black / Grey Color

ACETOXY

1-5 Days Depending on bead thickness, humidity and temperature

Brush: 0.6 -1.2 m2 /Lt with WFT of 1.6mm to 0.8 mm

Caulking Gun: 35-40 m per cartridge

125-130 lineal ft. /tube of 310 ml @ 1/8 inch bead

30-35 lineal ft. /tube of 310 ml @ 1/4 inch bead



Surface Preparation

The surface should be structurally sound, clean, dry, leveled and free from dust curing compounds grease and other loose debris.

Application Procedure

Premier 32-17 UL is applied to clean, dry, oil-free and sounded surface, by Power Extrusion or trowel uniformly.

Packaging

510 gm (310 ml) cartridge.

Shelf life Storage

12 months from date of manufacturing in an original unopened container.

Storage

Store product at 10°C - 40°C for maximum storage life. Higher temperatures reduce normal storage life. Lower temperatures may cause increased viscosity of a temporary nature. Rotate stock on a "first in – first out" basis.

Health & Safety

Please refer to the MSDS.



This Information and our technical advice - whether verbal, in writing or by way of trials - are given in good faith but without warranty, and this also applies where proprietary rights of third parties are involved. Our advice does not release you from the obligation to verify the information currently provided - especially that contained in our safety data and technical information sheets - and to test our products as to their suitability for the intended processes and uses. The application, use and processing of our products and the products manufactured by you on the basis of our technical advice are beyond our control and, therefore, entirely your own responsibility.