

Type

UL Listed HVAC Vapor Barrier Coating.

Description

PREMIER VB-95 UL is an UL certified, zero VOC water based, fire retardant, high solid vapor barrier coating for duct insulation. It is washable, tough and abrasion resistant. It has excellent water resistance and lower water permeance. It can be used in highly humid environment and greatly retards water vapor permeation. It is specially formulated for both indoor and outdoor application. PREMIER VB-95 UL meets the requirements of Military Specification MIL-A-3316C class 1, grade A. PREMIER VB-95 UL meets the requirements for LEED IEQ 4.2, Low emitting material, paints and coatings. VOC 0.01g/l PREMIER VB-95 UL is produced under the classification and follow up service of Underwriter's Laboratory, Inc. PREMIER VB-95 UL contains no asbestos, lead, mercury or mercury compounds.

Recommended Use

It is used for outdoors as well as indoors-thermal insulation material on metal duct in areas where high humidity and elevated temperature are major problems. It is ideal for sealing ASJ, FRK and FSK jacket board facing at joints, laps over staple and weld pin puncture.

Features

- Excellent water resistant
- Zero flame spread and smoked developed
- Excellent adhesion and high strength
- Washable
- Compatible with polystyrene and polyurethane foam insulation
- Non toxic and non flammable
- UV resistant
- Antibacterial
- Doesn't get discolored with age

Form Supplied

Thixotropic paste

DATA REPRODUCED FROM UNDERWRITERS LABORATORIES, INC. BUILDING MATERIALS DIRECTORY

COATING GENERAL PURPOSE	R-27945
	Surface Burning Inorganic Characteristics 14inch (6.4 mm) Reinforced cement board
Surface Flame Spread	0
Smoked Developed	0
Number of Coats	1
Rate per coat (sq.ft.per gal.)	40

Specification

PROPERTY	Value	Unit of Measurement	Method
Specific Gravity	1.35±0.15	kg/l	ASTM D 1475-98
Solid	62±2	%	ASTM D 1644
Viscosity	25000-55000	cps	ASTM D 2196
Flash point	>100	°C	ASTM D 93
VOC content	<0.01	g/l	ASTM D 2369-98
Water permeance	0.083	perms	ASTM F 1249
Drying time (touch)	0.013	perms	ASTM E 96
	30-60	minute	ASTM D 1640



Other Data*

Appearance	White color
Service Temperature	-18°C to 120°C
Chemical Resistance	Excellent
Cure Film	Flexible & tough
UV Resistivity	Excellent
Insulation Properties	Excellent

Surface Preparation

The surface should be structurally sound, clean, dry, leveled and free from dust, curing compounds, grease, and other loose debris.

Application Procedure

Apply PREMIER VB-95 UL @ 1.5 -2.5 m²/liter (subject to surface condition). It is very important to ensure that each coat of PREMIER VB-95 UL is totally cured before the next coat is applied. The dry film thickness will vary with fabric selected.

Packaging

5 USG Pails

Shelf life Storage

18 months from date of manufacturing in an original unopened container. Store product 10°C - 40°C for maximum storage life. Higher temperatures reduce Normal storage life. Lower temperatures may cause increased viscosity of a Temporary nature. Rotate stock on a "first in first out" basis.

Cleaning

Tools : Clean immediately after use with water or white spirit if the material has dried.

Surface : Immediately removed any adhesive from the surface of the floor covering with the damp cloth.

Health & Safety

Please refer to the MSDS.



This Information and our technical advice - whether verbal, in writing or by way of trials - are given in good faith but without warranty, and this also applies where proprietary rights of third parties are involved. Our advice does not release you from the obligation to verify the information currently provided - especially that contained in our safety data and technical information sheets - and to test our products as to their suitability for the intended processes and uses. The application, use and processing of our products and the products manufactured by you on the basis of our technical advice are beyond our control and, therefore, entirely your own responsibility.