

SILIBOX

 SILIBEST

C-Type first impression silicon putty.

is a Silicon Putty polysiloxane based condensation-curing specially formulated for both two-stage putty/wash and one-stage putty/ wash techniques. Very high viscosity and excellent reproduction of details. No release of toxic substances during and after curing.



 Main Characteristics

Pleasant minty taste	For more patient comfort
The combination of excellent initial flowing and final rigidity	best results for all impressions
High Compressive strength	Recovery from deformation
Adequate working time	For a stress-free procedure
Short intra-oral setting time	For real time-saving
Non-Sticky Material	Easy Handling and Mixing
No release of toxic substances	Highest Compatibility

Technical Characteristic


Mixing time	Working time	Minimum time in mouth	Recovery from Deformation	Strain compression	Linear dimensional change in 24 hours
30''	1'20''	3'	99,75%	3,5%	-0,15%

Detail reproduction	Hardness Shore A	Color	ISO 4823
40µm	53	Orange	Type 0 – Putty

- Recorded at 23 +/- 2°C and 50+/-10% relative humidity.

Packing

Jar of 900 mL + 1 spoon



✓ **SILILIGHT**


C-Type second impression silicon light body. SILILIGHT is a light body silicon polysiloxane based condensation curing specially formulated for both two-stage putty/wash and one-stage putty/ wash techniques. Low viscosity and excellent reproduction of details. No release of toxic substances during and after curing.



✓ **Main Characteristics:**

- Easy Handling and Mixing
- Optimal initial fluidity for easy intraoral product flowing
- High Compressive strength and recovery from deformation Perfect reproduction of all details
- Orange Flavor

✓ **Dosage**



Technical Characteristic


Mixing time	Working time	Minimum time in mouth	Recovery from Deformation	Strain compression	Linear dimensional change in 24 hours
30''	2'	3'30''	99,9%	4,5%	-0,2%

Detail reproduction	Hardness Shore A	Color	ISO 4823
5µm	40	Purple	Type 3- Light Body

- Recorded at 23 +/- 2°C and 50 +/- 10% relative humidity.

Packing

Tube of 140 mL



CATALYST GEL

BMS Dental Type C silicones are also available in practical and convenient SILIBOX and SILIKIT formats. Furthermore, thanks to the printed mixing guide on our mixing pads, the phases of dosage and mixing of Sililight with the Catalyst Gel are extremely simplified, thus avoiding material waste.

 **Packing** 
Tube of 60 mL

 **Blue color**



 **Dosage**

