International Journal of Biological Macromolecules 133 (2019) 811–816

Contents lists available at ScienceDirect

International Journal of Biological Macromolecules

journal homepage: http://www.elsevier.com/locate/ijbiomac

Development of chitosan encapsulated tricalcium phosphate biocomposite for fluoride retention

Natrayasamy Viswanathan [a,*], Ilango Aswin Kumar [a], Sankaran Meenakshi [b]

[a] Department of Chemistry, Anna University, University College of Engineering - Dindigul, Dindigul - 624 622, Tamilnadu, India
[b] Department of Chemistry, Gandhigram Rural Institute - Deemed to be University, Gandhigram - 624 302, Tamilnadu, India

ARTICLE INFO

Article history:
Received 22 December 2018
Received in revised form 26 March 2019
Accepted 11 April 2019
Available online 12 April 2019

Keywords:
Tricalcium phosphate
Chitosan
TCPCS composite
Fluoride sorption

ABSTRACT

The powder form of tricalcium phosphate (TCP) causes the significant pressure drop which limit its application under field conditions. To trounce such technological troubles and to enhance the defluoridation capacity (DC) of TCP, chitosan (CS) encapsulated TCP polymeric composite was prepared by dispersing TCP particles into chitosan polymeric matrix to produce tricalcium phosphate/chitosan (TCPCS) composite which could be made into any desirable form. The synthesized TCPCS composite possesses an enhanced DC of 1034 mgF^-/kg than the individual components viz., TCP and chitosan which has got DC of 490 and 52 mgF^-/kg respectively. The prepared adsorbents were characterized by FTIR, SEM and EDAX analysis. The various physico-chemical properties such as contact time, solution pH, co-anions and temperature were optimized to get maximum defluoridation. The equilibrium and kinetic experiments were conducted for TCPCS composite toward fluoride removal. The practical applicability of TCPCS composite was examined at field conditions.

© 2019 Elsevier B.V. All rights reserved.

1. Introduction

The excess fluoride content in drinking water is mainly due to the fluoride bearing rocks/minerals and anthropogenic sources. Drinking water is the major source of fluoride intake. Fluoride has both beneficial and detrimental effects on human body depending on its concentration in water. Fluoride ion, within the tolerance limit (<1.5 mg/L) is an essential for the formation of bone, teeth and for the normal mineralization in hard tissues. The presence of excess fluoride (>1.5 mg/L) content leads to fluorosis. Since, fluorosis is an incurable and irreversible disease. Defluoridation is one of the best options to reduce the fluoride concentration in water.

Researchers have turned their attention toward defluoridation and the various potential methods have been proposed viz., ion-exchange [1], precipitation [2], adsorption [3] and electro-coagulation [4] for fluoride removal. Among the techniques, adsorption seems to be effective because of its easy handling nature, effective removal efficiency and regeneration capability. The various prospective inorganic adsorbents namely activated alumina [5], synthetic metal oxide [6], hydroxyapatite [7], hydrotalcite [8], tricalcium phosphate [9], activated carbon [10], magnetic adsorbent [11], modified chitosan beads [12], zeolites [13], polymeric resins [3], metal loaded resins [14] and modified cellulose [15] were reported for the defluoridation of drinking water. In recent years, the inorganic materials have been utilized for adsorption study due to its selectivity and intercalation properties. These materials have been found to possess the better properties than the simple salt of metals. The selectivity may be enhanced by varying the composition of the materials.

Tricalcium phosphate (TCP) is an inorganic material possesses an appreciable defluoridation capacity (DC) but it has brittleness, poor mechanical strength and create pressure drops during column studies. To evade such technology bottlenecks, polymeric composites were prepared by dispersing the inorganic materials in organic polymeric matrix to produce the usable products. Biosorption is an environmentally sound technique for minimizing the water pollution. The biopolymers like chitin, chitosan, cellulose, etc., have been extensively utilized for the removal of various toxic ions [16–19]. Chitosan (CS) is the deacetylation of chitin, possesses the unique properties like non-toxicity, biocompatibility, biodegradability and biofunctional. The amine groups of CS get easily protonated in the acid solution and attract the metal ions or anionic pollutants [20]. Recently, chitosan supported materials have been utilized for toxic fluoride removal [21–25]. Hence, chitosan was encapsulated with TCP to prepare TCPCS composite for defluoridation studies.

The present investigation is aimed to utilize the advantages of both TCP and chitosan, by developing TCPCS composite for fluoride removal. Defluoridation experiments were carried out to optimize the various adsorption influencing parameters viz., contact time, solution pH, influence of co-anions and temperature for maximum defluoridation. The experimental data was fitted with various isotherms and kinetic models to find the best fit for the sorption system. The suitability of TCPCS

* Corresponding author.
E-mail address: drnviswanathan@gmail.com (N. Viswanathan).

https://doi.org/10.1016/j.ijbiomac.2019.04.076
0141-8130/© 2019 Elsevier B.V. All rights reserved.




Fig. 1. Effect of contact time on DC of chitosan, TCP and TCPCS composite by taking 0.1 g of adsorbent with 10 mg/L of initial fluoride concentration at 303 K.

composite at field conditions was also performed by collecting fluoride contaminated water in a nearby fluoride endemic village.

2. Materials and methods

2.1. Materials

Chitosan (85% deacetylated) with an average molecular mass of 25 kDa was supplied by Pelican Biotech and Chemicals Labs, Kerala, India. glutaraldehyde (98.00%), glacial acetic acid (>99.00%) and Tricalcium phosphate (99.00%) was procured from Merck, India. The fluoride stock solution was prepared using double distilled (DD) water. All other chemicals were used in analytical grade.

2.2. Synthesis of TCPCS composite

About 20 g of TCP powder was immersed in 30 mL of DD water to make TCP slurry. Chitosan (CS) was dissolved in 2% of dilute acetic acid and added to TCP slurry followed by the mixture was stirred under mechanical shaker for 30 min. Then, about 5% of glutaraldehyde solution at a volume ratio 40: 1 of CS was added and stirred vigorously for 5 min. Then, the mixture was refrigerated at 4 °C upto 24 h to undergo the cross-link reaction. Further, the mixture was dried in hot air oven at 60 °C for 6 h to completely remove the solvent and to reduce the excess shrinkage [26]. Finally, the dried TCPCS composite was ground to fine powders of uniform size using ball mill (IKA, Germany) and utilized for fluoride adsorption studies.

Table 1
Characteristics of TCPCS composite.

Constituents	TCPCS composite
Inorganic material	Tricalcium phosphate
Organic matrix	Chitosan cross-linked with glutaraldehyde
Particle size (nm)	264
Density (g/cm^3)	0.701
BET surface area (m^2/g)	69.05
pH_{zpc}	6.60

2.3. Fluoride sorption experiments

The defluoridation experiments were carried out by batch equilibrium method. About 0.1 g of the adsorbent was added into 50 mL of sodium fluoride solution having the initial concentration of 10 mg/L. The contents were shaken using a mechanical shaker at a rotating speed of 200 rpm followed by the filtrate concentration was analyzed using Thermo Orion Benchtop Multiparameter kit. The various adsorption affecting parameters like contact time, pH, co-anions and temperature were optimized to get maximum DC. In kinetic studies, the effect of the different initial fluoride concentrations viz., 9, 11, 13 and 15 mg/L at 303, 313 and 323 K on its sorption rate was studied. The defluoridation capacity (DC) of the adsorbent was calculated by the Eq. (1) as follows

$$\text{Defluoridation capacity(DC)} = \frac{C_i - C_e}{m}\ V \times 1000\ \text{mgF}^-/\text{kg} \qquad (1)$$

where, C_i is initial fluoride concentration (mg/L), C_e is equilibrium fluoride concentration (mg/L), m is mass of the sorbent (g) and V is volume of the solution (L).

2.4. Analysis

The concentration of fluoride was measured using Thermo Orion Benchtop Multiparameter kit (Model: VERSA STAR 92) with fluoride ion selective electrode (9609 BNWP) [27]. The solution pH was measured with the same instrument using pH electrode. All other water quality parameters were analyzed using standard methods [28]. The




Fig. 2. Effect of pH on DC of TCP and TCPCS composite by taking 0.1 g of adsorbent and 10 mg/L of initial fluoride concentration with fixed contact time of 30 min at 303 K.




Fig. 3. Effect of co-ions on DC of TCPCS composite by taking 200 mg/L of initial co-ions concentration and 10 mg/L of initial fluoride concentration with fixed contact time of 30 min at 303 K.




Fig. 4. FTIR spectra of CS, TCP and TCPCS composite.

pH at zero point of charge (pH_{zpc}) of the adsorbent was measured by pH drift method [29].

2.5. Instrumental analysis

The significant functional groups present in the prepared adsorbents were studied by Fourier transform infrared (FTIR) spectrometer with JASCO-460 plus model. The surface morphology of the composite was studied using scanning electron microscope (SEM) with Vega3 Tescan model. The energy dispersive X-ray analyzer (EDAX) with Bruker Nano GMBH model was used for the quantitative detection of elements in TCPCS composite and after fluoride adsorption. The surface area of the composite was studied by BET surface area analyzer with NOVA 1000 model.

2.6. Statistical tools

Computations were made using Microcal Origin (Version 15) software. The significance of the data trends for fitting the suitable model was attained using error bar plot, regression correlation coefficient (r), chi-square analysis and standard deviation (sd).

3. Results and discussion

3.1. Effect of contact time

The effect of contact time is the primary study in the adsorption system in which it offers the lowest time for the adsorbent to reach highest DC. The experiment was performed with six conical flasks having 50 mL of 10 mg/L of initial fluoride concentration and 0.1 g of the adsorbent with different contact time of 10–60 min at 303 K. It is evident from Fig. 1 that, DC of the adsorbents viz., CS, TCP and TCPCS composite reached saturation at 30 min. Among them, TCPCS composite possesses an enhanced DC of 1034 mgF^{-}/kg than TCP and CS which has got DC of 490 and 52 mgF^{-}/kg respectively. In addition, TCP also possess an appreciable DC. Hence, taking this concern further adsorption studies were focused to TCPCS composite and TCP with fixed contact time of 30 min.

3.2. Influence of solution pH

The solution pH is a significant parameter which affects the defluoridation at adsorbate-adsorbent interfaces. The sorption of fluoride ions onto the prepared adsorbents were studied at five different




Fig. 5. SEM images of (a) TCPCS composite and (b) fluoride sorbed TCPCS composite, EDAX spectra of (c) TCPCS composite and (d) fluoride treated TCPCS composite.

Table 2a
Isotherm models of TCPCS composite for fluoride adsorption.

Temp. (K)	Freundlich isotherm					Langmuir isotherm				
	1/n	n	k_F $\frac{(mg/g)}{(L/mg)^{1/n}}$	r	χ^2	Q° (mg/g)	b (L/g)	R_L	r	χ^2
303	0.346	2.890	0.511	0.989	1.14 E-4	1.550	0.193	0.366	0.999	5.00 E-5
313	0.323	3.096	0.641	0.954	8.57 E-4	2.169	0.227	0.328	0.979	3.04 E-4
323	0.300	3.333	0.971	0.992	1.47 E-4	2.632	0.283	0.282	0.997	1.20 E-4

initial pH levels viz., 3, 5, 7, 9 and 11 by keeping other parameters like contact time, dosage and initial fluoride concentration as constant at 303 K. The pH of the fluoride solution was adjusted by adding 0.1 M HCl/NaOH solution. Fig. 2 shows that DC of the sorbents was influenced by pH medium. The maximum DC of TCP and TCPCS composite was observed at acidic pH conditions whereas the minimum DC was observed at alkaline pH conditions.

The pH_{zpc} of TCPCS composite was found to be 6.60 (cf. Table 1). This result concludes that the adsorbent surface gets protonated if pH < pH_{zpc} and hence it attracts the negatively charged fluoride ion by means of electrostatic attraction. However, if pH > pH_{zpc}, the adsorbent surface gets negatively charged which results in the electrostatic repulsion of F^- ions. In all the pH ranges studied, TCPCS composite found to possess higher DC than that of TCP. Therefore, further studies were focused on TCPCS composite. In addition, the solution pH after the fluoride adsorption with TCPCS composite tends to be neutral which shows the suitability of TCPCS composite in the wide range of pH environment.

3.3. Effect of co-anions

In addition to F^-, the natural water also contains the other anions like Cl^-, SO_4^{2-}, HCO_3^- and NO_3^- ions which may often affects fluoride adsorption. To perform this study, the initial co-anions concentration were taken as 200 mg/L whereas the initial fluoride concentration was taken as 10 mg/L by keeping all other parameters such as contact time, pH and dosage as constants. From Fig. 3, it is evident that DC of TCPCS composite was slightly affected by the presence of Cl^-, SO_4^{2-}, NO_3^- and HCO_3^- ions; hence a reduction in DC was observed which shows the competing effect with F^- ion during sorption process. The order of interfering anions for fluoride removal was found to be $HCO_3^- > Cl^-$, $SO_4^{2-} > NO_3^-$. HCO_3^- ion present in the natural water may affect the fluoride adsorption because it has the similar ionic radius with that of fluoride. In addition, the normal water contains higher HCO_3^- concentration than fluoride. Hence, HCO_3^- readily occupies the reactive sites of TCPCS composite instead of fluoride in natural water.

3.4. Characterization of the materials

3.4.1. FTIR analysis

The significant functional groups present in CS, TCP and TCPCS composite were studied using FTIR analysis which is shown in Fig. 4. In FTIR spectra of CS, the symmetrical stretching bands of -OH and -NH_2 groups were observed at 3605 and 3151 cm^{-1} respectively. The asymmetric and symmetric frequency of C—H group was observed at 2929 and 2836 cm^{-1}. In addition, the stretching FTIR bands of carbonyl group of -CONHR and -NH_3^+ were appeared at 1650 and 1415 cm^{-1} respectively [30]. The comparison in FTIR spectra of CS with and without TCP powder has no identifiable difference. It was noticed that the corresponding FTIR bands of both CS and TCP were retained in FTIR spectra of TCPCS composite. Mainly, a sharp band at 1039 cm^{-1} represents the presence of PO_4^{3-} group of TCP in TCPCS composite. In addition, the FTIR bands at 1040, 961 and 601 cm^{-1} clearly indicates the presence of TCP [31]. The band at 3414 cm^{-1} indicates the presence of -OH groups in chitosan. The result concludes that the incorporation of TCP in CS gives TCPCS composite for fluoride adsorption. The characteristics of TCPCS composite are shown in Table 1.

3.4.2. SEM and EDAX analysis

The surface morphology of TCPCS composite before and after fluoride adsorption was studied by SEM analysis which is shown in Fig. 5a and b respectively. SEM micrograph of TCPCS composite possess the uneven surface which is shown in Fig. 5a whereas SEM image of fluoride sorbed TCPCS composite show the changes in the surface which may confirm the fluoride adsorption (cf. Fig. 5b). The presence of significant elements of TCPCS composite before and after fluoride adsorption was studied by EDAX analysis. EDAX spectra of TCPCS composite confirm the presence of respective elements such as Ca, O and P in the composite (cf. Fig. 5c). The fluoride sorption has occurred on TCPCS composite which was confirmed by the presence of fluoride peak in EDAX spectra of fluoride adsorbed TCPCS composite (cf. Fig. 5d).

3.5. Sorption isotherms

The nature of the fluoride adsorption mechanism on TCPCS composite was studied by adsorption isotherms. To quantify the sorption capacity of TCPCS composite toward fluoride removal, the isotherms namely Freundlich [32] and Langmuir [33] have been investigated. The linear plot of log q_e vs. log C_e indicates the applicability of Freundlich isotherm. The values of 1/n and k_F were calculated from the slope and the intercept of the plot are listed in Table 2a. The 1/n value lies between 0 and 1 whereas n value lies between in the range of 1 to 10 may indicate the favourable condition for fluoride adsorption.

As the reaction temperature increases, k_F value also increases which indicates the fluoride adsorption by TCPCS composite is endothermic in nature. A linear plot of C_e/q_e against C_e gives Q° and b values from the slope and intercept respectively which is listed in Table 2a. The increasing Q° value at the temperature goes from 303 to 323 K may also confirms the endothermic nature of fluoride sorption. The results of chi-square analysis (χ^2) and regression coefficient (r) are also presented in Table 2a. As a result concludes that Langmuir isotherm has lower value of χ^2 and higher value of r compared to Freundlich isotherm and hence Langmuir isotherm model can be considered as best fitting isotherm for the fluoride sorption onto TCPCS composite.

3.6. Thermodynamic parameters

Thermodynamic parameters are associated with the fluoride adsorption by means of the standard free energy change (ΔG°), standard

Table 2b
Thermodynamic parameter results of TCPCS composite.

Thermodynamic parameters		TCPCS composite
ΔG° (kJ/mol)	303 K	−6.70
	313 K	−6.64
	323 K	−6.59
ΔH° (kJ/mol)		8.38
ΔS° (J/mol/K)		0.01

Table 3
Kinetic models of TCPCS composite.

Kinetic models	Parameters	303 K				313 K				323 K			
		9 mg/L	11 mg/L	13 mg/L	15 mg/L	9 mg/L	11 mg/L	13 mg/L	15 mg/L	9 mg/L	11 mg/L	13 mg/L	15 mg/L
Pseudo-first-order	k_{ad} (min^{-1})	0.159	0.131	0.129	0.120	0.124	0.129	0.157	0.147	0.152	0.143	0.150	0.140
	r	0.969	0.965	0.937	0.983	0.940	0.976	0.960	0.957	0.984	0.974	0.958	0.971
	sd	0.183	0.163	0.217	0.103	0.207	0.132	0.208	0.205	0.125	0.151	0.204	0.157
Pseudo-second-order	q_e (mg/g)	1.385	1.239	1.311	1.290	1.404	1.597	1.880	1.855	1.972	2.053	2.222	2.179
	k (g/mg min)	0.052	0.127	0.106	0.170	0.144	0.084	0.048	0.081	0.083	0.084	0.079	0.145
	h (mg/g min)	0.100	0.195	0.181	0.283	0.285	0.214	0.171	0.278	0.325	0.353	0.389	0.687
	r	0.999	0.998	0.994	0.998	0.997	0.998	0.974	0.995	0.999	0.997	0.997	0.999
	sd	0.039	0.055	0.088	0.056	0.060	0.037	0.129	0.056	0.015	0.040	0.035	0.022
Particle diffusion	k_p (min^{-1})	0.158	0.131	0.129	0.120	0.125	0.130	0.157	0.148	0.153	0.142	0.149	0.139
	r	0.967	0.965	0.937	0.983	0.940	0.976	0.960	0.957	0.984	0.974	0.958	0.971
	sd	0.422	0.374	0.501	0.237	0.476	0.304	0.479	0.472	0.289	0.348	0.470	0.362
Intraparticle diffusion	k_i (mg/g $min^{0.5}$)	0.179	0.140	0.149	0.124	0.138	0.195	0.233	0.207	0.226	0.221	0.237	0.173
	r	0.993	0.992	0.999	0.994	0.999	0.976	0.977	0.995	0.981	0.995	0.996	0.994
	sd	0.029	0.024	0.010	0.018	0.007	0.059	0.068	0.029	0.060	0.031	0.028	0.025

enthalpy change (ΔH°) and standard entropy change (ΔS°) which are calculated according to the method suggested by Khan and Singh [34]. The calculated values of the various thermodynamic parameters are shown in Table 2b. The negative ΔG° value confirms the spontaneous nature of fluoride sorption. The positive ΔH° value indicates the fluoride sorption process is endothermic [35]. The positive ΔS° value shows the randomness at the solid/liquid interface during fluoride sorption which indicates that the process is irreversible.

3.7. Sorption kinetics

The kinetic models like reaction-based and diffusion-based models were studied to fit the experimental data for fluoride adsorption onto TCPCS composite. The commonly used pseudo-first-order [36] and pseudo-second-order [37] kinetic models were employed to elucidate the solid/liquid adsorption nature. The linear plot of log (q_e-q_t) against t gives a straight line which indicates the applicability of the pseudo-first-order kinetic model and their rate constant (k_{ad}) and r values are presented in Table 3. The value of q_e (1/slope), k (slope^2/intercept) and h (1/intercept) of the pseudo-second-order kinetic equation can be plotted by t/q_t vs t and the values of q_e, k, h and r of the pseudo-second-order kinetic model were attained at 303, 313 and 323 K. The q_e values increases with increase in temperature indicate the fluoride sorption is effective at high temperature. The higher r values for pseudo-second-order model than the pseudo-first-order indicates the applicability of the pseudo-second-order kinetic model toward fluoride adsorption.

For a solid-liquid sorption process, the solute transfer is usually characterized either by particle diffusion [38] or by intraparticle diffusion [39] control. The straight line plots of ln (1-C_t/C_e) vs. t and q_t vs. $t^{0.5}$ indicates the applicability of particle and intraparticle diffusion models respectively. The k_p, k_i and r values at different temperatures viz., 303, 313 and 323 K of both models are illustrated in Table 3. The r value obtained for both particle and intraparticle diffusion models are almost comparable which suggest that the fluoride adsorption on TCPCS composite follows both particle and intraparticle diffusion models. The fitting sorption data of the kinetic models were further assessed by the values of standard deviation (sd). Lower value of sd shows the better fit to sorption data. The sd value of TCPCS composite for all the kinetic models are summarized in Table 3. Smaller sd values observed for pseudo-second-order and intraparticle diffusion models indicate that these two models are significant in defining the fluoride adsorption onto TCPCS composite.

3.8. Defluoridation mechanism of TCPCS composite

The feasible mechanism of fluoride sorption onto TCPCS composite was mainly governed by electrostatic attraction which is shown in Fig. 6. The positively charged Ca^{2+} ions in the surface of TCPCS composite may attracts the negatively charged fluoride ions by means of electrostatic attraction and thus removes fluoride via chemisorption which was confirmed from EDAX spectra of the fluoride adsorbed TCPCS composite (cf. Fig. 5d). Moreover, the composite can be considered as hard acid because Ca^{2+} ion is possessed by TCPCS composite. Hence they prefer to bind with hard base, highly electronegative and low polarisable fluoride ion in water [40].

3.9. Field study

The suitability of TCPCS composite was also tested with the field water sample collected from the nearby fluoride-endemic area of Dindigul district, Tamilnadu. About 0.1 g of adsorbent was added into 50 mL of field water sample and are shaken using mechanical shaker at 30 min and the results are presented in Table 4. TCPCS composite




Fig. 6. Feasible mechanism of fluoride sorption by TCPCS composite.

Table 4
Field trial results of TCPCS composite.

Water quality parameters	TCPCS composite	
	Before	After
F^- (mg/L)	2.48	0.89
pH	8.52	8.10
Cl^- (mg/L)	390	332
Total hardness (mg/L)	800	673
Total dissolved solids (mg/L)	420	354

reduces the fluoride concentration of field water below the tolerance limit (< 1.5 mg/L). Moreover, there is a significant reduction in the levels of other water quality parameters in addition to fluoride was observed. The result indicates the suitability of the prepared TCPCS composite for defluoridation of the collected field water.

4. Conclusions

This present study was focused to synthesize TCPCS composite for fluoride adsorption. The prepared TCPCS composite possesses an enhanced DC than TCP and chitosan. The fluoride adsorption onto TCPCS composite was influenced by solution pH. In natural water, the bicarbonate ion competes with fluoride adsorption. The characterization details of the prepared adsorbents were studied using FTIR, SEM and EDAX analysis. TCPCS composite follows Langmuir isotherm toward fluoride adsorption. The thermodynamic parameters result shows that the nature of fluoride sorption is spontaneous and endothermic. The rate of sorption follows pseudo-second-order kinetic model and fluoride sorption occurred through intraparticle diffusion pattern. The possible mechanism of fluoride removal using TCPCS composite was governed by electrostatic attraction. Field trial studies indicate that TCPCS composite could be used as a good defluoridating material.

Acknowledgement

The authors are thankful to the Council of Scientific and Industrial Research (CSIR) (F.No.01(0226)/19), New Delhi, India for providing financial support to carry out this research work.

References

[1] S. Meenakshi, N. Viswanathan, Identification of selective ion-exchange resin for fluoride sorption, J. Colloid Interface Sci. 308 (2007) 438–450.
[2] K.M. Popat, P.S. Anand, B.D. Dasare, Selective removal of fluoride ions from water by the aluminium form of the aminomethylphosphonic acid-type ion exchanger, React. Polym. 23 (1994) 23–32.
[3] K. Pandi, N. Viswanathan, In situ fabrication of magnetic iron oxide over nano-hydroxyapatite gelatin eco-polymeric composite for defluoridation studies, J. Chem. Eng. Data 61 (2016) 571–578.
[4] S. Vasudevan, B. Suresh Kannan, J. Lakshmi, S. Mohanraj, G. Sozhan, Effects of alternating and direct current in electrocoagulation process on the removal of fluoride from water, J. Chem. Technol. Biotechnol. 86 (2011) 428–436.
[5] G. Karthikeyan, A.S. Sundarraj, S. Meenakshi, K.P. Elango, Adsorption dynamics and the effect of temperature of fluoride at alumina-solution interface, J. Indian Chem. Soc. 81 (2004) 461–466.
[6] K. Biswas, S.K. Saha, U.C. Ghosh, Adsorption of fluoride from aqueous solution by asynthetic Iron(III)-Aluminium(III) mixed oxide, Ind. Eng. Chem. Res. 46 (2007) 5346–5356.
[7] C. Sairam Sundaram, N. Viswanathan, S. Meenakshi, Defluoridation chemistry of synthetic hydroxyapatite at nano scale: equilibrium and kinetic studies, J. Hazard. Mater. 155 (2008) 206–215.
[8] H. Wang, J. Chen, Y. Cai, J. Ji, L. Liu, H.H. Teng, Defluoridation of drinking water by Mg/Al hydrotalcite-like compounds and their calcined products, Appl. Clay Sci. 35 (2007) 59–66.
[9] C.S. Boruff, Removal of fluoride from drinking waters, Ind. Eng. Chem. 26 (1934) 69–71.
[10] G. Karthikeyan, S. Siva Ilango, Fluoride sorption using Morringa Indica–based activated carbon, Iran, J. Environ. Health Sci. Eng. 4 (2007) 21–28.
[11] A. Goswami, M.K. Purkait, Removal of fluoride from drinking water using nanomagnetite aggregated schwertmannite, J. Water Process Engg. 1 (2014) 91–100.
[12] N. Viswanathan, S. Meenakshi, Enhanced fluoride sorption using La(III) incorporated carboxylated chitosan beads, J. Colloid Interface Sci. 322 (2008) 375–383.
[13] M.S. Onyango, Y. Kojima, O. Aoyi, E.C. Bernardo, H. Matsuda, Adsorption equilibrium modeling and solution chemistry dependence of fluoride removal from water by trivalent-cation exchanged zeolite F-9, J. Colloid Interface Sci. 279 (2004) 341–350.
[14] N. Viswanathan, S. Meenakshi, Effect of metal ion loaded in a resin towards fluoride retention, J. Fluor. Chem. 129 (2008) 645–653.
[15] Y. Zhao, X. Li, L. Liu, F. Chen, Fluoride removal by Fe(III)-loaded ligand exchange cotton cellulose adsorbent from drinking water, Carbohydr. Polym. 72 (2008) 144–150.
[16] I. Aswin Kumar, N. Viswanathan, Hydrothermal fabrication of zirconium oxyhydroxide capped chitosan/kaolin framework for highly selective nitrate and phosphate retention, Ind. Eng. Chem. Res. 57 (43) (2018) 14470–14481.
[17] C. Sairam Sundaram, N. Viswanathan, S. Meenakshi, Defluoridation of water using magnesia/chitosan composite, J. Hazard. Mater. 163 (2009) 618–624.
[18] R. Jayakumar, M. Rajkumar, H. Freitas, N. Selvamurugan, S.V. Nair, T. Furuike, H. Tamura, Preparation, characterization, bioactive and metal uptake studies of alginate/phosphorylated chitin blend films, Int. J. Biol. Macromol. 44 (2009) 107–111.
[19] S. Periyasamy, V. Gopalakannan, N. Viswanathan, Fabrication of magnetic particles imprinted cellulose based biocomposites for chromium(VI) removal, Carbohydr. Polym. 174 (2017) 352–359.
[20] I. Aswin Kumar, N. Viswanathan, Preparation and testing of a tetra-amine copper(II) chitosan bead system for enhanced phosphate remediation, Carbohydr. Polym. 183 (2018) 173–182.
[21] K. Pandi, S. Periyasamy, N. Viswanathan, Remediation of fluoride from drinking water using magnetic iron oxide coated hydrotalcite/chitosan composite, Int. J. Biol. Macromol. 104 (2017) 1569–1577.
[22] N. Viswanathan, K. Pandi, S. Meenakshi, Synthesis of metal ion entrapped silica gel/chitosan biocomposite for defluoridation studies, Int. J. Biol. Macromol. 70 (2014) 347–353.
[23] K. Pandi, N. Viswanathan, Synthesis and applications of eco-magnetic nano-hydroxyapatite chitosan composite for enhanced fluoride sorption, Carbohydr. Polym. 134 (2015) 732–739.
[24] M. Rajiv Gandhi, G.N. Kousalya, N. Viswanathan, S. Meenakshi, Sorption behaviour of copper on chemically modified chitosan beads from aqueous solution, Carbohydr. Polym. 83 (3) (2011) 1082–1087.
[25] N. Viswanathan, S. Meenakshi, Enriched fluoride sorption using alumina/chitosan composite, J. Hazard. Mater. 178 (1–3) (2010) 226–232.
[26] S.J. Ding, Biodegradation behavior of chitosan/calcium phosphate composites, J. Non-Cryst. Solids 353 (2007) 2367–2373.
[27] Fluoride Electrode Instruction Manual. , Orion Research, USA, 2005.
[28] APHA, Standard Methods for the Examination of Water and Waste Water, American Public Health Association, Washington DC, 2005.
[29] M.V. Lopez-Ramon, F. Stoeckli, C. Moreno-Castilla, F. Carrasco-Marin, On the characterization of acidic and basic surface sites on carbons by various techniques, Carbon 37 (1999) 1215–1221.
[30] I. Aswin Kumar, C. Jeyaprabha, S. Meenakshi, N. Viswanathan, Hydrothermal encapsulation of lanthanum oxide derived *Aegle marmelos* admixed chitosan bead system for nitrate and phosphate retention, Int. J. Biol. Macromol. 130 (2019) 527–535.
[31] R. Niwas, U. Gupta, A.A. Khan, K.G. Varshney, The adsorption of phosphamidon on the surface of styrene supported zirconium (IV) tungstophosphate: a thermodynamic study, Colloids Surf., A 164 (2000) 115–119.
[32] H.M.F. Freundlich, Over the adsorption in solutionn, Z. Phys. Chem. 57 (1906) 385–470.
[33] I. Langmuir, The constitution and fundamental properties of solids and liquids, J. Am. Chem. Soc. 38 (1916) 2221–2295.
[34] A.A. Khan, R.P. Singh, Adsorption thermodynamics of carbofuran on Sn (IV) arsenosilicate in H^+, Na^+ and Ca^{2+} forms, Colloids Surf., A 24 (1987) 33–42.
[35] I. Aswin Kumar, N. Viswanathan, Development of multivalent metal ions imprinted chitosan biocomposites for phosphate sorption, Int. J. Biol. Macromol. 104 (2017) 1539–1547.
[36] S. Lagergren, Zur theorie der sogenannten adsorption gelöster stoffe, K. Sven. Vetenskapsakad. Handl. 24 (1898) 1–39.
[37] Y.S. Ho, Second order kinetic model for the sorption of cadmium on to tree fern: a comparison of linear and non linear methods, Water Res. 40 (2006) 119–125.
[38] M. Chanda, K.F. O'Driscoll, G.L. Rempel, Sorption of phenolics onto cross-linked poly (4-vinyl pyridine), React. Polym. 1 (1983) 281–293.
[39] W.J. Weber, J.C. Morris, Equilibria and capacities for adsorption on carbon, J. Sanit. Eng. Div. 90 (1964) 79–91.
[40] R.G. Pearson, Hard and soft acids and bases, J. Am. Chem. Soc. 85 (1963) 3533–3539.