



Purchase Order

Boutique International (P) LTD

C-45-46 Hosiery Complex Noida, PH-II Gautam Budh Nagar, U.P. 201305.

GST No: 09AAA4905C1Z5 Tel: (+91) 120 6797979 Fax: (+91) 120 6797999

E-mail: info@boutique.in

PO No: **ABCPLA1** PO Date: 11 Mar 21 (Thu) Supplier: Ashoka Beads Corporation Pvt. Ltd. ETA Date: 31 Mar 21 (Wed)
₹3.2 (15 Days) (11 Mar 2021)

Dear Sir,
Please Arrange following as per details given below:

Accessory Quality (Size) Color/Print	Shrnkg (%)	Wstg (%)	Accessory Type	Quantity*			Finance*	
				Send	Received	Unit	Rate	Total Amount
GPO LACE SMALL (8")	3	4	Greige		204,040	Meter	3.1	₹ 632,524

History Of Revise Purchase Order		From Qty.	To Qty.	ETA Dates
Date	PO Quantity	1	50,000	27 Mar 21 (Sat)
11 Mar 21 (Thu)	204,040 Meter	50,001	100,000	29 Mar 21 (Mon)
		100,001	204,040	30 Mar 21 (Tue)

General Instructions

- :-
1. All bills must state the Purchase Order number. Missing PO numbers on bills will nullify the bill.
 2. Good must be 100% checked on tables by vendor. It is complete responsibility of the supplier to dispatch only acceptable goods under 4 point AQL. If goods fail 5% check at BIPL or arrives without 100% checking reports, BIPL reserves the right to return goods to vendor or charge them damages and checking charges.
 3. Any quality issues related base quality parameters will lead to discounts or cancellations by BIPL.
 4. Rejected goods must be collected within a week, else BIPL will not be responsible for the returnable goods.
 5. All disputes will be subject to Delhi NCR jurisdiction.

Processed Instructions :-

1. Matching to be on D65
2. Finishing should be silicon finished in overfeeding. Soft Handfeel. All polyester and Nylon antistatic finish is a must.
3. Finishing shrinkage/Dimensional stability to steam to be +/-2%.
4. Banned chemicals: Azo, PCP, PH Value -6, heavy metals.
5. Bowing less than 3 inches will be acceptable.
6. After wash shrinkage should be less than 2%.
7. BIPL stamp on both ends of the Accessories should not be removed.
8. Colour fastness on multi fiber: Rubbing, Dry Cleaning, Washing 40 *C, Sun Fastness, Light Fastness must be minimum 4.
9. Pilling should be 4-5.
10. Tensile Strength 15 kg, Tear strength 1000 GM and Seam Slippage 8kg.

Boutique International Pvt. Ltd.

**SIGNATURE
Not
AVAILABLE**

Hemant Thakur

Accepted by

**SIGNATURE
Not
AVAILABLE**

Hemant Thakur