Nitoprime Zincrich 1

constructive solutions

Single component zinc-rich primer

Uses

Nitoprime Zincrich 1 is a galvanic sacrificial primer with a high zinc content for the protection of steel. It may be used for the protection of steel reinforcement as part of a concrete repair system or as an anti-corrosive primer prior to painting.

Advantages

- One component, it avoids possible mixing problems and can be used multiple times.
- Easily application by brush.
- Time saving - fast drying time.
- Ideal for using in tropical weathers.
- Combats corrosion by electrochemical means.
- Excellent rust inhibiting properties.
- Highly bonded to regular steel.

Description

Nitoprime Zincrich 1 is supplied as a single component fast-drying primer based on zinc powder and special resin.

Technical Support

Fosroc offers a comprehensive technical support service to specifiers, end users and contractors. It is also able to offer on-site technical assistance, an AutoCAD facility and dedicated specification assistance in locations all over the world.

Typical properties

Density	:	1.75 ± 0.05kg/ltr (at 23°C)
Color	:	Grey
Solid content	:	> 74 % by weight
Surface drying time	:	20 minutes at 25ºC
Overcoating time	:	2 Hours at 25ºC

Technical Support

One or two coats of Nitoprime Zincrich 1 are generally required, dependent largely on the nature and profile of the substrate. Nitoprime Zincrich 1 is recoatable generally after 2 hours at 25°C.

Application of concrete repair materials may also proceed at this time. At elevated temperatures, the recoatable and overlay times will be reduced. The minimum application temperature for Nitoprime Zincrich 1 is 5°C. Consult the local Fosroc office for further information.

Specification

Steel reinforcement primer

The steel reinforcement primer shall be Nitoprime Zincrich 1, a single component zinc-rich liquid, packed and supplied ready to use. An unbroken 75 microns thick coating shall be capable of providing 'active' galvanic protection within the repair zone.

It shall be a suitable viscosity to enable the coating to penetrate imperfections and pits within the surface of corrosion damaged steel bars.

The formulation of the primer shall be such that drying occurs to allow the application of the repair mortar to proceed after 20 to 45 minutes at 35°C or after 30 minutes to one hour at 20°C. It shall be fully compatible with the Renderoc system of concrete repair.

Instruction for use

Application

The application of Nitoprime Zincrich 1 must take place as soon as possible to a dry steel surface after completion of the preparation work but always within 3 hours. Although a single component product, it should be stirred thoroughly before use in order to re-disperse any settlement.

Apply one full and unbroken coat of Nitoprime Zincrich 1 by suitable brush, making sure that the back of exposed reinforcing bars are fully coated. A small brush is generally more suitable for this purpose. Allow to dry fully before continuing. If any doubt exists about having achieved an unbroken coating, a second application should be made as soon as the first coat is fully dry (generally between 30 minutes and two hour).

The primed surfaces should not be left exposed to the elements for longer than necessary before overcoating or application of the repair material. Nitoprime Zincrich 1 will, however, protect steel under clean interior exposure conditions for a period of several months.

In non-aggressive exterior environments, a maximum interval of 14 days will be tolerated but in industrial and/or marine environments this interval should be reduced to the practical minimum.

The application of concrete repair materials should proceed as soon as the Nitoprime Zincrich 1 is fully dry (generally 20 minutes to two hours - see under properties).

Low temperature working

The minimum application temperature is 5°C. The material should not be applied when the substrate and/or air temperature is 5°C and falling. At 5°C static temperature or at 5°C and rising, the application may proceed.

Cleaning

Nitoprime Zincrich 1 should be removed from tools, mixers and equipment with Fosroc Solvent 102 immediately after use.

Limitations

Nitoprime Zincrich 1 should not be applied when the temperature is below 5°C or is 5°C and falling. If any doubts arise concerning temperature or application conditions, consult the local Fosroc office.

Estimating

Supply	
Nitoprime Zincrich 1	1 & 5 Kg Can

Coverage	
Nitoprime Zincrich 1	3.5 - 5 m^2 /Kg at 50 - 75 micron DFT

Note: The coverage figure for Nitoprime Zincrich 1 is theoretical due to wastage factors and the variety and nature of possible substrates, practical figures will be reduced.

Storage

Nitoprime Zincrich 1 has a shelf life of 12 months if kept in a dry store in the original unopened packs

Important note

Fosroc products are guaranteed against defective materials and manufacture and are sold subject to its standard Conditions for the Supply of Goods and Service. **All Fosroc datasheets are updated on a regular basis. It is the user's responsibility to obtain the recent version.**

Fosroc Chemtech
Construction Chemicals

Head Office
6th of October City, 3rd Industrial Zone, Arab Republic of Egypt.
Tel: (02) 38242045 / (02) 38242046
Fax: (02) 38242098
E-mail: Egypt@Fosroc.com