

UPM Raflatac Technical Information

12-03-2022 EN SI

Product	PET WHITE TC 50 / RC15 / HD 70
Sales Code	AJ/RC15/28
EAN	6415788089446
Product use	Product designed for durable labelling applications on surfaces such as steel, glass and ABS. It will perform for the lifetime of the labelled product with very good adhesion and good print resistance against chemicals, UV-light, heat and moisture.

Typical technical values

Face	PET WHITE TC 50
Product	White, matt, top-coated polyester film.
Substance	55 g/m ² DIN 53352
Caliper	50 µm DIN 53370
Opacity	92 % ISO 2471
Gloss	13 % ASTM D2457
Printability	Suitable for flexography, screen and offset printing methods. Special inks designed for non-absorbent materials should be used. Thermal transfer is possible with selected wax, wax-resin and resin ribbons.

Adhesive	RC15
Type	Permanent
Composition	UV-acrylic
Tack	20 N/25mm FTM 9 (on glass)
Peel 180°	25 N/25mm FTM 1 (on glass)

Backing	HD70
Product	A white transparent glassine backing paper.
Substance	62 g/m ² ISO 536
Caliper	54 µm ISO 534
Tensile strength MD	7 kN/m ISO 1924
Tensile strength CD	2,7 kN/m ISO 1924
Transparency	48 % DIN 53147

Performance	
Total caliper	127 µm
Minimum labelling temperature	5 °C
Service temperature	-40 °C to 150 °C
Shelf life	From date of manufacture: 24 months, under FINAT defined storage conditions (+20-25°C and RH 40-50%). Prolonged storage at higher temperatures and/or humidity levels will shorten the shelf life.

Information

Adhesive coatweight

23 g/m²

Adhesion

Due to the fact that the adhesive needs a certain time to reach its final adhesion, we recommend waiting at least 24h (better 72h) after dispensing the label to the substrate before proceeding with any performance tests. Test Conditions: 23°C, 50% RH FTM1: 180° Peel Adhesion (300 mm/min) with 72 h dwell time

Surface	[N/25mm]
Stainless Steel	22
ABS	25
Polycarbonate	27
Polypropylene	7
HDPE	9
PA6	13
PA6 + GF30	17
Polyester	18
Lacquered panel	13
Powder coated panel	14

Chemical resistance

Test Conditions: Dwell time on glass plate: 24 h; 23°C 50% rH Immersion in chemical: 4 h; 23°C 50% rH

Chemical	Visual Appearance	Edge Penetration (mm)
Brake Fluid	no change	0
Engine Oil	no change	0
Diesel	no change	0
Distilled Water	no change	0
Dish Washing Agent	no change	0
Bleach	no change	0

Thermal Transfer Ribbons

(included in File MH26760): Armor: AXR 600, AXR 7+, AXR 8; Astro-med RY; Dainippon R300, R510; Kurz K501; Ricoh B110C, B110CX, B120EC ; Zebra Technologies Corp. 5100

Approvals

UL and CSA compliance

UL recognized acc. to UL969 and CSA recognized acc. to C22.2 No. 0.15. File-No.: MH26760

Application Surface	Max Temp [°C]	Min Temp [°C]	Indoor Use	Outdoor Use
Acrylic Paint (AC PT)	100	-40	x	x
Alkyd paint (AK PT)	150	-40	x	x
Aluminium (AL)	150	-40	x	x
Galvanized steel (GS)	150	-40	x	x
Polyester paint (PER PT)	100	-40	x	x
Stainless steel (SS)	150	-40	x	-
Phenolic-Phenol formaldehyde	100	-40	x	x
Polycarbonate (PC)	100	-40	x	x
Nylon - Polyamide (PA)	80	-40	x	x
Acrylonitrile butadiene styrene (ABS)	60	-40	x	x
Polystyrene (PS)	60	-40	x	x

Typical values

The listed technical data are typical values and give indications about the performance of the material only. They are not intended for specification purpose.

Disclaimer

The performance of the product should always be tested in the actual application conditions. Our recommendations are based on our most current knowledge and experience. As our products are used in conditions beyond our control, we cannot assume any liability for damage caused through their use. Users of our products are solely responsible that the product is suitable for its intended application, and have determined such at their sole discretion. Users must comply with any applicable legislation and/or testing requirements for the finished article, and are responsible for bringing their products to market.

This publication does not constitute any warranty, express or implied, and is intended only for the recipient and cannot therefore be transferred to any third party. We cannot assume any liability for the use of our products in conjunction with other materials.

All our products are sold subject to UPM Raflatac's general sales conditions, and you should ensure that any existing laws are observed.

This publication replaces all previous versions. All information is subject to change without notice.

