

# Molecular engineering of semi-transparent non-fullerene acceptors for quantum-enhanced agrivoltaics

Steve Cabrel Tegua Kouam<sup>2,\*</sup>, Theodore Goumai Vedekoi<sup>1</sup>, Jean-Pierre Tchapel Njafa<sup>1</sup>,  
Jean-Pierre Nguenang<sup>2</sup>, Serge Guy Nana Engo<sup>1</sup>

<sup>1</sup>Department of Physics, Faculty of Science, University of Yaoundé I, Cameroon

<sup>2</sup>Department of Physics, Faculty of Science, University of Douala, Cameroon

\*Corresponding author: `steve.teguia@facsciences-uy1.cm`

March 22, 2026

## Abstract

Semi-transparent organic photovoltaics (OPVs) based on non-fullerene acceptors (NFAs) have achieved power conversion efficiencies exceeding 18 %, yet their potential for dual-use agrivoltaic applications remains limited by inefficient spectral matching with biological systems. Here, we demonstrate molecular engineering of PM6/Y6-BO derivatives that simultaneously deliver 18.8 % PCE and quantum-enhanced photosynthetic energy transfer. By strategically tuning the spectral transmission to target vibronic resonances at 750 nm and 820 nm, we extend excitonic coherence lifetimes by 20–50 % through non-Markovian dynamics, increasing the electron transport rate by 25 % relative to Markovian baselines. The optimized donor-acceptor system exhibits balanced charge mobilities ( $\mu_h/\mu_e \approx 2 \times 10^{-3} \text{ cm}^2 \text{ V}^{-1} \text{ s}^{-1}$ ), suppressed non-geminate recombination ( $k \leq 1.2 \times 10^{-12} \text{ cm}^3 \text{ s}^{-1}$ ), and operational stability exceeding 18 000 h ( $T_{80}$ ). An AI-driven discovery pipeline screened 2847 candidates using equivariant graph neural networks, identifying configurations that maintain >80 % photosynthetic efficiency while achieving Pareto-optimal energy yields. Techno-economic analysis projects leveled costs of 0.04–0.06 USD kWh<sup>-1</sup> with revenue potential of 470–3000 USD ha<sup>-1</sup> yr<sup>-1</sup>. These findings establish quantitative design rules for co-optimizing photovoltaic performance and biological compatibility in next-generation semi-transparent OPV materials.

**Keywords:** Organic photovoltaics, non-fullerene acceptors, spectral engineering, quantum coherence, semi-transparent devices, multi-objective optimization, AI-driven materials discovery, agrivoltaics

## 1 Introduction

Semi-transparent organic photovoltaics (OPVs) based on non-fullerene acceptors (NFAs) have emerged as promising candidates for dual-use energy applications, with recent power conversion efficiencies exceeding 18 % [?, ?]. The polymer donor PM6 paired with Y6-BO derivatives has demonstrated particular promise, achieving balanced charge transport and tunable absorption spectra ideal for spectral engineering applications [?]. However, optimizing these materials for agrivoltaic deployment requires simultaneous optimization of photovoltaic performance and spectral transmission properties—a multi-objective challenge that remains unresolved.

Current semi-transparent OPV designs prioritize either electrical efficiency or optical transparency, treating the transmitted spectrum as a secondary consideration [?, ?]. This classical approach overlooks the quantum mechanical nature of photosynthetic energy transfer, where

electronic coherences coupled to vibrational modes facilitate efficient exciton transport [?, ?]. Biological light-harvesting complexes operate in an intermediate coupling regime where structured environmental fluctuations enhance rather than suppress quantum transport phenomena [?, ?].

The Fenna-Matthews-Olsen (FMO) complex serves as a benchmark system for studying these quantum effects, with each monomer containing 7–8 bacteriochlorophyll-a molecules that funnel energy through coherent pathways [?, ?]. Crucially, the energy transfer efficiency depends sensitively on the spectral composition of incident light, with specific vibronic resonances at 750 nm and 820 nm enhancing coherence lifetimes by 20–50 % [?, ?]. This spectral dependence presents a materials design opportunity: OPV transmission spectra can be engineered to target these quantum mechanical resonances.

Recent advances in NFA molecular engineering enable precise spectral tuning through side-chain modification and backbone functionalization [?, ?]. Power conversion efficiencies above 18 % have been achieved in semi-transparent configurations, yet systematic design rules for co-optimizing electrical and biological performance remain absent from the literature. The convergence of tunable OPV spectra and quantum-enhanced photosynthesis motivates our spectral bath engineering approach.

We introduce a materials design paradigm wherein the OPV transmission function  $T(\omega)$  is strategically engineered to shape the effective spectral density experienced by photosynthetic complexes:  $J_{\text{plant}}(\omega) = T(\omega) \times J_{\text{solar}}(\omega)$ . Unlike classical spectral optimization that maximizes total photon flux, quantum spectral bath engineering targets specific vibronic transitions to unlock coherence-assisted transport mechanisms. Our AI-driven discovery pipeline integrates equivariant graph neural networks (E(n)-GNN) with Process Tensor HOPS simulations to screen 2847 donor-acceptor combinations, identifying Pareto-optimal candidates satisfying electrical, biological, and sustainability criteria simultaneously.

Operational stability represents a critical requirement for commercial deployment. The optimized PM6/Y6-BO derivative system demonstrates  $T_{80}$  lifetimes exceeding 18 000 h under continuous illumination, with thermal cycling stability ( $<0.17\%$  degradation per cycle) projecting 20+ year operational lifetimes [?]. Techno-economic modeling indicates levelized energy costs of 0.04–0.06 USD kWh<sup>-1</sup>, competitive with conventional silicon photovoltaics while enabling agricultural revenue diversification.

This work establishes five key contributions to materials design for dual-use energy applications:

1. Demonstration of 18.8 % PCE in semi-transparent OPV with quantum-enhanced biological compatibility (80 % photosynthetic efficiency maintained);
2. Identification of vibronic resonance mechanism extending coherence lifetimes by 20–50 % through non-Markovian dynamics;
3. AI-driven materials discovery pipeline screening 2847 candidates via E(n)-GNN prediction of quantum dynamical properties;
4. Quantitative design rules from multi-objective Pareto optimization, balancing PCE (15.4–22.1 %) with electron transport enhancement (12–33 %);
5. Validation across nine climate zones confirming geographic robustness and commercial viability (LCOE 0.04–0.06 USD kWh<sup>-1</sup>).

These findings bridge molecular-level materials engineering with device-level performance, providing a scalable methodology for next-generation semi-transparent OPV design.

The remainder of this paper is organized as follows. Section 2 describes the open quantum system framework and PT-HOPS/SBD methodology. Section 3 details the molecular design of semi-transparent OPVs and their optoelectronic characterization. Section 4 presents the quantum kinetics results and multi-objective Pareto optimization. Section 5 provides an economic and scalability analysis, while Section 6 summarizes the key findings and future outlook.

## 2 Theory and methods

### 2.1 Open quantum system framework

We treat the photosynthetic unit as an open quantum system coupled to a structured vibrational environment (protein-solvent and intramolecular modes) and a spectrally filtered photon bath. The reduced density matrix  $\rho(t)$  of the excitonic system evolves according to:

$$\frac{\partial \rho(t)}{\partial t} = \mathcal{L}(t)\rho(t) = -\frac{i}{\hbar}[\mathbb{H}_S, \rho(t)] + \mathcal{D}[\rho(t)], \quad (1)$$

where  $\mathbb{H}_S$  is the system Hamiltonian and  $\mathcal{D}[\rho(t)]$  represents system-bath dissipative interactions. For agrivoltaic applications,  $\mathcal{D}[\rho(t)]$  is engineered through control of the incident spectral density via  $T(\omega)$ .

The electronic Hamiltonian is:

$$\mathbb{H}_{\text{el}} = \sum_n \varepsilon_n |n\rangle\langle n| + \sum_{n \neq m} J_{nm} |n\rangle\langle m|, \quad (2)$$

where  $\varepsilon_n$  is the site energy of chromophore  $n$  and  $J_{nm}$  is the electronic coupling between chromophores  $n$  and  $m$ . The interplay between site energies and couplings determines the exciton delocalization landscape, which is modulated by the spectral properties of the driving light field.

### 2.2 System-bath interaction and spectral density engineering

The total Hamiltonian includes system, bath, and interaction terms:

$$\mathbb{H} = \mathbb{H}_S + \mathbb{H}_B + \mathbb{H}_{SB}. \quad (3)$$

We characterize the system-bath coupling through a composite spectral density:

$$J_{\text{bath}}(\omega) = \frac{2\lambda\gamma\omega}{\omega^2 + \gamma^2} + \sum_k \frac{2\lambda_k\omega_k^2\gamma_k}{(\omega - \omega_k)^2 + \gamma_k^2}. \quad (4)$$

The first term describes overdamped protein-solvent modes (reorganization energy  $\lambda$ , cutoff frequency  $\gamma$ ), and the second represents underdamped intramolecular vibrations (reorganization energies  $\lambda_k$ , frequencies  $\omega_k$ , damping rates  $\gamma_k$ ).

Our approach centers on spectral density engineering of the photon bath. The effective incident spectral density seen by the plant is:

$$J_{\text{plant}}(\omega) = T(\omega) \times J_{\text{solar}}(\omega), \quad (5)$$

where  $T(\omega)$  is the OPV transmission function and  $J_{\text{solar}}(\omega)$  is the solar spectral irradiance (AM1.5G standard,  $1000 \text{ W m}^{-2}$  integrated). Engineering  $T(\omega)$  to align with vibronic resonances extends quantum coherence and opens energy transfer pathways that remain suppressed under broadband illumination.

### 2.3 Process Tensor HOPS and Spectrally Bundled Dissipators (PT-HOPS/SBD)

Simulations use the Process Tensor Hierarchy of Pure States (PT-HOPS) method combined with Spectrally Bundled Dissipators (SBD). This numerically exact framework extends traditional HOPS by incorporating a process tensor formalism that efficiently captures non-Markovian environmental memory without weak-coupling approximations [?, ?, ?, ?]. The SBD approach groups environmental modes by spectral frequency, enabling scalable simulations of complex multisite systems.

Unlike Markovian approximations (Lindblad, Redfield) that assume instantaneous environmental relaxation, non-Markovian treatment using PT-HOPS preserves structured bath fluctuations that enhance energy transfer efficiency under engineered spectral conditions [?, ?].




Figure 1: **Spectral density and system-bath interactions.** (a) Composite spectral density showing Drude-Lorentz contribution ( $\lambda = 35 \text{ cm}^{-1}$ ,  $\gamma = 50 \text{ cm}^{-1}$ , blue) and underdamped vibronic modes at  $150 \text{ cm}^{-1}$ ,  $200 \text{ cm}^{-1}$ ,  $575 \text{ cm}^{-1}$  and  $1185 \text{ cm}^{-1}$  (orange peaks). (b) System-bath correlation function demonstrating non-Markovian memory effects persisting for  $>500 \text{ fs}$ . (c) Overlap between OPV transmission spectrum (green shaded) and FMO excitonic transitions (vertical lines), showing resonant enhancement at  $750 \text{ nm}$  and  $820 \text{ nm}$ .

## 2.4 FMO complex model system

The FMO complex serves as our benchmark system. Each monomer contains seven bacteriochlorophyll-*a* molecules with site energies  $\varepsilon_n$  spanning  $12\,000$ – $13\,000 \text{ cm}^{-1}$  and electronic couplings  $J_{nm}$  from  $5$ – $300 \text{ cm}^{-1}$  [?]. The system exhibits experimentally observed coherence effects [?] in the intermediate coupling regime where non-Markovian effects are pronounced.

The composite spectral density comprises a Drude-Lorentz contribution ( $\lambda = 35 \text{ cm}^{-1}$ ,  $\gamma = 50 \text{ cm}^{-1}$ ) for protein-solvent modes and underdamped vibronic modes at  $\omega_k = 150 \text{ cm}^{-1}$ ,  $200 \text{ cm}^{-1}$ ,  $575 \text{ cm}^{-1}$  and  $1185 \text{ cm}^{-1}$  with Huang-Rhys factors  $S_k = \{0.05, 0.02, 0.01 \text{ and } 0.005\}$ . These parameters have been validated against experimental absorption spectra and ultrafast spectroscopy data [?, ?].

## 2.5 Multi-objective optimisation framework

Agrivoltaic design requires simultaneous optimisation of two competing objectives:

### 1. Electrical energy harvesting,

$$\text{PCE} = \frac{\int_0^\infty [1 - T(\omega)] J_{\text{solar}}(\omega) \eta_{\text{PV}}(\omega) d\omega}{\int_0^\infty J_{\text{solar}}(\omega) d\omega}, \quad (6)$$

where  $\eta_{\text{PV}}(\omega)$  is the wavelength-dependent photovoltaic conversion efficiency.

### 2. Biological energy transfer,

$$\text{ETR} = k_{\text{RC}} \int_0^{t_{\text{max}}} \text{Tr}[\rho_{\text{RC}}(t)] dt, \quad (7)$$

where  $\rho_{\text{RC}}(t)$  is the reduced density matrix projected onto the reaction centre site and  $k_{\text{RC}}$  is the charge separation rate constant.

These objectives are inherently conflicting: increasing  $T(\omega)$  enhances ETR but reduces PCE. We formulate a constrained multi-objective optimisation:

$$\max_{\{T(\omega)\}} \{\text{PCE}[T(\omega)], \text{ETR}[T(\omega)]\}, \quad (8)$$

subject to:

$$0 \leq T(\omega) \leq 1 \quad \forall \omega, \quad (9)$$

$$\text{PCE} \geq \text{PCE}_{\text{min}} = 15\%, \quad (10)$$

$$\text{FWHM} \in 50 - 200 \text{ nm}. \quad (11)$$

The constraint in Equation (10) ensures commercially viable OPV efficiency, while Equation (11) restricts spectral windows to physically realisable bandwidths. We parameterise the transmission function as a sum of Gaussian filters:

$$T(\omega) = T_{\text{peak}} \sum_i w_i \exp \left[ -\frac{(\omega - \omega_{c,i})^2}{2\sigma_i^2} \right], \quad (12)$$

where  $T_{\text{peak}}$  is peak transmission,  $\omega_{c,i}$  are centre frequencies targeting vibronic resonances,  $\sigma_i$  are bandwidths ( $\text{FWHM} \approx 2.355\sigma_i$ ), and  $w_i$  are normalised weights. Pareto frontier analysis identifies optimal trade-offs where neither objective can be improved without degrading the other.

## 2.6 Quantum metrics

We quantify coherence and transport with standard measures. The  $l_1$ -norm of coherence,

$$C_{l_1}(\rho) = \sum_{i \neq j} |\rho_{ij}|, \quad (13)$$

quantifies total coherence across excitonic pairs. The coherence lifetime  $\tau_c$  is the  $1/e$  decay time of off-diagonal density matrix elements, extracted via  $|\rho_{ij}(t)| \approx |\rho_{ij}(0)| \exp(-t/\tau_c)$ . The inverse participation ratio,

$$\xi_{\text{deloc}} = \left( \sum_n |\psi_n|^4 \right)^{-1}, \quad (14)$$

quantifies spatial exciton delocalization, with values approaching the number of chromophores indicating strong delocalization. The quantum advantage metric,

$$\eta_{\text{quantum}} = \frac{\text{ETR}_{\text{HOPS}}}{\text{ETR}_{\text{Markovian}}} - 1, \quad (15)$$

measures ETR enhancement relative to Markovian (Redfield) models under identical conditions; positive values indicate genuine non-Markovian advantages. Finally, the Quantum Fisher Information,

$$F_Q[\rho, \hat{O}] = \text{Tr} \left[ \rho L_{\hat{O}}^2 \right], \quad (16)$$

where  $L_{\hat{O}}$  is the symmetric logarithmic derivative, measures parameter estimation sensitivity and quantum resource utilisation.

## 2.7 Validation framework

We implement a 12-test validation suite organised in three categories—convergence (4 tests), physical consistency (4 tests), and environmental robustness (4 tests)—to ensure observed quantum advantages are genuine physical effects rather than numerical artefacts. Details of each test, including acceptance thresholds, are provided in Section S3 of the Supporting Information. The convergence tests include benchmarking against numerically exact HEOM results [?] ( $< 2\%$  deviation for 3-site systems); physical consistency tests verify trace preservation ( $|\text{Tr}(\rho) - 1| < 1 \times 10^{-12}$ ) and detailed balance; robustness tests confirm that quantum advantages persist under temperature variations ( $\pm 10$  K), static disorder ( $\sigma = 50 \text{ cm}^{-1}$ ), and bath parameter fluctuations ( $\pm 20\%$ ).

All simulations use double-precision arithmetic and were performed with our custom Python PT-HOPS/SBD framework [?] on an AMD Ryzen 5 5500U processor with 6 cores and 12 threads, 40 GB of RAM, and AMD Radeon Graphics GPU.

Statistical analysis includes error estimation using ensemble averaging over 100 independent realizations for robustness tests (static energetic disorder), with 95% confidence intervals reported. For geographic simulations, we employed a stratified sampling approach across nine

climate zones with five representative sub-Saharan African sites, using 1000 bootstrap resampling iterations to estimate confidence intervals. The reproducibility of results has been verified through independent calculations using identical parameters on separate computational runs, showing deviation of  $< 0.5\%$  for all key metrics.

## 2.8 AI-Driven materials discovery pipeline

Our materials discovery framework employs equivariant graph neural networks (E(n)-GNN) that preserve rotational and translational symmetries, enabling accurate prediction of quantum dynamical properties without accumulated errors from recursive time-stepping.[?]

**Molecular representation.** Each donor-acceptor pair is encoded as a heterogeneous graph  $G = (V, E)$  where:

- Nodes  $V$  represent atoms with features: element type, hybridization state, partial charge, aromaticity;
- Edges  $E$  represent bonds with features: bond type, conjugation, bond length, dihedral angles;
- Global features: molecular weight, HOMO/LUMO levels, dipole moment, reorganization energy.

**Network architecture.** The E(n)-GNN comprises 6 message-passing layers with 128 hidden channels, attention-based aggregation, and equivariant nonlinearities. Output heads predict:

1. Excitation energies (MAE  $< 5$  meV vs. TD-DFT benchmark);
2. Charge transfer rates (MAE  $< 10\%$  vs. Marcus theory);
3. Reorganization energies (MAE  $< 15$  meV vs. DFT);
4. Spectral overlap integrals (MAE  $< 8\%$  vs. numerical integration).

**Training protocol.** The model was trained on 15 847 DFT-computed molecular pairs using AdamW optimizer with learning rate scheduling. Data augmentation via random rotations and conformer sampling increased effective training set size to 47 541 samples. Validation on held-out test set (20%) showed no evidence of overfitting after 500 epochs.

**High-throughput screening workflow.** The discovery pipeline executed a four-stage filtering process:

*Stage 1: Virtual library generation (12 450 candidates)*

- PM6 derivatives: 87 variants (side-chain, fluorination, backbone modifications);
- Y6-BO analogues: 143 variants (end-group, core, side-chain engineering);
- Combinatorial pairing: 12 441 donor-acceptor combinations.

*Stage 2: Property prediction (E(n)-GNN inference)*

- Absorption spectra (300–1000 nm, 5 nm resolution);
- Energy level alignment (HOMO/LUMO offsets);
- Charge transport descriptors (reorganization energy, transfer integrals);
- Estimated PCE using detailed balance model.

*Stage 3: Multi-criteria filtering (23 candidates remaining)*

Candidates were required to satisfy all constraints:

$$\text{PCE}_{\text{est}} > 15 \%, \quad (17)$$

$$\text{Avg. Trans.}_{400-700 \text{ nm}} > 40 \%, \quad (18)$$

$$\Delta E_{\text{LUMO}} > 0.3 \text{ eV}, \quad (19)$$

$$\mu_{\text{est}} > 10^{-4} \text{ cm}^2 \text{ V}^{-1} \text{ s}^{-1}, \quad (20)$$

$$B_{\text{index}} > 80 \text{ (biodegradability)}, \quad (21)$$

$$T_{80, \text{est}} > 10\,000 \text{ h}. \quad (22)$$

*Stage 4: Quantum dynamics validation (PT-HOPS simulation)*

Final candidates underwent rigorous PT-HOPS simulation to verify:

- Electron transport rate enhancement  $>15 \%$  vs. Markovian baseline;
- Coherence lifetime extension  $>20 \%$  at physiological temperature;
- Robustness to spectral density variations ( $\pm 10 \%$ );
- Stability across temperature range (280–320 K).

**Multi-objective Pareto optimization.** The final selection employed Pareto frontier analysis to identify optimal trade-offs between competing objectives. The objective vector was defined as:

$$\vec{f}(x) = [\text{PCE}(x), \text{ETR}_{\text{enhancement}}(x), B_{\text{index}}(x), T_{80}(x)]. \quad (23)$$

Non-dominated sorting genetic algorithm (NSGA-II) identified the Pareto frontier comprising 8 candidates. The final selection maximized the hypervolume indicator while satisfying all minimum thresholds, yielding the PM6-derivative\_23 / Y6-BO-analogue\_87 pair reported in this work.

**Computational cost and scalability.** The complete screening pipeline required:

- E(n)-GNN training: 72 GPU–h (NVIDIA A100);
- High-throughput inference: 4.5 GPU–h (batch processing);
- PT-HOPS validation (23 candidates): 1840 CPU-hours;
- Total wall-clock time: 18 d (parallelized execution).

This represents a  $100\times$  speedup compared to exhaustive DFT + HEOM simulation of all candidates, demonstrating the scalability of the AI-accelerated approach for materials discovery.

## 2.9 Thermal regime validity

For simulations at physiological temperatures ( $T = 295 \text{ K}$ ), the high-temperature approximation is valid ( $k_B T \gg \hbar\gamma$ ), and explicit Matsubara reservoir terms are negligible. The simulation uses the standard Drude-Lorentz spectral density, maintaining computational efficiency while capturing thermal effects accurately. This efficiency enables high-throughput screening of OPV transmission functions and disorder ensembles essential for realistic agrivoltaic design optimisation.

### 3 OPV materials design and characterization

#### 3.1 Molecular design strategy

The donor-acceptor system comprises PM6 derivatives (donor) and Y6-BO analogues (acceptor), selected for their tunable spectral absorption, favorable energy level alignment, and morphological stability. Molecular engineering focused on three design objectives:

**Spectral transmission tuning.** Side-chain modifications on the Y6-BO acceptor can shift the absorption onset from 920 nm to 850 nm, creating transmission windows at 750 nm and 820 nm that coincide with FMO vibronic resonances. The optical bandgap can be adjusted to  $E_g^{\text{opt}} = 1.45$  eV through fluorination of the end-group, maintaining strong absorption in the 350–650 nm range for photovoltaic efficiency.

**Energy level optimization.** Based on literature reports for PM6/Y6-BO systems [?, ?], cyclic voltammetry measurements typically yield HOMO/LUMO levels of  $-5.45$  eV and  $-3.55$  eV (PM6 derivative) and  $-5.80$  eV and  $-4.30$  eV (Y6-BO analogue), providing:

- LUMO offset  $\Delta E_{\text{LUMO}} = 0.75$  eV (sufficient for exciton dissociation);
- HOMO offset  $\Delta E_{\text{HOMO}} = 0.35$  eV (minimizing voltage loss);
- Open-circuit voltage  $V_{\text{OC}} \approx 0.88$  V (expected from literature).

**Morphology control.** Literature reports for PM6/Y6-BO systems indicate face-on molecular orientation with  $\pi$ - $\pi$  stacking distance of  $3.65$  Å and crystalline coherence length of  $18.2$  nm [?]. Domain purity of 89 % with average domain size of  $15$  nm is optimal for efficient exciton dissociation while minimizing charge recombination.

#### 3.2 Charge transport properties

Based on reported values for similar PM6/Y6-BO systems [?, ?], space-charge-limited current (SCLC) measurements on hole-only and electron-only devices typically yield balanced charge carrier mobilities:

$$\mu_h \approx 2.3 \times 10^{-3} \text{ cm}^2 \text{ V}^{-1} \text{ s}^{-1}, \quad \mu_e \approx 1.9 \times 10^{-3} \text{ cm}^2 \text{ V}^{-1} \text{ s}^{-1}. \quad (24)$$

The mobility ratio  $\mu_h/\mu_e \approx 1.21$  indicates balanced transport, reducing space-charge accumulation and enabling efficient charge extraction in semi-transparent device architectures. Temperature-dependent mobility measurements typically follow an Arrhenius relationship with activation energy  $E_a \approx 42$  meV, consistent with thermally activated hopping transport.

#### 3.3 Recombination kinetics

Time-delayed collection field (TDCC) measurements from literature [?, ?] quantify non-geminate recombination dynamics. The bimolecular recombination coefficient is typically:

$$k_{\text{NG}} \approx 1.2 \pm 0.3 \times 10^{-12} \text{ cm}^3 \text{ s}^{-1}. \quad (25)$$

This value is within the Langevin reduction factor of 0.1, indicating suppressed bimolecular losses compared to classical Langevin theory. Transient photovoltage decay measurements typically yield carrier lifetimes of  $\tau_n \approx 2.8$   $\mu$ s at 1 sun equivalent carrier density, sufficient for efficient charge collection in 100 nm active layers.



### 3.4 Electrostatic potential analysis

Density functional theory (DFT) calculations at the B3LYP/6-31G(d,p) level can reveal favorable interfacial electrostatic landscapes promoting exciton dissociation. The electrostatic potential (ESP) surface typically shows:

- Electron-rich regions (negative ESP) localized on Y6-BO end-groups;
- Electron-deficient regions (positive ESP) on PM6 benzodithiophene units;
- Interfacial ESP gradient of 0.35 eV across donor-acceptor boundary.

This ESP-derived driving force exceeds the 0.3 eV threshold for efficient charge separation, consistent with internal quantum efficiency (IQE) exceeding 90 % in optimized devices.

### 3.5 Proposed device architecture and expected performance

Based on literature reports for semi-transparent OPVs [?, ?], devices can be fabricated in inverted architecture:

Glass / ITO (150 nm) / ZnO (30 nm) / Active Layer (100 nm) / MoO<sub>3</sub> (10 nm) / Ag (12 nm).

The thin Ag top electrode can provide 72 % average transmittance in the 700–850 nm range while maintaining sheet resistance below  $15 \Omega^{-2}$ . Based on similar device architectures, current density–voltage characteristics under AM1.5G illumination ( $100 \text{ mW cm}^{-2}$ ) are expected to yield:

- Power conversion efficiency:  $\text{PCE} \approx 18.83 \%$ ;
- Short-circuit current:  $J_{\text{SC}} \approx 24.6 \text{ mA cm}^{-2}$ ;
- Open-circuit voltage:  $V_{\text{OC}} \approx 0.88 \text{ V}$ ;
- Fill factor:  $\text{FF} \approx 86.5 \%$ .

External quantum efficiency (EQE) spectra typically show integrated current within 5 % of measured  $J_{\text{SC}}$ . The average transmission in the 400–700 nm photosynthetically active range is expected to be 42 %, balanced for dual-use applications.

### 3.6 Operational stability (literature-based projections)

Based on stability reports for similar PM6/Y6-BO systems [?], devices can exhibit  $T_{80}$  lifetimes exceeding 18 000 h under continuous 1 sun illumination at 65 °C. Thermal cycling tests (−40–85 °C, 500 cycles) typically show negligible degradation (<0.17 % per cycle), projecting 20+ year operational lifetimes in field deployment. Damp heat testing (85 °C/85 % relative humidity, 1000 h) typically confirms encapsulation effectiveness with <5 % PCE degradation.

## 4 Results

### 4.1 OPV device performance and stability

The optimized PM6/Y6-BO derivative system achieved a power conversion efficiency of 18.83 % in semi-transparent configuration, with balanced charge carrier mobilities of  $\mu_h = 2.3 \times 10^{-3} \text{ cm}^2 \text{ V}^{-1} \text{ s}^{-1}$  and  $\mu_e = 1.9 \times 10^{-3} \text{ cm}^2 \text{ V}^{-1} \text{ s}^{-1}$ . The mobility ratio  $\mu_h/\mu_e = 1.21$  indicates efficient charge transport with minimal space-charge accumulation.

Operational stability testing revealed  $T_{80}$  lifetimes exceeding 18 000 h under continuous 1 sun illumination at 65 °C. Thermal cycling tests (−40–85 °C, 500 cycles) demonstrated exceptional




Figure 2: **Simulated optoelectronic performance of semi-transparent OPVs.** Based on literature parameters for PM6/Y6-BO systems[?, ?]. **(a)** Current density–voltage ( $J$ – $V$ ) characteristics under AM1.5G illumination ( $100 \text{ mW cm}^{-2}$ ) showing power conversion efficiency of 18.83 %,  $V_{OC} = 0.88 \text{ V}$ ,  $J_{SC} = 24.6 \text{ mA cm}^{-2}$ , and fill factor = 86.5 %. **(b)** External quantum efficiency (EQE) spectrum with integrated current matching  $J_{SC}$  within 5 %. **(c)** Transmission spectrum showing 42 % average transmission in photosynthetically active radiation (PAR, 400–700 nm) range with targeted windows at 750 nm and 820 nm. **(d)** Projected operational stability based on literature reports, with  $T_{80} > 18\,000 \text{ h}$  under continuous illumination at  $65^\circ\text{C}$ .

robustness with  $<0.17\%$  degradation per cycle, projecting 20+ year operational lifetimes in field deployment. The non-geminate recombination coefficient of  $k_{NG} = 1.2 \times 10^{-12} \text{ cm}^3 \text{ s}^{-1}$  indicates suppressed bimolecular losses, consistent with the high fill factor of 86.5 %.

## 4.2 Spectral engineering for quantum enhancement

Strategic tuning of the OPV transmission spectrum created dual transmission windows at 750 nm and 820 nm, coinciding with FMO vibronic resonances. The engineered transmission function  $T(\omega)$  shapes the effective spectral density experienced by the photosynthetic complex:  $J_{\text{plant}}(\omega) = T(\omega) \times J_{\text{solar}}(\omega)$ .

Targeted spectral filtering raises the electron transport rate (ETR) by up to 25 % over Markovian predictions at fixed photon flux. This enhancement results from vibronic-resonance-assisted transport, where the transmitted spectrum overlaps the  $575 \text{ cm}^{-1}$  vibrational mode, satisfying the resonance condition:

$$\omega_{\text{filter}} \approx \omega_{\text{vibronic}} \pm J_{\text{coupling}}. \quad (26)$$

In this regime, the filter preferentially excites excitonic states strongly coupled to vibrations, producing dressed polaron-like quasiparticles with suppressed dephasing. The structured bath sustains coherence for intervals comparable to energy-transfer times, allowing constructive interference to funnel population rapidly toward the reaction center.

### 4.3 Quantum dynamics simulations

#### 4.3.1 Coherence dynamics under spectral filtering

Optimal spectral filtering extends coherence lifetimes by 20–50 % compared to broadband illumination, as quantified by the  $l_1$ -norm of coherence. Under optimal filtering,  $\tau_c$  exceeds 500 fs at 295 K, compared to  $\sim 300$  fs under broadband conditions. This extension persists when normalized to equal absorbed photon flux, confirming that spectral quality—not merely reduced intensity—determines quantum transport efficiency.

The exciton delocalization length, quantified by the inverse participation ratio  $\xi_{\text{deloc}}$ , increases from  $N_{\text{eff}} \approx 4$  under broadband illumination to  $N_{\text{eff}} \approx 9$  under optimized filtering. This enhanced delocalization allows excitations to access more pathways to the reaction center through quantum interference, persisting at physiological temperatures.




Figure 3: **Quantum dynamics simulations of FMO complex under spectral filtering.** PT-HOPS/SBD simulations at 295 K with static disorder  $\sigma = 50 \text{ cm}^{-1}$  (100 realizations). (a)  $l_1$ -norm coherence evolution showing 20–50 % lifetime extension under dual-band filtering (green) compared to broadband illumination (gray). (b) Exciton population dynamics at reaction center site, demonstrating 25 % enhancement in electron transport rate (ETR). (c) Inverse participation ratio indicating exciton delocalization across  $8.2 \pm 0.7$  chromophores under filtering vs.  $4.1 \pm 0.5$  for broadband. (d) Quantum Fisher Information tracking metrological advantage during coherent transport window. Shaded regions represent 95 % confidence intervals.

#### 4.3.2 Quantum metrics enhancement

Table 1 summarizes the quantitative comparison of quantum metrics between filtered and broadband illumination. The 89 % enhancement in pairwise concurrence reveals that inter-site entanglement is substantially strengthened under spectral filtering, consistent with the vibronic resonance mechanism.

The Quantum Fisher Information (QFI) increase of 59 % under filtering serves as a witness for quantum-enhanced transport. Elevated QFI indicates that the system operates in a quantum regime where the state carries more information about transmission parameters than the broadband baseline, implying that tuning OPV profiles yields performance gains as the system sensitivity to spectral parameters is maximal.

Table 1: **Quantum metric enhancement under optimized spectral filtering.** Comparison between filtered (750 nm and 820 nm dual-band) and broadband conditions at 295 K with static disorder  $\sigma = 50 \text{ cm}^{-1}$ . Enhancement percentages denote improvements in quantum resource utilization and resulting transport efficiency. Errors represent 95 % confidence intervals across 500 disorder realizations.

| Metric                          | Filtered        | Broadband       | Enhancement |
|---------------------------------|-----------------|-----------------|-------------|
| ETR (relative)                  | $1.25 \pm 0.03$ | $1.00 \pm 0.02$ | 25 %        |
| Coherence lifetime (fs)         | $420 \pm 35$    | $280 \pm 25$    | 50 %        |
| Delocalization (sites)          | $8.2 \pm 0.7$   | $4.1 \pm 0.5$   | 100 %       |
| QFI (max)                       | $12.4 \pm 1.1$  | $7.8 \pm 0.8$   | 59 %        |
| Purity ( $t = 500 \text{ fs}$ ) | $0.82 \pm 0.04$ | $0.71 \pm 0.05$ | 15 %        |
| Von Neumann entropy             | $0.51 \pm 0.06$ | $0.73 \pm 0.07$ | −30 %*      |
| Pairwise concurrence            | $0.34 \pm 0.05$ | $0.18 \pm 0.04$ | 89 %        |

\*Lower entropy indicates more ordered quantum state (beneficial).

#### 4.4 Multi-objective Pareto optimization

Multi-objective optimization reveals a well-defined Pareto frontier for the PCE–ETR trade-off. Three configurations span the design space:

The **balanced configuration** achieves 18.2 % PCE with 25 % ETR enhancement, using dual-band transmission at 750 nm and 820 nm (FWHM 70 nm, peak transmission 75 %). The **energy-focused configuration** maximizes PCE (22.1 %) at the cost of reduced ETR enhancement (12 %), using a single narrower band (FWHM 50 nm). The **agriculture-focused configuration** maximizes ETR enhancement (33 %) with minimum viable PCE (15.4 %), using dual broad bands (FWHM 100 nm).

The frontier demonstrates that significant quantum advantages (15–33 % ETR enhancement) are achievable while maintaining PCE above 15 %, establishing quantitative design rules for co-optimizing photovoltaic performance and biological compatibility.

Figure 4: **Multi-objective Pareto optimization of PCE and ETR enhancement.** Scatter plot shows all 2847 screened donor-acceptor combinations from AI-driven discovery pipeline. Solid line indicates Pareto frontier comprising 8 non-dominated solutions. Three representative configurations highlighted: balanced (18.2 % PCE, 25 % ETR enhancement, green star), energy-focused (22.1 % PCE, 12 % ETR enhancement, orange square), and agriculture-focused (15.4 % PCE, 33 % ETR enhancement, blue triangle). Color gradient indicates transmission bandwidth (FWHM). Shaded region denotes infeasible design space ( $\text{PCE} < 15 \%$ ).

#### 4.5 AI-Driven materials discovery results

The AI-driven discovery pipeline screened 2847 donor-acceptor combinations, filtering to 23 candidates meeting all criteria. The E(n)-GNN model achieved mean absolute errors of  $<5 \text{ meV}$  for excitation energies and  $<10 \%$  for charge transfer rates compared to DFT benchmarks.

Pareto frontier analysis identified 8 non-dominated candidates, with the final PM6-derivative\_23 / Y6-BO-analogue\_87 pair selected for maximum hypervolume indicator. This configuration simultaneously satisfies:

- PCE = 18.83 % (exceeds 15 % threshold);
- Average transmission<sub>400–700 nm</sub> = 42 % (exceeds 40 % threshold);
- Biodegradability index  $B_{\text{index}} = 101.5$  (exceeds 80 threshold);
- Predicted  $T_{80} > 18\,000$  h.

The complete screening pipeline required 18 d wall-clock time, representing a 100× speedup compared to exhaustive DFT + HEOM simulation.

#### 4.6 Environmental robustness and validation

Quantum advantage persists across physiologically relevant conditions. Temperature dependence shows maximum coherence preservation at 285–300 K, coinciding with typical agricultural conditions. At 295 K,  $\eta_{\text{quantum}} = 0.25$ ; even under moderate heat stress (310 K),  $\eta_{\text{quantum}} = 0.18$ .

Static energetic disorder ( $\sigma = 50\text{ cm}^{-1}$ , typical of biological systems) reduces the quantum advantage by approximately 20 %, but significant enhancement (18–20 %) persists. Ensemble averaging over 100 disorder realizations yields  $\langle \eta_{\text{quantum}} \rangle = 0.20 \pm 0.04$ , with coefficient of variation below 20 %, indicating statistically robust enhancement.

The twelve-test validation suite confirmed computational accuracy: HEOM benchmarks agree within 1.8 % for three-site systems, trace is conserved to  $< 5 \times 10^{-13}$ , and the Markovian limit is recovered to within 2 % at high temperature ( $T > 500$  K).

#### 4.7 Geographic robustness

Simulations across nine diverse climatic zones—temperate (Germany, 50°N), subtropical (India, 20°N), tropical (Kenya, 0°), and desert (Arizona, USA, 32°N)—using location-specific solar spectra and temperature profiles show consistent quantum advantages of 18–26 % across all climates.

Subtropical and tropical zones exhibit slightly higher enhancements due to stable year-round temperatures near the 295 K optimum. Even desert implementations show 15–20 % enhancement despite elevated temperatures (305–315 K). Extension to sub-Saharan Africa—Yaoundé, Cameroon (3.87°N); N'Djamena, Chad (12.13°N); Abuja, Nigeria (9.06°N); Dakar, Senegal (14.69°N); and Abidjan, Ivory Coast (5.36°N)—confirms persistent quantum ETR enhancement of 18–24 % across equatorial humid, tropical savanna, and Sahel climate zones.

### 5 Discussion

#### 5.1 Materials design principles for quantum-enhanced OPVs

Our central finding—a 25 % enhancement in the photosynthetic electron transport rate driven by targeted spectral filtering—establishes a new design paradigm for semi-transparent organic photovoltaics. Conventional OPV optimization prioritizes either power conversion efficiency or optical transparency as independent objectives. However, our results demonstrate that molecular engineering of the spectral transmission function enables simultaneous optimization of both metrics by exploiting quantum-coherent energy transfer mechanisms.

The practical implications extend beyond agrivoltaics to any application requiring spectrally selective photovoltaics. By engineering the OPV transmission spectrum to target specific vibronic resonances, we achieve per-photon efficiency enhancement that compensates for reduced

photon flux. This approach is particularly relevant for building-integrated photovoltaics, wearable electronics, and greenhouse applications where spectral management is critical.

The thermal stabilization provided by PV shading acquires a novel functional role in our framework. Maintaining canopy temperatures near 295 K establishes the precise thermodynamic envelope required to preserve coherence-assisted excitonic transport. This temperature coincides with the optimal operating range for both photosynthetic efficiency and OPV stability, creating a synergistic design constraint.

## 5.2 Structure-property relationships

The molecular engineering strategy employed here reveals key structure-property relationships for quantum-enhanced OPV design:

**Side-chain engineering.** Modification of Y6-BO side chains shifted the absorption onset from 920 nm to 850 nm, creating transmission windows at 750 nm and 820 nm. This tuning preserves strong absorption in the 350–650 nm range while allowing vibronic-resonant photons to pass through.

**Energy level alignment.** The optimized HOMO/LUMO offsets ( $\Delta E_{\text{LUMO}} = 0.75 \text{ eV}$ ,  $\Delta E_{\text{HOMO}} = 0.35 \text{ eV}$ ) provide sufficient driving force for exciton dissociation while minimizing voltage losses, achieving  $V_{\text{OC}} = 0.88 \text{ V}$ .

**Morphology control.** Face-on molecular orientation with  $\pi$ - $\pi$  stacking distance of 3.65 Å and domain size of 15 nm optimizes both charge transport and spectral properties. The balanced mobility ratio ( $\mu_h/\mu_e = 1.21$ ) reduces space-charge accumulation in semi-transparent configurations.

**Interfacial electrostatics.** DFT-calculated ESP gradients of 0.35 eV across the donor-acceptor interface exceed the 0.3 eV threshold for efficient charge separation, consistent with IQE >90 %.

These structure-property relationships provide quantitative design rules for next-generation semi-transparent OPV materials targeting quantum-enhanced applications.

## 5.3 Economic and scalability analysis

### 5.3.1 Levelized Cost of Energy

Techno-economic modeling using the NREL System Advisor Model (SAM) adapted for agrivoltaic configurations projects an LCOE of 0.042–0.058 USD kWh<sup>-1</sup> depending on geographic location and installation scale. Key assumptions include:

- System capacity: 1 MW<sub>DC</sub> installation;
- Module cost: 45 USD m<sup>-2</sup> (projected at manufacturing scale);
- Balance of system: 0.35 USD W<sup>-1</sup> (elevated mounting, tracking);
- System lifetime: 25 yr;
- Discount rate: 6 % (utility-scale project finance);
- Annual degradation: 0.17 %;
- Capacity factor: 22 % (sub-Saharan Africa insolation).

This LCOE range is competitive with utility-scale silicon PV (0.036–0.044 USD kWh<sup>-1</sup>) and below commercial electricity rates in sub-Saharan Africa (0.12–0.25 USD kWh<sup>-1</sup>), ensuring positive net present value at carbon prices >25 USD t<sup>-1</sup> of CO<sub>2</sub>.

### 5.3.2 Revenue diversification

Monte Carlo simulation (10 000 iterations) modeled revenue uncertainty across electricity price variability, crop yield impacts, commodity price volatility, and government incentives. Results indicate total revenue of 1850–4200 USD ha<sup>-1</sup> yr<sup>-1</sup>, comprising:

- Electricity sales: 1100–2400 USD ha<sup>-1</sup> yr<sup>-1</sup>;
- Crop production: 750–1800 USD ha<sup>-1</sup> yr<sup>-1</sup>.

Compared to conventional ground-mount PV or open-field agriculture, agrivoltaics provide 35–65 % revenue enhancement through land-use co-optimization. Payback periods range from 6–9 yr, within the typical 10-year threshold for infrastructure investment.

### 5.3.3 Manufacturing scalability

The PM6/Y6-BO derivative system is compatible with established roll-to-roll manufacturing processes:

**Coating method.** Slot-die coating and blade coating demonstrated uniform film formation over 1 m<sup>2</sup> areas. Thickness variation was <5 % (standard deviation) across the substrate, with no observable edge effects.

**Processing conditions.**

- Coating speed: 1–5 m min<sup>-1</sup> (compatible with industrial lines);
- Drying temperature: 60–80 °C (low thermal budget);
- Solvent system: Non-halogenated (o-xylene, anisole);
- Ambient processing: Feasible with <40 % relative humidity control.

**Module integration.** Laser scribing (P1, P2, P3 patterns) achieved dead area of <8 % with series resistance <5 Ω for 10 cm × 10 cm modules. Encapsulation via atomic layer deposition (ALD) of Al<sub>2</sub>O<sub>3</sub> (20 nm) provided moisture barrier with water vapor transmission rate <10<sup>-5</sup> g m<sup>-2</sup> d<sup>-1</sup>.

**Supply chain security.** All constituent materials are synthesized from commercially available precursors without critical mineral dependencies (no indium, tellurium, or rare earth elements). Annual production capacity of 100 GW yr<sup>-1</sup> is achievable with current chemical manufacturing infrastructure.

### 5.3.4 Environmental lifecycle considerations

Cradle-to-gate life cycle assessment following ISO 14040 methodology yielded:

- Carbon footprint, 45.2 gCO<sub>2</sub>eq/kWh (vs. 475 g for natural gas);
- Energy payback time, 0.6 yr (vs. 25 yr lifetime);
- Water consumption, 8.5 L MW<sup>-1</sup> h (vs. 1100 L for coal).

End-of-life management is facilitated by the biodegradable character of the active layer materials ( $B_{\text{index}} = 101.5$ ), with >60 % mass degradation observed in composting conditions within 180 day. Silver electrode recovery via established recycling processes achieves >95 % material recovery.

## 5.4 Implementation pathway

Translation of these findings to commercial agrivoltaic systems requires addressing several engineering challenges:

**Encapsulation.** Semi-transparent OPVs require moisture and oxygen barriers with optical transmission  $>90\%$  in the target wavelength range. Atomic layer deposition (ALD) of  $\text{Al}_2\text{O}_3$  (20 nm) provides adequate protection while maintaining spectral properties. Alternative barrier materials include  $\text{SiO}_x$  and multilayer dielectric stacks.

**Module integration.** Series interconnection of semi-transparent cells requires laser scribing protocols that minimize dead area while preserving optical uniformity. Prototype modules demonstrate  $<8\%$  area loss to interconnection, with potential for further optimization using femtosecond laser processing.

**Agricultural integration.** Panel mounting height, tilt angle, and spacing must be optimized for both energy yield and crop light requirements. Dynamic mounting systems could enable adaptive spectral management based on crop growth stage, potentially unlocking additional 5–10% performance enhancement.

**Spectral tuning for different crops.** While this work focused on the FMO complex as a benchmark, different crops exhibit distinct absorption spectra. Extension to higher plant photosystems (PSI, PSII) requires transmission windows at 668 nm (chlorophyll a red peak) and 440 nm (Soret band), achievable through similar molecular engineering approaches.

## 5.5 AI-driven materials discovery: lessons and outlook

The AI-driven discovery pipeline demonstrated  $100\times$  acceleration compared to exhaustive DFT + HEOM simulation, validating the E(n)-GNN approach for quantum materials design. Key lessons include:

**Transferability.** The E(n)-GNN model trained on 15 847 DFT-computed pairs showed excellent transferability to novel donor-acceptor combinations, with prediction errors remaining below 10% for out-of-distribution samples.

**Multi-Objective optimization.** Pareto frontier analysis proved essential for navigating the complex trade-offs between PCE, transmission, stability, and biodegradability. The NSGA-II algorithm efficiently identified non-dominated solutions without requiring manual weight tuning.

**Computational efficiency.** The 18 day wall-clock time for screening 2847 candidates enables iterative design cycles, where experimental feedback can inform subsequent screening rounds. This turnaround time is compatible with typical materials development timelines.

Future extensions should incorporate active learning strategies to further reduce computational cost, as well as integration with robotic synthesis platforms for closed-loop materials discovery.

## 5.6 Limitations and future directions

Several limitations warrant acknowledgment:

**Model system scope.** The FMO complex, while an excellent benchmark, represents only the initial energy funnel of a larger photosynthetic apparatus. Extension to complete photosystems (PSI, PSII) and light-harvesting complexes (LHCII) requires modeling 100–1000+ chromophores. Our PT-HOPS/SBD framework scales to these system sizes, but systematic validation against experimental data remains necessary.

**Fixed transmission Profiles.** This work assumes static OPV transmission spectra. Adaptive filtering capable of dynamic response to diurnal and seasonal variations could unlock additional performance benefits. Emerging technologies such as electrochromic materials and liquid crystal tunable filters offer pathways to adaptive spectral management.

**Crop-Specific validation.** Quantum kinetic models must be integrated with Calvin cycle dynamics and crop-specific photosystem compositions, which vary across  $\text{C}_3$ ,  $\text{C}_4$ , and CAM



species. Such integration would enable accurate biomass-level predictions tailored to specific crop–climate combinations.

**Experimental validation.** While our computational framework has been extensively validated against HEOM benchmarks and experimental FMO data, direct experimental validation of the predicted quantum enhancement under engineered spectral conditions remains a priority. Ultrafast spectroscopy (2DES) under filtered illumination and controlled environment growth chambers with programmable LED spectra offer immediate validation pathways.

## 5.7 Broader implications for materials design

The "spectral bath engineering" approach introduced here—identifying quantum-enhanced processes in nature, characterizing their environmental coupling, and deliberately engineering artificial environments to maximize those quantum resources—may prove applicable to fields beyond agrivoltaics:

**Artificial photosynthesis.** Molecular catalysts for water splitting and CO<sub>2</sub> reduction could benefit from spectral engineering to enhance charge separation lifetimes and reaction selectivity.

**Quantum solar cells.** Intermediate band solar cells and singlet fission devices exploit quantum phenomena that could be enhanced through spectral bath engineering.

**Bio-inspired molecular electronics:** Molecular junctions and single-molecule devices operating in the quantum coherent regime could leverage environmental engineering for performance optimization.

The convergence of AI-driven materials discovery, quantum dynamics simulation, and techno-economic analysis demonstrated here provides a comprehensive framework for multi-objective materials optimization applicable across these domains.

## 6 Conclusion

We have demonstrated that molecular engineering of semi-transparent non-fullerene acceptors enables quantum-enhanced energy harvesting with power conversion efficiencies reaching 18.8%. By strategically tuning the spectral transmission to target vibronic resonances in photosynthetic complexes, these materials simultaneously achieve high electrical output and preserved biological activity.

The quantum enhancement mechanism—extending coherence lifetimes by 20–50% through non-Markovian dynamics—provides a new design principle for OPV materials in dual-use applications. Multi-objective optimization establishes quantitative trade-offs between photovoltaic performance and spectral transmission, with validated design rules for targeting specific applications:

- Balanced configuration: 18.2% PCE with 25% ETR enhancement;
- Energy-focused configuration: 22.1% PCE with 12% ETR enhancement;
- Agriculture-focused configuration: 15.4% PCE with 33% ETR enhancement.

The AI-driven discovery pipeline screened 2847 candidates using equivariant graph neural networks, achieving 100× acceleration compared to exhaustive DFT + HEOM simulation. This methodology provides a scalable framework for multi-objective materials optimization applicable beyond agrivoltaics.

Operational stability represents a critical requirement for commercial deployment. The optimized PM6/Y6-BO derivative system demonstrates T<sub>80</sub> lifetimes exceeding 18000 h under continuous illumination, with thermal cycling stability (<0.17% degradation per cycle) projecting 20+ year operational lifetimes [?]. Techno-economic modeling indicates levelized energy costs of

0.04–0.06 USD kWh<sup>-1</sup>, competitive with conventional silicon photovoltaics while enabling agricultural revenue diversification.

Key structure-property relationships established in this work provide quantitative design rules for next-generation semi-transparent OPVs:

- Side-chain engineering for spectral transmission tuning (750 nm and 820 nm windows);
- Energy level alignment optimization ( $\Delta E_{\text{LUMO}} = 0.75 \text{ eV}$ ,  $\Delta E_{\text{HOMO}} = 0.35 \text{ eV}$ );
- Morphology control for balanced charge transport ( $\mu_h/\mu_e \approx 1.2$ );
- Interfacial ESP gradients  $>0.3 \text{ eV}$  for efficient exciton dissociation.

Geographic validation across nine climate zones, including sub-Saharan Africa, confirms persistent quantum advantages of 18–26 % under diverse environmental conditions. The temperature optimum of 285–300 K coincides with typical agricultural conditions, ensuring robust performance in target deployment regions.

These findings establish spectral bath engineering as a materials design paradigm for co-optimizing energy conversion and biological compatibility in next-generation semi-transparent photovoltaics. The integration of AI-driven discovery, quantum dynamics simulation, and techno-economic analysis provides a comprehensive framework applicable to artificial photosynthesis, quantum solar cells, and bio-inspired molecular electronics.

## Acknowledgments

This work was supported by the University of Yaoundé I and the University of Douala.

## Data availability statement

All data supporting the findings of this study are available within the article and its Supporting Information. Raw simulation output files, analysis scripts, and parameter sets are available from the corresponding author upon reasonable request. Our custom PT-HOPS/SBD simulation framework, computational notebooks, source code, and datasets generated during this study are available in the GitHub repository at [https://github.com/NanaEngo/Quantum\\_Agrivoltaic\\_HOPS](https://github.com/NanaEngo/Quantum_Agrivoltaic_HOPS). Reproducibility information: All simulations were performed using Python 3.12.12, NumPy 2.0.2, and SciPy 1.14.1. Computational parameters and environment configurations are documented in the Supporting Information. All reported values include standard errors calculated from ensemble averaging, with 95 % confidence intervals explicitly stated for all quantitative results derived from 100 independent realizations.

## Conflicts of interest

The authors declare no conflicts of interest.

## Author contributions

**Steve Cabrel Tegua Kouam:** Methodology, validation, formal analysis, writing – original draft. **Theodore Goumai Vedekoi:** Software, investigation, data curation, writing – original draft. **Jean-Pierre Tchapel Njafa:** Conceptualization, theoretical framework, writing – review & editing. **Jean-Pierre Nguenang:** Resources, supervision, formal analysis. **Serge Guy Nana Engo:** Project administration, conceptualization, theoretical framework, final manuscript editing. All authors have given approval to the final version of the manuscript.

## Supporting Information

Supporting Information includes detailed OPV synthesis protocols, device fabrication procedures, quantum dynamics methods (PT-HOPS/SBD technical details), AI/ML model architecture specifications, stability testing protocols (ISOS standards), economic analysis details (LCOE calculations), and additional validation data (12 tests expanded).




Figure 5: **AI-driven materials discovery pipeline.** (a) Four-stage screening workflow: (1) virtual library generation (12 450 candidates), (2) E(n)-GNN property prediction, (3) multi-criteria filtering (23 candidates remaining), (4) PT-HOPS quantum dynamics validation (final selection). (b) E(n)-GNN architecture with 6 message-passing layers, attention aggregation, and 4 output heads. (c) Parity plots showing model performance: excitation energies (MAE < 5 meV), charge transfer rates (MAE < 10 %), reorganization energies (MAE < 15 meV). Testing on 3962 held-out samples. Complete screening achieved 100 $\times$  speedup vs. exhaustive DFT + HEOM.

Figure 6: **Environmental robustness of quantum enhancement.** (a) Temperature dependence showing maximum coherence preservation at 285–300 K (shaded green), coinciding with typical agricultural conditions. (b) Static energetic disorder effects: ensemble average over 100 realizations with  $\sigma = 50 \text{ cm}^{-1}$  yields  $\langle \eta_{\text{quantum}} \rangle = 0.20 \pm 0.04$ . (c) Geographic validation across 9 climate zones: temperate (Germany, 50°N), subtropical (India, 20°N), tropical (Kenya, 0°), desert (Arizona, 32°N), and 5 sub-Saharan African sites (circles). Consistent 18–26 % enhancement across all climates. (d) Bath parameter fluctuations ( $\lambda, \gamma \pm 20 \%$ ): enhancement persists at 18–26 %. Error bars represent 95 % confidence intervals.




Figure 7: **Summary of design guidelines for quantum-enhanced agrivoltaics.** (a) Key molecular design parameters: spectral transmission windows (750 nm and 820 nm), energy level offsets ( $\Delta E_{\text{LUMO}} > 0.3 \text{ eV}$ ), charge mobility ( $\mu > 10^{-3} \text{ cm}^2/\text{V/s}$ ). (b) Structure-property relationships linking molecular modifications to device performance. (c) Implementation roadmap from computational design to experimental validation and commercial deployment. Based on simulation results and literature analysis presented in this work.