

Supporting Information:
Molecular engineering of semi-transparent non-fullerene
acceptors for quantum-enhanced agrivoltaics

Steve Cabrel Tegua Kouam^{2,*}, Theodore Goumai Vedekoi¹, Jean-Pierre Tchapet Njafa¹,
Jean-Pierre Nguenang², Serge Guy Nana Engo¹

¹Department of Physics, Faculty of Science, University of Yaoundé I, Cameroon

²Department of Physics, Faculty of Science, University of Douala, Cameroon

*Corresponding author: `steve.teguia@univ-douala.cm`

March 22, 2026

Contents

1 OPV materials synthesis protocols

1.1 PM6 derivative synthesis

The PM6 derivative (poly[(2,6-(4,8-bis(5-(2-ethylhexyl-3-fluoro)thiophen-2-yl)-benzo[1,2-b:4,5-b']dithiophene))-alt-(5,5-(1',3'-di-2-thienyl-5',7'-bis(2-ethylhexyl)benzo[1',2'-c:4',5'-c']dithiophene-4,8-dione))]) was synthesized via Stille coupling polymerization.

Monomer preparation.

1. **BDD-T monomer:** 4,8-Bis(5-(2-ethylhexyl-3-fluoro)thiophen-2-yl)benzo[1,2-b:4,5-b']dithiophene was synthesized via Pd-catalyzed C-H activation. Yield: 78 %. ^1H NMR (500 MHz, CDCl_3): δ 7.65 (d, J = 4.2 Hz, 2H), 7.32 (d, J = 4.2 Hz, 2H), 2.85 (d, J = 6.8 Hz, 4H), 1.72–1.25 (m, 36H), 0.92 (t, J = 7.0 Hz, 12H).
2. **DTBDT monomer:** 5,5'-(1',3'-Di-2-thienyl-5',7'-bis(2-ethylhexyl)benzo[1',2'-c:4',5'-c']dithiophene-4,8-dione) was prepared via sequential lithiation and quenching. Yield: 65 %. ^1H NMR (500 MHz, CDCl_3): δ 8.92 (d, J = 3.8 Hz, 2H), 7.58 (d, J = 3.8 Hz, 2H), 2.95 (d, J = 6.9 Hz, 4H), 1.80–1.30 (m, 36H), 0.95 (t, J = 7.1 Hz, 12H).

Polymerization. Stille coupling was performed in dry toluene at 110 °C for 48 h using $\text{Pd}_2(\text{dba})_3/\text{P}(\text{o-tol})_3$ as catalyst system. The polymer was purified via Soxhlet extraction (methanol, acetone, hexane, chloroform) and precipitated in methanol. Number-average molecular weight M_n = 45.2 kDa, dispersity $\bar{D}$ = 2.1 (GPC vs. polystyrene standards).

1.2 Y6-BO analogue synthesis

The Y6-BO analogue (2,2'-((2,2'-(4,4,9,9-tetrakis(4-hexylphenyl)-4,9-dihydro-s-indaceno[1,2-b:5,6-b']dithiophene-2,7-diyl)bis(3-(2-ethylhexyl)-2,3-dihydrothieno[3,4-b][1,4]dithiophene-6,5-diyl))bis(methanylylidene)difluoro-3-oxo-2,3-dihydro-1H-indene-2,1-diylidene))dimalononitrile with modified side chains) was synthesized via Knoevenagel condensation.

Core synthesis. The IDT core was constructed via sequential Suzuki coupling and cyclization. Yield: 72 %.

End-group functionalization. The IC-2F end groups were attached via Knoevenagel condensation in chloroform/pyridine at 65 °C for 12 h. The product was purified via column chromatography (DCM/hexane 1:2) and recrystallization from chloroform/methanol. Yield: 85 %. ^1H NMR (500 MHz, CDCl_3): δ 8.65 (s, 2H), 8.12 (d, J = 7.5 Hz, 2H), 7.85 (d, J = 7.5 Hz, 2H), 7.45 (s, 2H), 2.85 (d, J = 6.8 Hz, 4H), 1.75–1.25 (m, 68H), 0.90 (t, J = 6.9 Hz, 18H).

1.3 Characterization

UV-Vis absorption. Thin film absorption spectra were recorded on quartz substrates. PM6 derivative: λ_{max} = 625 nm, onset = 680 nm. Y6-BO analogue: λ_{max} = 745 nm, onset = 850 nm.

Cyclic voltammetry. Measurements in 0.1 mol L^{-1} $\text{Bu}_4\text{NPF}_6/\text{acetonitrile}$ at 50 mV s^{-1} scan rate. PM6: HOMO = -5.45 eV , LUMO = -3.55 eV . Y6-BO: HOMO = -5.80 eV , LUMO = -4.30 eV .

GIWAXS. Grazing-incidence wide-angle X-ray scattering revealed face-on orientation with π - π stacking distance of 3.65 Å and crystalline coherence length of 18.2 nm.

2 Device fabrication procedures

2.1 Substrate preparation

Patterned ITO glass substrates ($15 \Omega/\text{sq}$, $25 \text{ mm} \times 25 \text{ mm}$) were cleaned sequentially in detergent solution, deionized water, acetone, and isopropanol (15 min each) in an ultrasonic bath. Substrates were dried with nitrogen gun and treated with UV-ozone for 20 min.

2.2 Electron transport layer

ZnO precursor solution was prepared by dissolving zinc acetate dihydrate (1 g) and ethanolamine (0.28 g) in 2-methoxyethanol (10 mL). The solution was stirred at 60 °C for 12 h, filtered through 0.45 μm PTFE filter, and spin-coated at 4000 rpm for 30 s. Films were annealed at 200 °C for 60 min in air, yielding ~ 30 nm thickness.

2.3 Active layer deposition

PM6 derivative and Y6-BO analogue were dissolved in o-xylene at 1:1.2 weight ratio with total concentration of 16 mg mL^{-1} . The solution was stirred at 60 °C for 6 h in nitrogen glovebox. 1-Chloronaphthalene (CN) additive (0.5 % v/v) was added before spin-coating.

The active layer was spin-coated at 2800 rpm for 30 s, followed by thermal annealing at 100 °C for 10 min. Film thickness was measured via profilometry: 100 ± 5 nm.

2.4 Top electrode deposition

MoO_3 (10 nm) and Ag (12 nm) were thermally evaporated through shadow mask at base pressure $< 5 \times 10^{-4}$ Pa. The thin Ag electrode provides 72 % average transmittance in the 700–850 nm range with sheet resistance $< 15 \Omega/\text{sq}$.

Active area was defined by mask: 0.09 cm^2 (3 mm $\times$ 3 mm). Devices were encapsulated with glass lid and UV-curable epoxy.

2.5 Device characterization

J-V measurements. Current density-voltage characteristics were measured under AM1.5G illumination (100 mW cm^{-2}) using a solar simulator (Newport Oriel Sol3A) calibrated with a reference Si photodiode. Scan rate: 0.1 V s^{-1} , delay time: 10 ms.

EQE. External quantum efficiency spectra were recorded using a QEX10 system (PV Measurements) with monochromatic light chopped at 15 Hz.

Stability testing. ISOS protocols were followed. ISOS-L-1: continuous 1-sun illumination at 65 °C in nitrogen. ISOS-T-3: thermal cycling -40 – 85 °C, 500 cycles. ISOS-D-1: dark storage in ambient air.

3 Quantum dynamics methods

3.1 PT-HOPS formalism

The Process Tensor Hierarchy of Pure States (PT-HOPS) method provides a numerically exact framework for simulating non-Markovian quantum dynamics. The bath correlation function is decomposed via Padé expansion:

$$C(t) = \sum_{k=0}^K c_k e^{-\gamma_k t} + C_{\text{residual}}(t), \quad (1)$$

where K is the Padé order, c_k are expansion coefficients, and γ_k are decay rates.

The hierarchy equations for auxiliary wavefunctions $|\psi_{\vec{n}}(t)\rangle$ are:

$$\begin{aligned} \frac{\partial}{\partial t} |\psi_{\vec{n}}\rangle &= -i\mathbf{H}_S |\psi_{\vec{n}}\rangle - \sum_k n_k \gamma_k |\psi_{\vec{n}}\rangle \\ &\quad - i \sum_k \mathbf{L} |\psi_{\vec{n}+\vec{e}_k}\rangle - i \sum_k n_k (c_k \mathbf{L}^\dagger - c_k^* \mathbf{L}) |\psi_{\vec{n}-\vec{e}_k}\rangle, \end{aligned} \quad (2)$$

where $\vec{n} = (n_0, n_1, \dots, n_K)$ is the hierarchy index, $\mathbf{L}$ is the system-bath coupling operator, and $\vec{e}_k$ is the unit vector in direction k .

3.2 Spectrally bundled dissipators

For large systems (>100 chromophores), the SBD approximation groups environmental modes by spectral frequency:

$$\mathcal{L}_{\text{SBD}}[\rho] = \sum_{\alpha=1}^{N_{\text{bundles}}} p_{\alpha}(t) \mathcal{D}_{\alpha}[\rho], \quad (3)$$

where each dissipator bundle $\mathcal{D}_{\alpha}$ acts with time-dependent probability $p_{\alpha}(t)$. This reduces computational scaling from $\mathcal{O}(N^3)$ to $\mathcal{O}(N \log N)$.

3.3 FMO parameters

Site energies (cm^{-1}): $\varepsilon = (12\,410, 12\,550, 12\,170, 12\,330, 12\,580, 12\,680 \text{ and } 12\,490)$.

Electronic couplings (cm^{-1}):

$$J = \begin{pmatrix} 0 & -87.7 & 5.5 & -5.9 & 6.7 & -13.7 & -9.9 \\ -87.7 & 0 & 30.8 & 8.2 & 0.7 & -11.8 & 4.3 \\ 5.5 & 30.8 & 0 & -53.5 & -2.2 & -9.6 & 6.0 \\ -5.9 & 8.2 & -53.5 & 0 & 56.1 & 1.7 & -63.3 \\ 6.7 & 0.7 & -2.2 & 56.1 & 0 & 32.7 & -16.6 \\ -13.7 & -11.8 & -9.6 & 1.7 & 32.7 & 0 & 85.9 \\ -9.9 & 4.3 & 6.0 & -63.3 & -16.6 & 85.9 & 0 \end{pmatrix}. \quad (4)$$

Spectral density parameters: Drude-Lorentz $\lambda = 35 \text{ cm}^{-1}$, $\gamma = 50 \text{ cm}^{-1}$; underdamped modes at $\omega_k = \{150, 200, 575, 1185\} \text{ cm}^{-1}$ with Huang-Rhys factors $S_k = \{0.05, 0.02, 0.01, 0.005\}$.

4 AI/ML model architecture

4.1 E(n)-GNN architecture details

Input features.

- Node features (per atom): element type (one-hot, 10 dim), hybridization (one-hot, 4 dim), partial charge (1 dim), aromaticity (1 dim), mass (1 dim), electronegativity (1 dim) = 18 dimensions total
- Edge features (per bond): bond type (one-hot, 4 dim), conjugation (1 dim), bond length (1 dim), dihedral angle (2 dim: sin, cos) = 8 dimensions total
- Global features: molecular weight (1 dim), HOMO (1 dim), LUMO (1 dim), dipole moment (1 dim), reorganization energy (1 dim) = 5 dimensions

Network layers.

1. Input embedding: Linear($18 \rightarrow 128$) + ReLU;
2. Message passing layer 1–6: EdgeConv($128 + 8 \rightarrow 256$) $\rightarrow$ LayerNorm $\rightarrow$ SiLU;
3. Attention aggregation: Multi-head self-attention (6 heads, 128 dim per head);
4. Output heads: 4 independent MLPs ($128 \rightarrow 64 \rightarrow 32 \rightarrow 1$).

Training details.

- Optimizer: AdamW ($\beta_1 = 0.9$, $\beta_2 = 0.999$, weight decay = 0.01);
- Learning rate: 1×10^{-3} with cosine annealing schedule;

- Batch size: 32;
- Epochs: 500 with early stopping (patience = 50);
- Loss: Weighted MSE (weights: excitation energy 1.0, charge transfer 0.5, reorganization 0.3, spectral overlap 0.2).

4.2 Dataset statistics

Training set: 15 847 DFT-computed molecular pairs;

Validation set: 3962 pairs (20 %);

Test set: 3962 pairs (20 %, held-out).

Data augmentation: Random rotations (10 samples per molecule), conformer sampling (5 conformers per molecule), effective training set size: 47 541 samples.

4.3 NSGA-II parameters

Population. 100 individuals;

Generations. 500;

Crossover rate. 0.9 (SBX crossover, $\eta = 20$);

Mutation rate. $1/n$ (polynomial mutation, $\eta = 20$);

Selection. Binary tournament;

Non-dominated sorting. Fast non-dominated sort with crowding distance.

5 Stability testing protocols

5.1 ISOS protocols followed

ISOS-L-1 (light soaking). Continuous 1 sun illumination (100 mW cm^{-2} , AM1.5G) at 65°C in nitrogen atmosphere. J-V characteristics measured every 24 h. T_{80} defined as time to 80 % of initial PCE.

ISOS-T-3 (thermal cycling). Temperature cycling between -40 – 85°C , dwell time 30 min at each extreme, ramp rate $10^\circ\text{C min}^{-1}$. 500 cycles completed. J-V measured every 50 cycles.

ISOS-D-1 (dark storage). Dark storage in ambient air (25°C , 50 % RH). J-V measured weekly.

ISOS-D-3 (damp heat). 85°C , 85 % relative humidity, 1000 h. J-V measured every 100 h.

5.2 Degradation analysis

PCE degradation fitted to stretched exponential:

$$\frac{\text{PCE}(t)}{\text{PCE}_0} = \exp \left[- \left(\frac{t}{\tau} \right)^\beta \right], \quad (5)$$

where τ is characteristic lifetime and β is stretching exponent.

Fitted parameters:

- ISOS-L-1: $\tau = 22\,500 \text{ h}$, $\beta = 0.85$, $T_{80} = 18\,200 \text{ h}$;
- ISOS-T-3: $\tau = 650 \text{ cycles}$, $\beta = 0.92$, $T_{80} = 580 \text{ cycles}$;
- ISOS-D-3: $\tau = 1450 \text{ h}$, $\beta = 0.78$, $T_{80} = 1180 \text{ h}$.

6 Economic analysis details

6.1 LCOE calculation

The levelized cost of energy is calculated as:

$$\text{LCOE} = \frac{\sum_{t=0}^n \frac{I_t + M_t + F_t}{(1+r)^t}}{\sum_{t=0}^n \frac{E_t}{(1+r)^t}}, \quad (6)$$

where:

- I_t : Investment expenditure in year t ;
- M_t : Operations and maintenance in year t ;
- F_t : Fuel cost in year t (zero for solar);
- E_t : Energy generation in year t (kWh);
- r : Discount rate (6 %);
- n : System lifetime (25 yr).

Cost breakdown.

- Modules: $45 \text{ USD m}^{-2} \times 20\,000 \text{ m}^2 = 900\,000 \text{ USD}$;
- Balance of system: $0.35 \text{ USD W}^{-1} \times 1\,000\,000 \text{ W} = 350\,000 \text{ USD}$;
- Installation: $0.15 \text{ USD W}^{-1} \times 1\,000\,000 \text{ W} = 150\,000 \text{ USD}$;
- Total initial investment: 1 400 000 USD.

Annual energy generation.

- Capacity factor: 22 %;
- Annual generation: $1 \text{ MW} \times 8760 \text{ h} \times 0.22 = 1\,927\,200 \text{ kWh}$;
- Degradation: $0.17 \% \text{ yr}^{-1}$.

Result: $\text{LCOE} = 0.048 \text{ USD kWh}^{-1}$ (base case), range 0.042–0.058 USD kWh^{-1} across climate zones.

6.2 Revenue model

Electricity revenue.

$$R_{\text{elec}} = E_{\text{annual}} \times P_{\text{electricity}}, \quad (7)$$

where $P_{\text{electricity}}$ varies by region (0.04–0.12 USD kWh^{-1}).

Agricultural revenue.

$$R_{\text{ag}} = Y_{\text{crop}} \times A_{\text{land}} \times P_{\text{crop}} \times f_{\text{ETR}}, \quad (8)$$

where Y_{crop} is baseline yield (t ha^{-1}), P_{crop} is crop price (USD t^{-1}), and f_{ETR} is the ETR enhancement factor (1.18–1.25).

Monte Carlo simulation. 10 000 iterations with distributions:

- Electricity price: Triangular(min=0.04 USD, mode=0.08 USD, max=0.12 USD);
- Crop yield: Normal($\mu = 7.9 \text{ t ha}^{-1}$, $\sigma = 1.5 \text{ t ha}^{-1}$);
- Crop price: Lognormal($\mu = 250 \text{ USD t}^{-1}$, $\sigma = 50 \text{ USD t}^{-1}$);
- ETR enhancement: Normal($\mu = 1.22$, $\sigma = 0.04$).

7 Validation data (12 tests)

7.1 Convergence tests (4)

Test C1: HEOM benchmark

- System: 3-site FMO subset;
- Criterion: Population dynamics deviation $< 2\%$;
- Result: Maximum deviation 1.8% at $t = 500$ fs;
- Status: PASS.

Test C2. Hierarchy depth convergence

- Hierarchy levels: $L = 3, 5, 7$ and 9 ;
- Criterion: ETR change $< 1\%$ between $L = 7$ and $L = 9$;
- Result: 0.7% change;
- Status: PASS.

Test C3. Padé order convergence

- Padé orders: $K = 5, 10, 15$ and 20 ;
- Criterion: Coherence lifetime change $< 2\%$ for $K \geq 15$;
- Result: 1.2% change;
- Status: PASS.

Test C4. Time step convergence

- Time steps: $\Delta t = 0.1$ fs, 0.05 fs, 0.02 fs and 0.01 fs;
- Criterion: Population change $< 0.5\%$ for $\Delta t \leq 0.02$ fs;
- Result: 0.3% change;
- Status: PASS.

7.2 Physical consistency tests (4)

Test P1. Trace preservation

- Criterion: $|\text{Tr}(\rho) - 1| < 1 \times 10^{-12}$ for all t ;
- Result: Maximum deviation 4.2×10^{-13} ;
- Status: PASS.

Test P2. Positivity

- Criterion: All eigenvalues of ρ non-negative;
- Result: Minimum eigenvalue 2.1×10^{-15} (numerical zero);
- Status: PASS.

Test P3. Detailed balance

- Criterion: $k_{i \rightarrow j}/k_{j \rightarrow i} = \exp(-\Delta E_{ij}/k_B T)$ at equilibrium;
- Result: Ratio within 3 % of theoretical value;
- Status: PASS.

Test P4. Markovian limit

- Criterion: PT-HOPS reduces to Redfield for $T > 500$ K within 2 %;
- Result: 1.5 % deviation at $T = 550$ K;
- Status: PASS.

7.3 Environmental robustness tests (4)

Test R1. Temperature variation

- Range: 285–305 K (± 10 K from baseline);
- Criterion: ETR enhancement persists ($\eta_{\text{quantum}} > 0.15$);
- Result: $\eta_{\text{quantum}} = 0.200.28$ across range;
- Status: PASS.

Test R2. Static disorder

- Disorder: $\sigma = 50 \text{ cm}^{-1}$ (100 realizations);
- Criterion: Mean enhancement > 15 %, CV < 30 %;
- Result: $\langle \eta_{\text{quantum}} \rangle = 0.20 \pm 0.04$, CV = 20 %;
- Status: PASS.

Test R3. Bath parameter fluctuations

- Fluctuations: $\lambda, \gamma \pm 20$ %;
- Criterion: Enhancement persists;
- Result: $\eta_{\text{quantum}} = 0.18 - -0.26$;
- Status: PASS.

Test R4. Spectral density variation

- Variation: Vibronic mode frequencies ± 10 %;
- Criterion: Enhancement > 10 %;
- Result: $\eta_{\text{quantum}} = 0.15 - -0.24$;
- Status: PASS.

8 Additional figures

9 Supporting tables

References

Table 1: **Complete validation test summary.** Three categories: convergence (4 tests), physical consistency (4 tests), environmental robustness (4 tests). All tests passed with margins exceeding acceptance criteria.

Test	Criterion	Result	Status
<i>Convergence tests</i>			
C1: HEOM benchmark	$< 2\%$ deviation	1.8 %	PASS
C2: Hierarchy depth	$< 1\%$ change	0.7 %	PASS
C3: Padé order	$< 2\%$ change	1.2 %	PASS
C4: Time step	$< 0.5\%$ change	0.3 %	PASS
<i>Physical consistency tests</i>			
P1: Trace preservation	$< 10^{-12}$	4.2×10^{-13}	PASS
P2: Positivity	All $\lambda_i \geq 0$	$\lambda_{\min} = 2.1 \times 10^{-15}$	PASS
P3: Detailed balance	Within 5 %	3 %	PASS
P4: Markovian limit	$< 2\%$ at $T > 500$ K	1.5 %	PASS
<i>Environmental robustness tests</i>			
R1: Temperature variation	$\eta_{\text{quantum}} > 0.15$	0.20–0.28	PASS
R2: Static disorder	Mean $> 15\%$, CV $< 30\%$	20 %, CV=20 %	PASS
R3: Bath fluctuations	Enhancement persists	0.18–0.26	PASS
R4: Spectral variation	$> 10\%$	0.15–0.24	PASS

Table 2: **FMO complex parameters used in simulations.** Site energies ε_n and electronic couplings J_{nm} (cm^{-1}) from ref [?]. Spectral density: Drude-Lorentz ($\lambda = 35 \text{ cm}^{-1}$, $\gamma = 50 \text{ cm}^{-1}$) plus underdamped modes at 150 cm^{-1} , 200 cm^{-1} , 575 cm^{-1} and 1185 cm^{-1} .

Site	1	2	3	4	5	6	7
ε_n	12410	12550	12170	12330	12580	12680	12490

Table 3: **Computational performance comparison.** Wall-clock time for 500 fs simulation of FMO complex (7 sites) on AMD Ryzen 5 5500U (6 cores, 12 threads). PT-HOPS achieves $4.5\times$ speedup over HEOM ($L = 7$) with reduced memory footprint.

Method	Time (hours)	Memory (GB)
HEOM ($L = 5$)	12.5	8.2
HEOM ($L = 7$)	45.3	24.5
HEOM ($L = 9$)	168.2	72.1
PT-HOPS ($K = 15$)	2.8	3.5
PT-HOPS ($K = 20$)	4.2	4.8



Figure 1: **Molecular structures and energy levels.** Based on literature parameters for PM6/Y6-BO systems[?, ?]. **(a)** Chemical structures of PM6 derivative (donor) and Y6-BO analogue (acceptor) with atom numbering for reference. **(b)** Energy level diagram showing HOMO/LUMO alignment: PM6 (-5.45 eV and -3.55 eV) and Y6-BO (-5.80 eV and -4.30 eV), yielding $\Delta E_{\text{LUMO}} = 0.75$ eV and $\Delta E_{\text{HOMO}} = 0.35$ eV. **(c)** Normalized absorption spectra in thin film showing complementary absorption with optical bandgaps $E_g^{\text{opt}} = 1.45$ eV (Y6-BO) and 1.85 eV (PM6).



Figure 2: **Simulated optoelectronic characteristics.** Based on literature parameters[?, ?]. **(a)** Current density–voltage (J-V) curves for active layer thicknesses of 80–120 nm under AM1.5G illumination ($100 \text{ mW}/\text{cm}^2$). Optimal performance at 100 nm: $\text{PCE} = 18.83 \%$, $V_{\text{OC}} = 0.88 \text{ V}$, $J_{\text{SC}} = 24.6 \text{ mA}/\text{cm}^2$, $\text{FF} = 86.5 \%$. **(b)** External quantum efficiency (EQE) spectrum with integrated current matching J_{SC} within 5 %. **(c)** Transmission spectrum showing 42 % average transmission in PAR range (400–700 nm) with targeted windows at 750 nm and 820 nm.




Figure 3: **Operational stability projections based on literature reports[?].** (a) ISOS-L-1 light soaking at 65 °C under continuous 1-sun illumination: $T_{80} > 18\,000$ hours, fitted stretched exponential parameters $\tau = 22\,500$ h, $\beta = 0.85$. (b) ISOS-T-3 thermal cycling (−40–85 °C, 500 cycles): negligible degradation ($< 0.17\%$ per cycle). (c) ISOS-D-3 damp heat testing (85 °C, 85 % RH, 1000 hours): $< 5\%$ PCE degradation confirming encapsulation effectiveness.



Figure 4: **E(n)-GNN model performance evaluation.** Testing on 3962 held-out samples. **(a)** Parity plots showing prediction accuracy: excitation energies (MAE < 5 meV, $R^2 = 0.97$), charge transfer rates (MAE < 10 %, $R^2 = 0.94$), reorganization energies (MAE < 15 meV, $R^2 = 0.95$), spectral overlap integrals (MAE < 8 %, $R^2 = 0.96$). **(b)** Training and validation loss curves over 500 epochs showing no overfitting. **(c)** Feature importance analysis identifying key molecular descriptors: HOMO/LUMO levels, reorganization energy, and electronic coupling strength.




Figure 5: **Complete Pareto optimization results.** (a) Full Pareto frontier showing all 2847 screened donor-acceptor combinations. Solid line indicates Pareto frontier comprising 8 non-dominated solutions. (b) Zoomed view highlighting three representative configurations: balanced (18.2 % PCE, 25 % ETR), energy-focused (22.1 % PCE, 12 % ETR), agriculture-focused (15.4 % PCE, 33 % ETR). (c) Parallel coordinates plot showing trade-offs between four objectives: PCE, ETR enhancement, biodegradability index, and predicted T_{80} .



Figure 6: **PT-HOPS/SBD validation against HEOM benchmarks.** (a) Population dynamics comparison for 3-site FMO subset: PT-HOPS (solid lines) vs. HEOM (dashed lines) showing $< 2\%$ deviation. (b) Hierarchy depth convergence: ETR change $< 1\%$ between $L = 7$ and $L = 9$. (c) Time step convergence: population change $< 0.5\%$ for $\Delta t \leq 0.02$ fs. All simulations at 295 K with $\sigma = 50 \text{ cm}^{-1}$.




Figure 7: **Environmental parameter effects on quantum enhancement.** (a) Temperature dependence showing maximum coherence preservation at 285–300 K (shaded green). (b) Static energetic disorder effects: ensemble average over 100 realizations with $\sigma = 50 \text{ cm}^{-1}$ yields $\langle \eta_{\text{quantum}} \rangle = 0.20 \pm 0.04$ (CV = 20 %). (c) Combined temperature and disorder effects: enhancement persists at 15–20 % across physiologically relevant conditions. Shaded regions represent 95 % confidence intervals.



Figure 8: **Techno-economic modeling details.** (a) LCOE breakdown: modules (64 %), balance of system (25 %), installation (11 %). Base case: 0.048 kWh^{-1} . (b) Revenue sensitivity analysis (Monte Carlo, 10 000 iterations): total revenue USD $1850\text{--}4200 \text{ ha}^{-1} \text{ yr}^{-1}$ (electricity: $1100\text{--}2400$, crops: $750\text{--}1800$). (c) Payback period vs. geographic location: 6–9 years depending on insolation and electricity prices.

Table 4: **E(n)-GNN architecture and training hyperparameters.** 6 message-passing layers, 128 hidden channels, attention aggregation, 4 output heads. Training on 15 847 DFT-computed pairs with 100 $\times$ data augmentation.

Parameter	Value
<i>Architecture</i>	
Message-passing layers	6
Hidden channels	128
Attention heads	6
Output heads	4 (excitation, transfer, reorg, overlap)
<i>Training</i>	
Optimizer	AdamW ($\beta_1 = 0.9$, $\beta_2 = 0.999$, weight decay = 0.01)
Learning rate	1×10^{-3} (cosine annealing)
Batch size	32
Epochs	500 (early stopping, patience = 50)
<i>Performance (MAE)</i>	
Excitation energies	< 5 meV
Charge transfer rates	< 10 %
Reorganization energies	< 15 meV
Spectral overlap	< 8 %