

A Multiscale CMC-Fracture Problem: Motivation, Mathematical Statement, and Methodological Basis

Abstract

Ceramic-matrix composites (CMCs) offer low density, high-temperature capability, and damage tolerance, but their matrix-cracking response depends on geometry, material architecture, interfaces, loading, and environment. This note defines a bounded computational problem: evaluate a fracture-driving quantity and its associated fields with a finite-element (FE) model, learn a fast surrogate for the same parameterized map, and accept its use only when it agrees with the reference calculation under predeclared criteria. This is a research architecture, not a claim that a solver or surrogate has been qualified for a structural decision.

1 Motivation

Continuous-fiber CMCs are intended to avoid the abrupt tensile failure of monolithic ceramics. A suitably compliant interphase can deflect matrix cracks, permit interface debonding, and leave fibers bridging the crack faces. The material can then accumulate distributed damage rather than concentrating all energy at one unstable crack. The compensating difficulty is that the response depends on constituent properties, fiber architecture, interface condition, defects, temperature history, and the local multiaxial stress field. NASA reports on SiC/SiC composites identify matrix cracking, oxidation, creep, and fiber degradation as coupled life-relevant phenomena [1, 3].

For an analyst, a CAD geometry is consequently not a material model. It must be paired with a declared architecture, constitutive and fracture laws, boundary conditions, loading history, and mesh. Its results must retain units, discretization, solver settings, and material parameters. Otherwise two outputs called “fracture” can answer different physical questions. This distinction is unromantic, but a simulation pipeline does not become credible simply because its containers are arranged in a directed acyclic graph.

The problem here is deliberately narrower than complete service-life prediction. For a family of CMC structures, estimate displacement and stress fields near a crack or notch and a fracture-driving quantity represented by the J -integral. In its original elastic setting, J is a path-independent measure of energy release rate for crack advance [10]. In a heterogeneous, bridged, nonlinear, or dissipative CMC, path independence and equivalence to a unique material toughness require additional assumptions. Thus J is an informative target and diagnostic, not a scalar that makes the microphysics go away.

High-fidelity FE analysis gives a defensible reference route: it resolves the specified geometry and boundary conditions, exposes constitutive assumptions, and permits mesh and contour-convergence studies. Its cost becomes onerous in a study spanning geometries, thermal states, material parameters, and loads. A neural operator is attractive because it learns a map between input functions and solution fields, rather than just a finite-dimensional regression at one grid resolution [4]. The Fourier neural operator (FNO) uses Fourier-space kernel parameterization and has demonstrated rapid PDE-solution surrogates on benchmark families [5].

Speed is not evidence. A model trained on FE cases can interpolate within its corpus yet fail on a changed notch topology, fiber orientation, thermal state, or crack configuration. Fracture quantities are especially unforgiving: a modest local field error can change a contour integral or a threshold decision. The FE track must therefore remain a comparison authority for selected cases. The system should record disagreement, quality checks, and an out-of-distribution indicator, then refuse a surrogate screening result when the stated limits are not met. That refusal is a useful result, not a software exception wearing a false moustache.

This has consequences for how the multiscale problem is framed. The word “multiscale” should not suggest that a component calculation has automatically resolved the fiber, interface, pore, matrix grain, and crack process zone at their physical scales. It means that information from more than one scale is represented deliberately. A component-scale FE model may use homogenized anisotropic properties, an interface law informed by smaller-scale experiments, and a crack-driving functional evaluated at the structural scale. Each abstraction has a regime of validity. In particular, the parameters in an effective law should be regarded as calibrated model inputs, not as immutable properties that remain correct after changes in temperature, environmental exposure, architecture, or manufacturing route.

The scale separation also explains why the choice of output matters. A scalar such as J is valuable because it supports comparison across a parameter sweep, but it is not sufficient to diagnose every failure mechanism. A result viewer should preserve the displacement, stress, and damage fields that explain why a particular value was obtained. A high J near one region may be caused by a geometric stress concentrator, a boundary-condition artifact, an inadequate mesh, or a genuine material-interface effect. Conflating those possibilities into a single traffic-light label would be efficient in the same sense that a compass is an efficient substitute for a map.

The proposed FE–surrogate pairing is therefore best understood as an experiment-design mechanism. The expensive model supplies selected reference cases across the variables that define the intended domain of use. The fast model explores between those cases and highlights candidates that merit renewed resolution. This permits adaptive allocation of computational effort, but it also requires discipline in data splitting and reporting. Randomly withholding individual voxels or repeated perturbations of one geometry is not evidence that a surrogate can generalize to a new component family. The held-out cases should match the actual claim: unseen loads for load interpolation, unseen geometries for geometric generalization, or unseen material states for material generalization. These are different questions and usually have different error profiles.

Finally, the workflow has a useful engineering boundary. Its near-term purpose is comparative screening and model development, not automated release of a fracture-critical design. To cross that boundary would require model-form verification, calibration, experimental validation in the relevant regime, uncertainty treatment, and configuration control of both numerical and learned models. Those activities are expensive because they replace attractive diagrams with accountable evidence. They are also the activities that make a prediction worth believing. The formulation below is intentionally arranged so that this later evidence can attach to explicit inputs, outputs, assumptions, and acceptance decisions.

2 Problem to be solved

Let $\Omega(\theta) \subset \mathbb{R}^3$ be a component domain obtained from geometry parameters θ . Let Γ_u , Γ_t , and Γ_c denote displacement, traction, and crack/damage boundaries. A simulation case is

$$x = (\Omega(\theta), \mathcal{A}, \mathcal{M}, b, \ell, \tau), \quad (1)$$

where $\mathcal{A}$ is the modeled material architecture, $\mathcal{M}$ its constitutive/fracture parameters, b boundary data, ℓ a load history, and τ the analysis increment. Its required output is

$$y = (\mathbf{u}, \boldsymbol{\sigma}, \boldsymbol{\varepsilon}, d, J; q), \quad (2)$$

where the first four terms are displacement, stress, strain, and a declared damage/crack state; J is a fracture quantity; and q records provenance, units, mesh, model/solver versions, tolerances, and convergence status.

For a quasistatic reference model, seek $\mathbf{u} \in \mathcal{V}$ such that

$$\int_{\Omega} \boldsymbol{\varepsilon}(\mathbf{v}) : \boldsymbol{\sigma}(\mathbf{u}, d, \mathcal{M}) d\Omega = \int_{\Omega} \mathbf{v} \cdot \mathbf{f} d\Omega + \int_{\Gamma_t} \mathbf{v} \cdot \bar{\mathbf{t}} d\Gamma \quad \forall \mathbf{v} \in \mathcal{V}_0, \quad (3)$$

with $\mathbf{u} = \bar{\mathbf{u}}$ on Γ_u . This equilibrium statement is not yet a complete CMC model. An implementation must state its kinematics, anisotropy, thermal dependence, interface law, and damage evolution. For example, an energy-based damage model enforces $\dot{d} \geq 0$; a cohesive model instead introduces a traction–separation law on an internal surface. They are alternative hypotheses, not interchangeable labels.

For a contour Γ surrounding a crack tip with local propagation direction x_1 , write

$$J = \int_{\Gamma} \left(W n_1 - \sigma_{ij} n_j \frac{\partial u_i}{\partial x_1} \right) ds, \quad W = \int_0^{\boldsymbol{\varepsilon}} \boldsymbol{\sigma} : d\boldsymbol{\varepsilon}. \quad (4)$$

In the CMC application, every reported value must identify contour/domain, crack-front direction, treatment of inhomogeneity and dissipation, and mesh and contour convergence. This is what makes J auditable rather than merely numerically expensive.

Denote the reference operator by $\mathcal{S} : x \mapsto y_{\text{FE}}$. Given a corpus $\mathcal{D}_{\text{train}}$ of verified reference cases, train an FNO surrogate $\hat{\mathcal{S}}_{\phi}$ to approximate selected fields and functionals. A schematic FNO layer is

$$\mathbf{v}_{k+1}(\mathbf{r}) = \sigma(W_k \mathbf{v}_k(\mathbf{r}) + \mathcal{F}^{-1}(R_k \mathcal{F}[\mathbf{v}_k])(\mathbf{r})), \quad (5)$$

with local mixing W_k , retained Fourier modes R_k , and transform $\mathcal{F}$. Inputs must have a declared common raster or geometry-aware encoding; FFT-based processing does not make an arbitrary unstructured FE mesh into a regular voxel field.

The training loss should weight the outputs used in the actual decision:

$$\min_{\phi} \mathbb{E}_{(x,y) \sim \mathcal{D}_{\text{train}}} \left[\alpha \frac{\|\hat{\mathbf{u}} - \mathbf{u}\|_2^2}{\|\mathbf{u}\|_2^2 + \epsilon} + \beta \frac{\|\hat{\boldsymbol{\sigma}} - \boldsymbol{\sigma}\|_2^2}{\|\boldsymbol{\sigma}\|_2^2 + \epsilon} + \gamma \frac{|\hat{J} - J|}{|J| + \epsilon} \right]. \quad (6)$$

Held-out evaluation must separate the physical generalization claim—new loads, geometries, or material states—rather than neighboring records from the same run. A new case is accepted for screening only when field and J errors, numerical-quality checks, and an out-of-distribution criterion satisfy predeclared limits. Otherwise it is routed to FE and labeled *indeterminate*.

3 Brief literature review and methodological position

The mechanics foundation begins with energy-based fracture measures. Rice introduced the path-independent integral behind Equation (4) [10]. For CMCs, Marshall and Evans documented multiple matrix cracking, fiber fracture, and pull-out, while Marshall, Cox, and Evans modeled the role of fiber-bridging closure tractions in matrix cracking [7, 8]. Budiansky, Hutchinson, and Evans

distinguish interface regimes relevant to matrix fracture [2]; Moran and Shih provide the domain-integral formulation used naturally in finite-element evaluation [9]. Together, this literature argues for explicit crack/interface assumptions rather than a single, context-free toughness number.

FE is the reference mechanism here because it makes governing assumptions and numerical sensitivity inspectable. Reference does not mean physical truth: calibration, experimental validation, and uncertainty evidence are still needed before any result supports an allowable or life claim. The surrogate literature offers a complementary route. Neural operators formalize maps between function spaces [4]; FNOs are a Fourier-parameterized practical member of that family [5]. Geo-FNO extends the approach toward irregular geometries [6]. Neither result establishes accuracy for CMC crack fields or J ; that must be measured against the declared FE corpus.

The methodological position is therefore conservative. The surrogate is an acceleration layer with a bounded empirical domain of use. It can prioritize designs and make field-level exploration cheaper, but it may not silently replace the reference calculation. Its comparison stage is an adjudication record, not validation unless independent physical evidence has been supplied.

4 Scope and next evidence

The immediate scientific deliverable is one reproducible benchmark corpus for a specified CMC architecture and fracture configuration. Every case should carry the input contract, reference fields, J evaluation details, mesh/convergence evidence, and stable artifact identity. Only then can accuracy, speedup, and refusal behavior be measured. Temperature dependence, interface degradation, transient loads, and richer microstructure are appropriate later extensions, but each expands the physical claim and requires fresh verification and validation.

References

- [1] Narottam P. Bansal. SiC/SiC composites for 1200 C and above. Technical Report NASA/TM-2004-213048, NASA Glenn Research Center, 2004. URL <https://ntrs.nasa.gov/citations/20040191405>.
- [2] Bernard Budiansky, John W. Hutchinson, and Anthony G. Evans. Matrix fracture in fiber-reinforced ceramics. *Journal of the Mechanics and Physics of Solids*, 34(2):167–189, 1986. doi: 10.1016/0022-5096(86)90035-9.
- [3] Michael C. Halbig, James D. Cawley, and Mrityunjay Singh. High temperature mechanical behavior of ceramic composites. Technical Report NASA/TM-1996-106838, NASA Glenn Research Center, 1996. URL <https://ntrs.nasa.gov/citations/19960008148>.
- [4] Nikola Kovachki, Zongyi Li, Kamyar Azizzadenesheli, et al. Neural operator: Learning maps between function spaces with applications to pdes. *Journal of Machine Learning Research*, 24(89):1–97, 2023. URL <https://www.jmlr.org/papers/v24/21-1524.html>.
- [5] Zongyi Li, Nikola Kovachki, Kamyar Azizzadenesheli, et al. Fourier neural operator for parametric partial differential equations. *International Conference on Learning Representations*, 2021. URL <https://arxiv.org/abs/2010.08895>.
- [6] Zongyi Li, Daniel Z. Huang, Burigede Liu, and Anima Anandkumar. Fourier neural operator with learned deformations for pdes on general geometries. *Journal of Machine Learning Research*, 24(388):1–26, 2023. URL <https://arxiv.org/abs/2207.05209>.

- [7] David B. Marshall and Anthony G. Evans. Failure mechanisms in ceramic-fiber/ceramic-matrix composites. *Journal of the American Ceramic Society*, 68(5):225–231, 1985. doi: 10.1111/j.1151-2916.1985.tb15313.x.
- [8] David B. Marshall, Brian N. Cox, and Anthony G. Evans. The mechanics of matrix cracking in brittle-matrix fiber composites. *Acta Metallurgica*, 33(11):2013–2021, 1985. doi: 10.1016/0001-6160(85)90124-5.
- [9] Brian Moran and C. F. Shih. Crack tip and associated domain integrals from momentum and energy balance. *Engineering Fracture Mechanics*, 27(6):615–642, 1987. doi: 10.1016/0013-7944(87)90155-X.
- [10] J. R. Rice. A path independent integral and the approximate analysis of strain concentration by notches and cracks. *Journal of Applied Mechanics*, 35(2):379–386, 1968. doi: 10.1115/1.3601206.