

PDRC MB399AD

Polymer doctor mb399 is a random ethylene-malik grafted polymer.

- It brings Coupling and polarity, while keeping high thermal stability during processing.
- The high content low-molecular-weight, thermoplastic aliphatic polymer brings softness and excellent adhesion.
- Mgives reactivity (versus OH, COOH and NH₂ groups), leading to optimal dispersion during melt mixing with pe
- As an ethylene grafted is compatible with LDPE in all proportions, and with almost all other ethylene copolymers.

Mb399AD is suitable as:

- Adhesion promotor to woven sack fabric
- Adhesion promotor on paper
- adhesion promoter onto metallic surface.

Typical Properties

	Test Method	Unit	Typical Value
Melt Index (190°C/2.16kg)	ISO 1133	g/10min.	6
Melting Point	ISO 11357-3 / ASTM D3418	°C	85
Vicat Softening Temperature (10N)	ISO 306 / ASTM D1525	°C	<40
Flexural Modulus ¹	ISO 178	MPa	<30
Elongation at Break ¹	ISO 527-2 / ASTM D638	%	1100
Tensile Strength at Break ¹	ISO 527-2 / ASTM D638	MPa	4

CAUTION: MB 399 reacts with polymers containing maleic anhydride and acid. This reaction may generate gels or can block an extruder if not controlled. Extruders must be thoroughly purged before and after extruding

Storage Handling and Safety

It should be stored in dry conditions and be kept out of moisture in an aerated building. Improper storage conditions may cause degradation and could have consequences on physical properties of the product. Due to its physical properties (Vicat temperature $<40^{\circ}\text{C}$), it may be possible that the MB399 shows some caking. This is particularly true during summer time. Safety data sheet as well as information on handling and storage of the MB399 is available upon request from polymer doctor or at www.polymerdoctor.com.

Shelf Life

Three years from the date of delivery, in unopened packaging. For any use above this limit, please refer to our technical services.