High Voltage X7R Dielectric, 500 - 3,000 VDC (Commercial Grade)




Overview

KEMET's High Voltage surface mount MLCCs in X7R Dielectric feature a 125°C maximum operating temperature and are considered "temperature stable." The Electronics Industries Alliance (EIA) characterizes X7R dielectric as a Class II material. Components of this classification are fixed, ceramic dielectric capacitors suited for bypass and decoupling applications or for frequency discriminating circuits where Q and stability of capacitance characteristics are not critical. X7R exhibits a predictable change in capacitance with respect to time and voltage and boasts a minimal change in capacitance with reference to ambient temperature. Capacitance change is limited to ±15% from -55°C to +125°C.

In addition to Commercial Grade, Automotive Grade devices are available which meet the demanding Automotive Electronics Council's AEC-Q200 qualification requirements.

Applications

- Charging stations
- · LCD fluorescent backlight ballasts
- · Voltage multiplier circuits
- DC/DC converters
- Power supply
- LAN/WAN interface
- · High voltage decoupling
- Filters
- DC blocking
- · ESD Protection



Ordering Information

С	1210	С	154	K	С	R	Α	С	TU
Ceramic	Case Size (L" x W")	Specification/ Series	Capacitance Code (pF)	Capacitance Tolerance	Rated Voltage (VDC)	Dielectric	Failure Rate/Design	Termination Finish ¹	Packaging/ Grade (C-Spec)
	0402 0603 0805 1206 1210 1808 1812 1825 2220 2225	C = Standard	Two significant digits and number of zeros.	J = ±5% K = ±10% M = ±20%	C = 500 B = 630 D = 1,000 F = 1,500 G = 2,000 Z = 2,500 H = 3,000	R = X7R	A = N/A	C = 100% Matte Sn L = SnPb (5% Pb minimum)	See "Packaging C-Spec Ordering Options Table"

¹ Additional termination finish options may be available. Contact KEMET for details.



Packaging C-Spec Ordering Options Table

Packaging Type ¹	Packaging/Grade Ordering Code (C-Spec)
Bulk Bag/Unmarked	Not required (Blank)
7" Reel/Unmarked	TU
13" Reel/Unmarked	7411 (EIA 0603 and smaller case sizes) 7210 (EIA 0805 and larger case sizes)
7" Reel/Marked	ТМ
13" Reel/Marked	7040 (EIA 0603) 7215 (EIA 0805 and largSer case sizes)

¹ Default packaging is "Bulk Bag". An ordering code C-Spec is not required for "Bulk Bag" packaging.

Benefits

- -55°C to +125°C operating temperature range
- · Industry-leading CV values
- · Exceptional performance at high frequencies
- · Lead (Pb)-free, RoHS and REACH compliant
- EIA 0402, 0603, 0805, 1206, 1210, 1808, 1812, 1825, 2220, and 2225 case sizes
- DC voltage ratings of 500 V, 630 V, 1 KV, 1.5 KV, 2 KV, 2.5 KV, and 3 KV
- Capacitance offerings ranging from 10 pF to 560 nF

- Available capacitance tolerances of ±5%, ±10%, and ±20%
- Low ESR and ESL
- Non-polar device, minimizing installation concerns
- Automotive (AEC-Q200) Grade available
- 100% pure matte tin-plated termination finish allowing for excellent solderability
- SnPb plated termination finish option available upon request (5% Pb minimum)

Applications

Typical applications include switch mode power supplies (input filters, resonators, tank circuits, snubber circuits, output filters), high voltage coupling and DC blocking, lighting ballasts, voltage multiplier circuits, DC/DC converters and coupling capacitors in Ćuk converters. Markets include power supply, LCD fluorescent backlight ballasts, HID lighting, telecom equipment, industrial and medical equipment/control, LAN/WAN interface, analog and digital modems, and automotive (electric and hybrid vehicles, charging stations and lighting applications).


Application Note

X7R dielectric is not recommended for AC line filtering or pulse applications. These capacitors and/or the assembled circuit board containing these capacitors may require a protective surface coating to prevent external surface arcing.

¹ The terms "Marked" and "Unmarked" pertain to laser marking option of capacitors. All packaging options labeled as "Unmarked" will contain capacitors that have not been laser marked. Please contact KEMET if you require a laser marked option. For more information see "Capacitor Marking".



Dimensions - Millimeters (Inches)



EIA Size Code	Metric Size Code	L Length	W Width	T Thickness	B Bandwidth	S Separation Minimum	Mounting Technique
0402	1005	1.00 (0.040) ±0.05 (0.002)	0.50 (0.020) ±0.05 (0.002)		0.30 (0.012) ±0.10 (0.004)	0.30 (0.012)	Solder Reflow Only
0603	1608	1.60 (0.063) ±0.15 (0.006)	0.80 (0.032) ±0.15 (0.006)		0.35 (0.014) ±0.15 (0.006)	0.50 (0.020)	
0805	2012	2.00 (0.079) ±0.20 (0.008)	1.25 (0.049) ±0.20 (0.008)		0.50 (0.02) ±0.25 (0.010)	0.70 (0.028)	Solder Wave or Solder Reflow
1206	3216	3.20 (0.126) ±0.20 (0.008)	1.60 (0.063) ±0.20 (0.008)		0.50 (0.02) ±0.25 (0.010)	1.50 (0.060)	
1210	3225	3.20 (0.126) ±0.20 (0.008)	2.50 (0.098) ±0.20 (0.008)	See Table 2 for	0.50 (0.02) ±0.25 (0.010)	1.50 (0.060)	
1808	4520	4.70 (0.185) ±0.50 (0.020)	2.00 (0.079) ±0.20 (0.008)	Thickness	0.60 (0.024) ±0.35 (0.014)	2.90 (0.114)	
1812	4532	4.50 (0.177) ±0.30 (0.012)	3.20 (0.126) ±0.30 (0.012)		0.60 (0.024) ±0.35 (0.014)	2.30 (0.091)	Solder Reflow
1825	4564	4.50 (0.177) ±0.30 (0.012)	6.40 (0.252) ±0.40 (0.016)		0.60 (0.024) ±0.35 (0.014)	2.30 (0.091)	Only
2220	5650	5.70 (0.224) ±0.40 (0.016)	5.00 (0.197) ±0.40 (0.016)		0.60 (0.024) ±0.35 (0.014)	3.50 (0.138)	
2225	5664	5.60 (0.220) ±0.40 (0.016)	6.40 (0.248) ±0.40 (0.016)		0.60 (0.024) ±0.35 (0.014)	3.20 (0.126)	

Qualification/Certification

Commercial Grade products are subject to internal qualification. Details regarding test methods and conditions are referenced in Table 4, Performance & Reliability.

Environmental Compliance

Lead (Pb)-free, RoHS, and REACH compliant without exemptions (excluding SnPb termination finish option).



Table 1A - Capacitance Range/Selection Waterfall (0603 - 1812 Case Sizes)

			se S Serie		C0402C	C	060	3C	CO	80			C.	1206	5C			C	1210	C				C 1	1808	ВС					C1	812	C ²		
Con	Сар	Vol	tage (Code	С	С	В	D	С	В	D	С	В	D	F	G	С	В	D	F	G	С	В	D	F	G	Z	Н	С	В	D	F	G	Z	н
Cap	Code	Rate		Itage	200	200	630	000	200	630	1000	200	630	1000	200	2000	200	630	1000	1500	2000	200	930	1000	1500	2000	2500	3000	200	930	1000	1500	2000	2500	3000
			(VDC	ance	. r.	L	9	· •	odu								_				_										=	~		5	<u>بج</u>
10 pF	100	J	lera:	M					DG	DG	DG	ED	ED	ED	ED.				FM			LB	LB	LB	LB	LB	LB	LB	GK	GK	GK	GK	GK	GK	GK
11 pF	110	J	K	М					DG	DG	DG	ED	ED	ED	ED	ED	FM	FM	FM	FM	FM	LB	LB	LB	LB	LB	LB	LB	GK	GK	GK	GK	GK	GK	GK
12 pF	120	J	K	M					DG	DG	DG	ED	ED	ED	ED	ED		FM	FM	FM	FM	LB	LB	LB	LB	LB	LB	LB	GK	GK	GK	GK	GK	GK	GK
13 pF 15 pF	130 150	J	K	M					DG DG	DG DG	DG DG	ED ED	ED ED	ED ED	ED ED	ED ED	FM FM	FM FM	FM FM	FM FM	FM FM	LB LB	LB LB	LB LB	LB LB	LB LB	LB LB	LB LB	GK GK	GK GK	GK GK	GK GK	GK GK	GK GK	GK GK
16 pF	160	J	K	M					DG	DG	DG	ED	ED	ED	ED	ED	FM	FM	FM	FM	FM	LB	LB	LB	LB	LB	LB	LB	GK	GK	GK	GK	GK	GK	GK
18 pF	180	J	K	М		İ			DG	DG	DG	ED	ED	ED	ED	ED	FM	FM	FM	FM	FM	LB	LB	LB	LB	LB	LB	LB	GK	GK	GK	GK	GK	GK	GK
20 pF	200	J	K	М					DG	DG	DG	ED	ED	ED	ED	ED	FM	FM	FM	FM	FM	LB	LB	LB	LB	LB	LB	LB	GK	GK	GK	GK	GK	GK	GK
22 pF	220	IJ	K	M					DG	DG	DG	ED	ED	ED	ED	ED	FM	FM	FM	FM	FM	LB	LB	LB	LB	LB	LB	LB	GK	GK	GK	GK	GK	GK	GK
24 pF 27 pF	240 270	J	K	M					DG DG	DG DG	DG DG	ED ED	ED ED	ED ED	ED ED	ED ED	FM FM	FM FM	FM FM	FM FM	FM FM	LB LB	LB LB	LB LB	LB LB	LB LB	LB LB	LB LB	GK GK	GK GK	GK GK	GK GK	GK GK	GK GK	GK GK
30 pF	300	Ĵ	K	M					DG	DG	DG	ED	ED	ED	ED	ED	FM	FM	FM	FM	FM	LB	LB	LB	LB	LB	LB	LB	GK	GK	GK	GK	GK	GK	GK
33 pF	330	J	K	М					DG	DG	DG	ED	ED	ED	ED	ED	FM	FM	FM	FM	FM	LB	LB	LB	LB	LB	LB	LB	GK	GK	GK	GK	GK	GK	GK
36 pF	360	J	K	М					DG	DG	DG	ED	ED	ED	ED	ED		FM	FM	FM	FM	LB	LB	LB	LB	LB	LB	LB	GK	GK	GK	GK	GK	GK	GK
39 pF	390	J	K	M					DG	DG	DG	ED	ED	ED	ED	ED	FM	FM	FM	FM	FM	LB	LB	LB	LB	LB	LB	LB	GK	GK	GK	GK	GK	GK	GK
43 pF 47 pF	430 470	J	K	M					DG DG	DG DG	DG DG	ED ED	ED ED	ED ED	ED ED	ED ED	FM FM	FM FM	FM FM	FM FM	FM FM	LB LB	LB LB	LB LB	LB LB	LB LB	LB LB	LB LB	GK GK	GK GK	GK GK	GK GK	GK GK	GK GK	GK GK
51 pF	510	Ĵ	K	M					DG	DG	DG	ED	ED	ED	ED	ED	FM	FM	FM	FM	FM	LB	LB	LB	LB	LB	LB	LB	GK	GK	GK	GK	GK	GK	GK
56 pF	560	J	K	М		l			DG	DG	DG	ED	ED	ED	ED	ED	FM	FM	FM	FM	FM	LB	LB	LB	LB	LB	LB	LB	GK	GK	GK	GK	GK	GK	GK
62 pF	620	J	K	М					DG	DG	DG	ED	ED	ED	ED	ED	FM	FM	FM	FM	FM	LB	LB	LB	LB	LB	LB	LB	GK	GK	GK	GK	GK	GK	GK
68 pF	680	J	K	M					DG	DG	DG	ED	ED	ED	ED	ED	FM	FM	FM	FM	FM	LB	LB	LB	LB	LB	LB	LB	GK	GK	GK	GK	GK	GK	GK
75 pF 82 pF	750 820	J	K	M					DG DG	DG DG	DG DG	ED ED	ED ED	ED ED	ED ED	EF EF	FM FM	FM FM	FM FM	FM FM	FM FM	LB LB	LB LB	LB LB	LB LB	LB LB	LB LB	LB LB	GK GK	GK GK	GK GK	GK GK	GK GK	GK GK	GK GK
91 pF	910	J	K	M					DG	DG	DG	ED	ED	ED	ED	EF	FM	FM	FM	FM	FM	LB	LB	LB	LB	LB	LB	LB	GK	GK	GK	GK	GK	GK	GK
100 pF	101	Ĵ	K	М					DG	DG	DG	ED	ED	ED	ED	EF	FM	FM	FM	FM	FM	LB	LB	LB	LB	LB	LC	LB	GK	GK	GK	GK	GK	GK	GK
110 pF	111	J	K	М					DG	DG	DG	ED	ED	ED	ED	EG	FM	FM	FM	FM	FM	LB	LB	LB	LB	LB	LC	LB	GK	GK	GK	GK	GK	GK	GK
120 pF	121	J	K	M					DG	DG	DG	ED	ED	ED	ED	EG	FM	FM	FM	FM	FM	LA	LA	LA	LA	LB	LC	LB	GK	GK	GK	GK	GK	GK	GK
130 pF 150 pF	131 151	J	K	M					DG DG	DG DG	DG DG	ED ED	ED ED	ED ED	ED EF	EG EG	FG FG	FG FG	FG FG	FM FM	FM FM	LA	LA	LA LA	LA	LB LB	LC	LB LB	GK GK	GK GK	GK GK	GK GK	GK GK	GK GK	GK GK
180 pF	181	J	K	M					DG	DG	DG	ED	ED	ED	EF	EG	FG	FG	FG	FM	FM	LA	LA	LA	LA	LC	LC	LB	GK	GK	GK	GK	GK	GK	GK
220 pF	221	J	K	М					DG	DG	DG	ED	ED	ED	EF	EF	FG	FG	FG	FM	FM	LA	LA	LA	LA	LC	LC	LB	GH	GH	GH	GH	GH	GK	GK
270 pF	271	J	K	М					DG	DG	DG	ED	ED	ED	EF	EF	FG	FG	FG	FK	FK	LA	LA	LA	LB	LC	LC	LC	GH	GH	GH	GH	GH	GK	GK
330 pF	331	J	K	M					DG	DG	DG	ED	ED	EF	EF	EF	FG	FG	FG	FK	FK	LA	LA	LA	LB	LC	LC	LC	GH	GH	GH	GH	GH	GK	GK
390 pF 470 pF	391 471	J	K	M					DG DG	DG DG	DG DG	ED ED	ED ED	EF EF	EF EF	EF EF	FG FG	FG FM	FG FM	FK FS	FS FS	LA	LA LB	LA LB	LB	LB LB	LB LB	LC	GK GK	GK GK	GK GK	GK GK	GK GK	GK GK	GK GK
560 pF	561	J	K	M					DG	DG	DG	ED	ED	EF	EF	EF	FG	FM	FM	FS	FL	LA	LB	LB	LC	LB	LB	LC	GH	GH	GH	GK	GH	GK	GK
680 pF	681	Ĵ	K	М					DG	DG	DG	ED	ED	EF	EF	EF	FG	FM	FM	FS	FL	LB	LB	LB	LA	LB	LC	LC	GH	GH	GH	GK	GH	GK	GK
820 pF	821	J	K	М					DG	DG	DG	ED	ED	ED	EF	EF	FG	FM	FM	FL	FL	LB	LB	LB	LA	LB	LC	LC	GH	GH	GH	GK	GH	GK	GK
1,000 pF	102	J	K	М	BB	CG	CG	CG	DG	DG	DG	ED	ED	ED	EF	EF	FM	FM	FM	FL	FL	LB	LB	LB	LA	LB	LC	LC	GH	GH	GH	GH	GH	GK	GK
1,200 pF	122	J	K	M	BB BD	CG	CG		DG	DG	DG	ED	ED	ED	EG	EG	FM	FK	FK	FL	FM	_	LC	LC	LB	LC	LA		GH GK	GK	GK	GH	GH	GK	GK
1,500 pF 1,800 pF	152 182	.1	K	M	ΒÜ	CG	CG		DG DG	DG DG	DG DG	ED ED	ED ED	ED ED	EG EG	EG EG	FK FK	FS FS	FS FS	FL FL	FM FM		LC	LC LC	LB LB	LC	LB LC		GK		GK GK	GH GH		GK GK	
2,200 pF	222	J	K	M		CG			DG		DG		ED	ED	EG	EG	FK	FL	FL	FL	FM	LC	LA	LA	LB	LC	LC		GK		GK				
2,700 pF	272	J	K	М		CG			DG	DG	DG	ED	ED	ED	EG		FS	FL	FL	FL	FM	LC	LA	LA	LB	LC			GK	GH	GH	GH	GK	GM	
3,300 pF	332	J	K	M		CG			DG	DG	DG		ED	ED	EG		FS	FL	FL	FL	FM	LA	LA	LA	LB	LA			GK		GH				
3,900 pF 4,700 pF	392	IJ	K	M		CG			DG DG	DG DG	DG DG		ED ED	ED ED	EG		FL	FL FL	FL FL	FL FL	FK FK	LA	LA	LA	LB	LB			GK	1			GM GH		
5,600 pF	472 562	.1	K	M					DG	DG	טט	ED	EF	EF	EG EF		FL FL	FL	FL	FM	FK	LA LA	LA LB	LA LB	LB LC	LC			GH GH		GH			GU	
6,800 pF	682	ľ	K	M					DG	DG		EF	EF	EF	EF		FL	FL	FL	FM	FS	LA	LB	LB	LC				GH		GH				
8,200 pF	822	J	K	М					DG	DG		EF	EG	EG	EF		FL	FL	FL	FK		LA	LB	LB	LC				GH	GH	GH	GK	GM		
10,000 pF	103	J	K	М				_	DG	DG	_	EF	EG	EG	EG	_	FL	FL	FL	FK	_	LA	LB	LB		_	_	_	_	_	GH			_	
		Rate	ed Vo (VDC	ltage ;)	200	200	630	1000	200	630	1000	200	630	1000	1500	2000	200	630	1000	1500	2000	200	630	1000	1500	2000	2500	3000	200	630	1000	1500	2000	2500	3000
Cap	Cap Code			Code	С	С	В	D	С	В	D	С	В	D	F	G	С	В	D	F	G	С	В	D	F	G	Z	Н	С	В	D	F	G	Z	Н
			se S Serie		C0402C	С	060	3C	C	0805			C	1206	C			C	1210	С				C.	1808	3C					C1	812	C ²		

KEMET reserves the right to substitute product with an improved temperature characteristic, tighter capacitance tolerance and/or higher voltage capability within the same form factor (configuration and dimensions).

² Available capacitance values available in <u>X7R with KONNEKT Technology</u>.



Table 1A - Capacitance Range/Selection Waterfall (0603 - 1812 Case Sizes) cont.

		Cas S	e Si erie		C0402C	C	0603	3C	C	080	5C		C.	1200	5C			C.	1210	OC				C1	1808	ВС					C1	1812	C ²		
Cap	Cap					С	В	D	С	В	D	С	В	D	F	G	С	В	D	F	G	С	В	D	F	G	Z	Н	С	В	D	F	G	Z	н
Сар	Code	Rate	d Vol	tage)	500	200	630	1000	200	630	1000	200	630	1000	1500	2000	200	630	1000	1500	2000	200	630	1000	1500	2000	2500	3000	200	630	1000	1500	2000	2500	3000
		Cap: Tol	acita eran					Pı	rodu	ct A	vaila	bilit	y an	d Cl	nip T	hick	nes	s Co	des	- Se	e Ta	ble	2 for	Chi	p Th	ickr	iess	Dim	ensi	ions					
12,000 pF	123	J	K	М					DG	DG		EG	EJ	EJ			FL	FL	FL	FK		LA	LC	LC	LB				GH	GK	GK	GK			
15,000 pF	153	J	K	М					DG			EG	EJ	EJ			FL	FL	FL	FL		LA	LC	LC	LC				GH	GK	GK	GH			
18,000 pF	183	J	K	М					DG			EJ	EJ	EJ			FL	FL	FL	FM		LA	LE	LE					GH	GK	GK				
22,000 pF	223	J	K	М					DG			EJ	EJ	EJ			FL	FM	FM			LA	LE	LE					GH	GK	GK				
27,000 pF	273	J	K	М								EJ	EJ				FM	FK	FK	FK		LA	LA	LA					GH	GB	GB				
33,000 pF	333	J	K	М								EJ	EJ				FM	FG	FH	FS		LC	LA	LA					GH	GB	GB	GO			
39,000 pF	393	J	K	М								EJ					FK	FG	FH	FS		LC	LA	LA					GH	GB	GB				
47,000 pF	473	J	K	М								EJ					FK	FH	FK			LC	LA	LB					GH	GB	GC				
56,000 pF	563	J	K	М								EJ					FG	FH	FK			LC	LA	LB					GH	GB	GE				
68,000 pF	683	J	K	М								EJ					FG	FK	FS			LA	LA	LC					GE	GE	GE				
82,000 pF	823	J	K	М													FH	FK				LA	LC						GB	GE	GK				
0.10 μF	104	J	K	М													FK	FS				LA	LC						GB	GH	GJ				
0.12 μF	124	J	K	М													FK					LA							GE	GK					
0.15 μF	154	J	K	М													FK					LB							GE	GN					
0.18 µF	184	J	K	М																		l							GF						
0.22 µF	224	J	K	М																									GJ						
0.27 μF	274	J	K	М																									GL						
0.33 μF	334	J	K	М				_	<u> </u>		_		_	_	_	_	_		_	_	_	┝	_	_	_	_	_	_	GS		_	_	_	_	_
		Rate	d Vol VDC	-	500	200	630	1000	200	630	1000	200	630	1000	1500	2000	200	630	1000	1500	2000	200	630	1000	1500	2000	2500	3000	200	630	1000	1500	2000	2500	3000
Cap	Cap Code	Volta	age C	Code	С	С	В	D	С	В	D	С	В	D	F	G	С	В	D	F	G	С	В	D	F	G	Z	Н	С	В	D	F	G	Z	н
	Joue	Cas S	e Si erie		C0402C	C	0603	3C	С	080	SC		C	1206	C			С	1210	С				C	1808	3C					C	1812	C ²		

Table 1B - Capacitance Range/Selection Waterfall (1825-2225 Case Sizes)

			se Si Serie				С	1825	5C					C	2220	C					C	222	5C		
Canacitance	Cap	Vo	ltage C	ode	С	В	D	F	G	Z	Н	С	В	D	F	G	Z	Н	С	В	D	F	G	Z	Н
Capacitance	Code	Rated	Voltage	(VDC)	200	630	1000	1500	2000	2500	3000	200	630	1000	1500	2000	2500	3000	200	630	1000	1500	2000	2500	3000
			pacita: Toleran				Produ	ıct Av	ailabi	lity a	nd Ch	ip Thi	ckne	ss Co	des -	See 7	Table	2 for	Chip	Thick	ness	Dime	nsion	3	
100 pF	101	J	K	М	HG	HG	HG	HG	HG	HG	HG	JK	JK	JK	JK	JK	JK	JK	KF	KF	KF	KF	KF	KF	KF
110 pF	111	J	K	M	HG	HG	HG	HG	HG	HG	HG	JK	JK	JK	JK	JK	JK	JK	KF	KF	KF	KF	KF	KF	KF
120 pF	121	J	K	M	HG	HG	HG	HG	HG	HG	HG	JK	JK	JK	JK	JK	JK	JK	KF	KF	KF	KF	KF	KF	KF
130 pF	131	J	K	M	HG	HG	HG	HG	HG	HG	HG	JK	JK	JK	JK	JK	JK	JK	KF	KF	KF	KF	KF	KF	KF
150 pF	151	J	K	M	HG	HG	HG	HG	HG	HG	HG	JK	JK	JK	JK	JK	JK	JK	KF	KF	KF	KF	KF	KF	KF
180 pF	181	J	K	M	HG	HG	HG	HG	HG	HG	HG	JK	JK	JK	JK	JK	JK	JK	KF	KF	KF	KF	KF	KF	KF
220 pF	221	J	K	M	HE	HE	HE	HE	HE	HE	HG	JK	JK	JK	JK	JK	JK	JK	KF	KF	KF	KF	KF	KF	KF
270 pF	271	J	K	M	HE	HE	HE	HE	HE	HE	HG	JK	JK	JK	JK	JK	JK	JK	KE	KE	KE	KE	KE	KE	KF
330 pF	331	J	K	M								JE	JE	JE	JE	JE	JK	JK	KE	KE	KE	KE	KE	KE	KF
390 pF	391	J	K	M								JE	JE	JE	JE	JE	JK	JK	KE	KE	KE	KE	KE	KE	KF
470 pF	471	J	K	M	HG	HG	HG	HG	HG	HG	HG	JE	JE	JE	JE	JE	JK	JK	KF	KF	KF	KF	KE	KE	KF
560 pF	561	J	K	M	HG	HG	HG	HG	HG	HG	HG	JK	JK	JK	JK	JK	JK	JK	KF	KF	KF	KF	KE	KE	KF
680 pF	681	J	K	M	HG	HG	HG	HG	HG	HG	HG	JE	JE	JE	JK	JK	JK	JK	KF	KF	KF	KF	KE	KF	KF
820 pF	821	J	K	M	HG	HG	HG	HG	HG	HG	HG	JE	JE	JE	JK	JK	JK	JK	KE	KE	KE	KF	KE	KF	KF
		Rated	Voltage	(VDC)	200	630	1000	1500	2000	2500	3000	200	630	1000	1500	2000	2500	3000	200	630	1000	1500	2000	2500	3000
Capacitance	Cap Code	Vo	ltage C	ode	С	В	D	F	G	Z	Н	С	В	D	F	G	Z	н	С	В	D	F	G	Z	Н
		Case	Size/	Series			(1825	С	,				C	2220	С					C	2225	С		

KEMET reserves the right to substitute product with an improved temperature characteristic, tighter capacitance tolerance and/or higher voltage capability within the same form factor (configuration and dimensions).

² Available capacitance values available in X7R with KONNEKT Technology.



Table 1B - Capacitance Range/Selection Waterfall (1825 - 2225 Case Sizes) cont.

			se Si Serie	-			C	182	5C					C	2220	C					C	222	5C		
Capacitance	Cap	Vo	Itage C	ode	С	В	D	F	G	Z	Н	С	В	D	F	G	Z	н	С	В	D	F	G	Z	Н
Capacitance	Code	Rated	Voltage	(VDC)	200	630	1000	1500	2000	2500	3000	200	630	1000	1500	2000	2500	3000	200	630	1000	1500	2000	2500	3000
			pacitar Tolerand			ı	Produ	ict Av	ailabi	lity aı	nd Ch	ip Thi	ckne	ss Co	des -	See '	Гablе	2 for	Chip 1	Thick	ness	Dime	nsion	S	
1,000 pF	102	J	K	М	HG	HG	HG	HG	HG	HG	HG	JE	JK	JK	JK	JK	JK	JK	KE	KE	KE	KF	KE	KF	KF
1,200 pF	122	J	K	M	HG	HG	HG	HG	HG	HG	HG	JE	JK	JK	JK	JK	JK	JK	KE	KE	KE	KF	KF	KF	KF
1,500 pF	152	J	K	M	HG	HG	HG	HG	HG	HG	HG	JE	JK	JK	JK	JK	JK	JK	KE	KE	KE	KF	KF	KF	KF
1,800 pF	182	J	K	М	HE	HE	HE	HE	HE	HG	HG	JE	JK	JK	JK	JK	JK	JK	KE	KE	KE	KF	KF	KF	KF
2,200 pF	222	J	K	М	HE	HE	HE	HE	HE	HG	HG	JE	JK	JK	JE	JE	JK	JK	KF	KE	KE	KF	KF	KF	KF
2,700 pF	272	J	K	м	HE	HE	HE	HE	HE	HG		JK	JK	JK	JE	JE	JK	JK	KE	KE	KE	KE	KE	KF	KE
3,300 pF	332	J	K	M	HE	HE	HE	HE	HE	HG		JK	JK	JK	JE	JE	JK	JE	KE	KE	KE	KE	KE	KF	KE
3,900 pF	392	Ĵ	K	M	HE	HE	HE	HE	HE	HG		JK	JK	JK	JE	JE	JK	JE	KE	KF	KF	KE	KE	KF	KE
4,700 pF	472	J	K	M	HE	HE	HE	HE	HE	HG		JK	JK	JK	JE	JK	JE	JE	KE	KF	KF	KE	KE	KF	KE
5,600 pF	562	J	K	M	HE	HE	HE	HE	HE	HG		JK	JK	JK	JE	JK	JE	JE	KE	KF	KF	KE	KE	KF	KE
6,800 pF	682	Ĵ	K	M	HE	HE	HE	HE	HE	HJ		JK	JE	JE	JE	JK	JE	JE	KE	KF	KF	KE	KF	KE	KE
8,200 pF	822	Ĵ	K	M	HE	HE	HE	HE	HE	HJ		JK	JE	JE	JE	JK	JK	JK	KF	KE	KE	KE	KF	KF	KF
10,000 pF	103	Ĵ	K	M	HE	HE	HE	HE	HJ	НК		JE	JE	JE	JE	JL	JL	JL	KF	KE	KE	KE	KF	KH	KH
12,000 pF	123	Ĵ	K	M	HE	HE	HE	HG	HJ			JE	JK	JK	JK	JL	JL	JL	KE	KE	KE	KE	KF	KH	KH
15,000 pF	153	Ĵ	K	M	HE	HE	HE	HG	HK			JE	JK	JK	JK	JL	JN	JN	KE	KE	KE	KE	KF	KJ	KJ
18,000 pF	183	J	K	M	HE	HE	HE	HG	1111			JE	JK	JK	JK	JN	314	JIN	KE	KE	KE	KE	KH	INO	IX.
22,000 pF	223	J	K	M	HE	HG	HG	HG				JE	JK	JK	JK	JN			KE	KF	KF	KF	KJ		
27,000 pF	273	J	K	M	HE	HG	HG	HG				JE	JK	JK	JK	JIN			KE	KF	KF	KF	KJ		
33,000 pF	333	J	K	M	HE	HG	HG	HE				JE	JK	JK	JK				KE	KF	KF	KF	KJ		
	393	J	K	M	HE	HG	HG	HG				JE	JK	JK	JE				KE	KF	KF	KF			
39,000 pF	473	J	K	M	HE	HG	HG	НJ				JE	JK	JK	JK				KE	KF	KF	KF			
47,000 pF	-					HG	-						-	JE	-					KF	KF	KF			
56,000 pF	563	J	K	M	HE		HG	HJ				JE	JE		JL				KE						
68,000 pF	683	J	K	M	HG	HJ	HJ	HK				JE	JK	JK	JL				KE	KF	KF	KJ			
82,000 pF	823	J	K	M	HG	HJ	HJ					JE	JL	JL	JN				KE	KF	KF	KJ			
0.10 μF	104	J	K	M	HG	HK	HK					JE	JN	JN					KE	KH	KH	KJ			
0.12 μF	124	J	K	M	HG	HE						JE	JN	JN					KE	KH	KH				
0.15 μF	154	J	K	M	HG	HE						JK	JE						KF	KJ	KJ				
0.18 μF	184	J	K	M	HG	HG						JK	JE						KF	KE					
0.22 μF	224	J	K	M	HG	HJ						JK	JK						KF	KF					
0.27 μF	274	J	K	M	HJ	HJ						JK	JL						KF	KH					
0.33 μF	334	J	K	M	HJ							JL	JN						KF	KH					
0.39 μF	394	J	K	M	HK							JN							KH	KJ					
0.47 μF	474	J	K	M								JN							KH	KJ					
0.56 μF	564	J	K	M															KJ						
		Rated	Voltage	e (VDC)	500	630	1000	1500	2000	2500	3000	500	630	1000	1500	2000	2500	3000	200	630	1000	1500	2000	2500	3000
Capacitance	Cap Code	Vo	ltage C	С	В	D	F	G	Z	Н	С	В	D	F	G	Z	Н	С	В	D	F	G	Z	Н	
		Case	Size/ S				1825	С					C	2220	С					С	2225	С			

KEMET reserves the right to substitute product with an improved temperature characteristic, tighter capacitance tolerance and/or higher voltage capability within the same form factor (configuration and dimensions).



Table 2A - Chip Thickness/Tape & Reel Packaging Quantities

Thickness	Case	Thickness ±	Paper C	Quantity	Plastic (Quantity
Code	Size ¹	Range (mm)	7" Reel	13" Reel	7" Reel	13" Reel
BB	0402	0.50 ± 0.05	10000	50000	0	0
BD	0402	0.55 ± 0.05	10000	50000	0	0
CG	0603	0.80 ± 0.10	4,000	15,000	0	0
DG	0805	1.25 ± 0.15	0	0	2,500	10,000
ED	1206	1.00 ± 0.10	0	0	2,500	10,000
EF	1206	1.20 ± 0.15	0	0	2,500	10,000
EG	1206	1.60 ± 0.15	0	0	2,000	8,000
EJ	1206	1.70 ± 0.20	0	0	2,000	8,000
FG	1210	1.25 ± 0.15	0	0	2,500	10,000
FL	1210	1.40 ± 0.15	0	0	2,000	8,000
FH FM	1210 1210	1.55 ± 0.15 1.70 ± 0.20	0 0	0 0	2,000	8,000
FK	1210	2.10 ± 0.20	0	0	2,000 2.000	8,000 8.000
FS	1210	2.50 ± 0.20 2.50 ± 0.30	0	0	1,000	4,000
LE	1808	1.00 ± 0.10	0	0	2,500	10,000
LA	1808	1.40 ± 0.15	0	0	1,000	4,000
LB	1808	1.60 ± 0.15	Ö	Ö	1,000	4,000
LC	1808	2.00 ± 0.15	0	ő	1,000	4,000
GB	1812	1.00 ± 0.10	Ö	Ö	1,000	4,000
GC	1812	1.10 ± 0.10	Ö	0	1,000	4,000
GE	1812	1.30 ± 0.10	0	0	1,000	4,000
GH	1812	1.40 ± 0.15	0	0	1,000	4,000
GF	1812	1.50 ± 0.10	0	0	1,000	4,000
GK	1812	1.60 ± 0.20	0	0	1,000	4,000
GJ	1812	1.70 ± 0.15	0	0	1,000	4,000
GN	1812	1.70 ± 0.20	0	0	1,000	4,000
GL	1812	1.90 ± 0.20	0	0	500	2,000
GM	1812	2.00 ± 0.20	0	0	500	2,000
GS	1812	2.10 ± 0.20	0	0	500	2,000
G0	1812	2.50 ± 0.20	0	0	500	2,000
HE	1825	1.40 ± 0.15	0	0	1,000	4,000
HG	1825	1.60 ± 0.20	0	0	1,000	4,000
HJ	1825	2.00 ± 0.20	0	0	500	2,000
HK	1825	2.50 ± 0.20	0	0	500	2,000
JE	2220	1.40 ± 0.15	0	0	1,000	4,000
JK	2220	1.60 ± 0.20	0	0	1,000	4,000
JL	2220	2.00 ± 0.20	0	0	500	2,000
JN KE	2220 2225	2.50 ± 0.20 1.40 ± 0.15	0 0	0 0	500 1,000	2,000
I KE	2225	1.40 ± 0.15 1.60 ± 0.20	0	0	1,000	4,000 4,000
KH	2225	2.00 ± 0.20	0	0	500	2,000
KJ	2225	2.50 ± 0.20 2.50 ± 0.20	0	0	500	2,000
Thickness	Case	Thickness ±	7" Reel	13" Reel	7" Reel	13" Reel
Code	Size ¹	Range (mm)	Paper Q	uantity ¹	Plastic (Quantity

Package quantity based on finished chip thickness specifications.



Table 2B - Bulk Packaging Quantities

Dookse	ving Type	Loose P	ackaging
Раска	jing Type	Bulk Bag	(default)
Packagi	ng C-Spec ¹	N,	/A ²
Cas	e Size	Packaging Quantities (pieces/unit packaging)
EIA (in)	Metric (mm)	Minimum	Maximum
0402	1005		
0603	1608		
0805	2012		50,000
1206	3216		
1210	3225	1	
1808	4520	ľ	
1812	4532		
1825	4564		20,000
2220	5650		
2225	5664		

¹ The "Packaging C-Spec" is a 4 to 8 digit code which identifies the packaging type and/or product grade. When ordering, the proper code must be included in the 15th through 22nd character positions of the ordering code. See "Ordering Information" section of this document for further details. Commercial Grade product ordered without a packaging C-Spec will default to our standard "Bulk Bag" packaging. Contact KEMET if you require a bulk bag packaging option for Automotive Grade products.

² A packaging C-Spec (see note 1 above) is not required for "Bulk Bag" packaging (excluding Anti-Static Bulk Bag and Automotive Grade products). The 15th through 22nd character positions of the ordering code should be left blank. All product ordered without a packaging C-Spec will default to our standard "Bulk Bag" packaging.




Table 3 - Chip Capacitor Land Pattern Design Recommendations per IPC-7351

EIA Size Code	Metric Size Code	ı	Maxi	sity Lev mum (I rotrusio	Most))		Media	sity Lev an (Nor rotrusio)			sity Lev mum (L rotrusio	.east))
Coue	Code	С	Y	X	V1	V2	С	Y	X	V1	V2	С	Υ	X	V1	V2
0402	1005	0.50	0.72	0.72	2.20	1.20	0.45	0.62	0.62	1.90	1.00	0.40	0.52	0.52	1.60	0.80
0603	1608	0.90	1.15	1.10	4.00	2.10	0.80	0.95	1.00	3.10	1.50	0.60	0.75	0.90	2.40	1.20
0805	2012	1.00	1.35	1.55	4.40	2.60	0.90	1.15	1.45	3.50	2.00	0.75	1.50	1.35	2.80	1.70
1206	3216	1.60	1.35	1.90	5.60	2.90	1.50	1.15	1.80	4.70	2.30	1.40	0.95	1.70	4.00	2.00
1210	3225	1.60	1.35	2.80	5.65	3.80	1.50	1.15	2.70	4.70	3.20	1.40	0.95	2.60	4.00	2.90
1808	4520	2.30	1.75	2.30	7.40	3.30	2.20	1.55	2.20	6.50	2.70	2.10	1.35	2.10	5.80	2.40
1812	4532	2.15	1.60	3.60	6.90	4.60	2.05	1.40	3.50	6.00	4.00	1.95	1.20	3.40	5.30	3.70
1825	4564	2.15	1.60	6.90	6.90	7.90	2.05	1.40	6.80	6.00	7.30	1.95	1.20	6.70	5.30	7.00
2220	5650	2.75	1.70	5.50	8.20	6.50	2.65	1.50	5.40	7.30	5.90	2.55	1.30	5.30	6.60	5.60
2225	5664	2.70	1.70	6.90	8.10	7.90	2.60	1.50	6.80	7.20	7.30	2.50	1.30	6.70	6.50	7.00

Density Level A: For low-density product applications. Recommended for wave solder applications and provides a wider process window for reflow solder processes. KEMET only recommends wave soldering of EIA 0603, 0805 and 1206 case sizes.

Density Level B: For products with a moderate level of component density. Provides a robust solder attachment condition for reflow solder processes. **Density Level C:** For high component density product applications. Before adapting the minimum land pattern variations the user should perform qualification testing based on the conditions outlined in IPC Standard 7351 (IPC-7351).

Image below based on Density Level B for an EIA 1210 case size.





Soldering Process

Recommended Soldering Technique:

- Solder wave or solder reflow for EIA case sizes 0603, 0805 and 1206
- · All other EIA case sizes are limited to solder reflow only

Recommended Reflow Soldering Profile:

KEMET's families of surface mount multilayer ceramic capacitors (SMD MLCCs) are compatible with wave (single or dual), convection, IR or vapor phase reflow techniques. Preheating of these components is recommended to avoid extreme thermal stress. KEMET's recommended profile conditions for convection and IR reflow reflect the profile conditions of the IPC/ J-STD-020 standard for moisture sensitivity testing. These devices can safely withstand a maximum of three reflow passes at these conditions.

Profile Feature	Terminat	ion Finish
1 Tome Teature	SnPb	100% Matte Sn
Preheat/Soak		
Temperature Minimum (T _{Smin})	100°C	150°C
Temperature Maximum (T _{Smax})	150°C	200°C
Time (t_s) from T_{smin} to T_{smax}	60 - 120 seconds	60 - 120 seconds
Ramp-Up Rate $(T_L \text{ to } T_p)$	3°C/second maximum	3°C/second maximum
Liquidous Temperature (T_L)	183°C	217°C
Time Above Liquidous (t _L)	60 - 150 seconds	60 - 150 seconds
Peak Temperature (T _P)	235°C	260°C
Time Within 5°C of Maximum Peak Temperature (t _p)	20 seconds maximum	30 seconds maximum
Ramp-Down Rate (T _P to T _L)	6°C/second maximum	6°C/second maximum
Time 25°C to Peak Temperature	6 minutes maximum	8 minutes maximum

Note 1: All temperatures refer to the center of the package, measured on the capacitor body surface that is facing up during assembly reflow.






Table 4 - Performance & Reliability: Test Methods and Conditions

Stress	Reference	Test Condition	Limits
Visual and Mechanical	KEMET Internal	No defects that may affect performance (10X)	Dimensions according KEMET Spec Sheet
Capacitance (Cap)	KEMET Internal	C ≤ 10 µF 1 kHz ±50 Hz and 1.0 ±0.2 V _{rms} or 0.5 ±0.2 V _{rms} * C > 10 µF120 Hz ±10 Hz and 0.5 ±0.1 V _{rms} * See part number specification sheet for voltage Capacitance measurements (including tolerance) are indexed to a referee time of 48 or 1,000 hours Please refer to a part number specification sheet for referee time details	Within Tolerance
Dissipation Factor (DF)	KEMET Internal	C \leq 10 μF Frequency: 1 kHz \pm 50 Hz Voltage*:1.0 \pm 0.2 V _{rms} , 0.5 \pm 0.2 V _{rms} , C > 10 μF Frequency: 120 Hz \pm 10 Hz Voltage: 0.5 \pm 0.1 V _{rms} * See part number specification sheet for voltage	Within Specification Dissipation factor (DF) maximum limit at 25°C = 2.5%
Insulation Resistance (IR)	KEMET Internal	500 VDC applied for 120 ±5 seconds at 25°C	Within Specification To obtain IR limit, divide MΩ-μF value by the capacitance and compare to GΩ limit. Select the lower of the two limits.
Temperature Coefficient of Capacitance (TCC)	KEMET Internal	C ≤ 10 μF Frequency: 1 kHz ±50 Hz Voltage*: 1.0 ±0.2 V _{rms} , 0.5 ±0.2 V _{rms} , 0.2 ±0.1 V _{rms} C > 10 μF Frequency: 120 Hz ±10 Hz Voltage: 0.5 ±0.1 V _{rms} * See part number specification sheet for voltage Step Temperature (°C)	Capacitance ±15% over -55°C to +125°C



Table 4 – Performance & Reliability: Test Methods and Conditions cont.

Reference	Test Cor	Limits		
	(5 ±1 second and charge/discha	arge not exc	eeding 50 mA)	
	Case Size 500 V	630 V	≥ 1,000 V	
	0402 120% of rated voltage	N/A	N/A	Cap: Initial Limit DF: Initial Limit
KEMET Internal	0805 1206 1210	1206 1210 1808 150% of rated voltage 120% of rated voltage 1812 1825 2220 120% of rated voltage 120%		IR: Initial Limit IR: Initial Limit Withstand test voltage without insulation breakdown or damage.
KEMET Internal	indexed to a referee time Please refer to a part numb	e of 48 or 1, er specific	000 hours.	Please refer to a part number specification sheet for specific Aging rate
KEMET Internal		No evidence of mechanical damage		
AEC-Q200-005	Standard Termination System 2.0 mm Flexible Termination System 3.0 mm Test Time: 60± 5 seconds Ramp Time: 1 mm/second	No evidence of mechanical damage		
J-STD-002	155°C dry bake apply all method	Visual Inspection. 95% coverage on termination. No leaching		
JESD22 Method JA-104	1,000 cycles (-55°C to +125°C) 2 - 3 cycles per hour Soak Time: 1 or 5 minute	Measurement at 24 hours ±4 hours after test conclusion. Cap: Initial Limit DF: Initial Limit IR: Initial Limit		
MIL-STD-202 Method 103	200 VDC maximum	Measurement at 24 hours ±4 hours after test conclusion. Within Post Environmental Limits Cap: ±20% shift IR: 10% of Initial Limit DF Limit Maximum: 3.0%		
	KEMET Internal KEMET Internal AEC-Q200-005 J-STD-002 JESD22 Method JA-104	See Dielectric Withstanding Vol (5 ±1 second and charge/dische EIA Case Size 500 V 0402 120% of rated voltage 0603 1206 1210 1808 150% of rated voltage 1206 1210 1808 1812 1825 2220 2225 1825	See Dielectric Withstanding Voltage (DWV) (5 ±1 second and charge/discharge not exc EIA	See Dielectric Withstanding Voltage (DWV) Table (5 ±1 second and charge/discharge not exceeding 50 mA) EIA Case Size 500 V 630 V ≥1,000 V



Table 4 - Performance & Reliability: Test Methods and Conditions


Stress	Reference	Test Condition	Limits
Moisture Resistance	MIL-STD-202 Method 106	Number of Cycles Required: 10, 24 hours per cycle. Steps 7a and 7b not required	Measurement at 24 hours ±4 hours after test conclusion. Within Post Environmental Limits Cap: ±20% shift IR: 10% of Initial Limit DF Limit Maximum: 3.0%
Thermal Shock	MIL-STD-202 Method 107	Number of Cycles Required: 5, (-55°C to 125°C) Dwell time 15 minutes.	Cap: Initial Limit DF: Initial Limit IR: Initial Limit
High Temperature Life	MIL-STD-202	1,000 hours at 125°C with 1.2 X rated voltage applied.	Within Post Environmental Limits Cap: ±20% shift
Storage Life	Method 108	1,000 hours at 150°C, Unpowered	IR: 10% of Initial Limit DF Limit Maximum: 3.0%
Vibration	MIL-STD-202 Method 204	5 g's for 20 minutes, 12 cycles each of 3 orientations. Test from 10 – 2,000 Hz	Cap: Initial Limit DF: Initial Limit IR: Initial Limit
Mechanical Shock	MIL-STD-202 Method 213	1,500 g's 0.5 millisecond Half-sine, Velocity Change: 15.4 feet/second (Condition F)	Cap: Initial Limit DF: Initial Limit IR: Initial Limit
Resistance to Solvents	MIL-STD-202 Method 215	Add Aqueous wash chemical OKEMCLEAN (A 6% concentrated Oakite cleaner) or equivalent. Do not use banned solvents.	Visual Inspection 10X Readable marking, no decoloration or stains. No physical damage.

Storage and Handling

Ceramic chip capacitors should be stored in normal working environments. While the chips themselves are quite robust in other environments, solderability will be degraded by exposure to high temperatures, high humidity, corrosive atmospheres, and long term storage. In addition, packaging materials will be degraded by high temperature—reels may soften or warp and tape peel force may increase. KEMET recommends that maximum storage temperature not exceed 40°C and maximum storage humidity not exceed 70% relative humidity. Temperature fluctuations should be minimized to avoid condensation on the parts and atmospheres should be free of chlorine and sulfur bearing compounds. For optimized solderability chip stock should be used promptly, preferably within 1.5 years of receipt.



Construction





Capacitor Marking (Optional)


These surface mount multilayer ceramic capacitors are normally supplied unmarked. If required, they can be marked as an extra cost option. Marking is available on most KEMET devices, but must be requested using the correct ordering code identifier(s). If this option is requested, two sides of the ceramic body will be laser marked with a "K" to identify KEMET, followed by two characters (per EIA–198 - see table below) to identify the capacitance value. EIA 0603 case size devices are limited to the "K" character only.

Laser marking option is <u>not</u> available on:

- · COG, ultra stable X8R and Y5V dielectric devices.
- EIA 0402 case size devices.
- EIA 0603 case size devices with flexible termination option.
- KPS commercial and automotive grade stacked devices
- X7R dielectric products in capacitance values outlined below.

EIA Case Size	Metric Size Code	Capacitance
0603	1608	≤ 170 pF
0805	2012	≤ 150 pF
1206	3216	≤ 910 pF
1210	3225	≤ 2,000 pF
1808	4520	≤ 3,900 pF
1812	4532	≤ 6,700 pF
1825	4564	≤ 0.018 µF
2220	5650	≤ 0.027 µF
2225	5664	≤ 0.033 µF

Marking appears in legible contrast. Illustrated below is an example of an MLCC with laser marking of "KA8", which designates a KEMET device with rated capacitance of 100 μ F. Orientation of marking is vendor optional.





Capacitor Marking (Optional) cont.

	Capacitance (pF) For Various Alpha/Numeral Identifiers									
	Numeral									
Alpha	9	0	1	2	3	4	5	6	7	8
Character					Capa	citance	e (pF)			
Α	0.10	1.0	10	100	1,000	10,000	100,000	1,000,000	10,000,000	100,000,000
В	0.11	1.1	11	110	1,100	11,000	110,000	1,100,000	11,000,000	110,000,000
С	0.12	1.2	12	120	1,200	12,000	120,000	1,200,000	12,000,000	120,000,000
D	0.13	1.3	13	130	1,300	13,000	130,000	1,300,000	13,000,000	130,000,000
E	0.15	1.5	15	150	1,500	15,000	150,000	1,500,000	15,000,000	150,000,000
F	0.16	1.6	16	160	1,600	16,000	160,000	1,600,000	16,000,000	160,000,000
G	0.18	1.8	18	180	1,800	18,000	180,000	1,800,000	18,000,000	180,000,000
Н	0.20	2.0	20	200	2,000	20,000	200,000	2,000,000	20,000,000	200,000,000
J	0.22	2.2	22	220	2,200	22,000	220,000	2,200,000	22,000,000	220,000,000
К	0.24	2.4	24	240	2,400	24,000	240,000	2,400,000	24,000,000	240,000,000
L	0.27	2.7	27	270	2,700	27,000	270,000	2,700,000	27,000,000	270,000,000
М	0.30	3.0	30	300	3,000	30,000	300,000	3,000,000	30,000,000	300,000,000
N	0.33	3.3	33	330	3,300	33,000	330,000	3,300,000	33,000,000	330,000,000
Р	0.36	3.6	36	360	3,600	36,000	360,000	3,600,000	36,000,000	360,000,000
Q	0.39	3.9	39	390	3,900	39,000	390,000	3,900,000	39,000,000	390,000,000
R	0.43	4.3	43	430	4,300	43,000	430,000	4,300,000	43,000,000	430,000,000
S	0.47	4.7	47	470	4,700	47,000	470,000	4,700,000	47,000,000	470,000,000
T	0.51	5.1	51	510	5,100	51,000	510,000	5,100,000	51,000,000	510,000,000
U	0.56	5.6	56	560	5,600	56,000	560,000	5,600,000	56,000,000	560,000,000
٧	0.62	6.2	62	620	6,200	62,000	620,000	6,200,000	62,000,000	620,000,000
W	0.68	6.8	68	680	6,800	68,000	680,000	6,800,000	68,000,000	680,000,000
Х	0.75	7.5	75	750	7,500	75,000	750,000	7,500,000	75,000,000	750,000,000
Υ	0.82	8.2	82	820	8,200	82,000	820,000	8,200,000	82,000,000	820,000,000
Z	0.91	9.1	91	910	9,100	91,000	910,000	9,100,000	91,000,000	910,000,000
а	0.25	2.5	25	250	2,500	25,000	250,000	2,500,000	25,000,000	250,000,000
b	0.35	3.5	35	350	3,500	35,000	350,000	3,500,000	35,000,000	350,000,000
d	0.40	4.0	40	400	4,000	40,000	400,000	4,000,000	40,000,000	400,000,000
е	0.45	4.5	45	450	4,500	45,000	450,000	4,500,000	45,000,000	450,000,000
f	0.50	5.0	50	500	5,000	50,000	500,000	5,000,000	50,000,000	500,000,000
m	0.60	6.0	60	600	6,000	60,000	600,000	6,000,000	60,000,000	600,000,000
n	0.70	7.0	70	700	7,000	70,000	700,000	7,000,000	70,000,000	700,000,000
t	0.80	8.0	80	800	8,000	80,000	800,000	8,000,000	80,000,000	800,000,000
у	0.90	9.0	90	900	9,000	90,000	900,000	9,000,000	90,000,000	900,000,000



Tape & Reel Packaging Information

KEMET offers multilayer ceramic chip capacitors packaged in 8, 12 and 16 mm tape on 7" and 13" reels in accordance with EIA Standard 481. This packaging system is compatible with all tape-fed automatic pick and place systems. See Table 2 for details on reeling quantities for commercial chips.




Table 5 - Carrier Tape Configuration, Embossed Plastic & Punched Paper (mm)

		Embosse	ed Plastic	Punche	d Paper
EIA Case Size	Tape Size (W)*	7" Reel	13" Reel	7" Reel	13" Reel
	(**)	Pitch	(P ₁)*	Pitch	(P ₁)*
01005 - 0402	8			2	2
0603	8			4	4
0805	8	4	4	4	4
1206 - 1210	8	4	4	4	4
1805 – 1808	12	4	4		
≥ 1812	12	8	8		
KPS 1210	12	8	8		
KPS 1812 and 2220	16	12	12		
Array 0612	8	4	4		

^{*}Refer to Figures 1 and 2 for W and P_1 carrier tape reference locations.

^{*}Refer to Tables 6 and 7 for tolerance specifications.



Figure 1 - Embossed (Plastic) Carrier Tape Dimensions




Table 6 - Embossed (Plastic) Carrier Tape Dimensions

Metric will govern

	Constant Dimensions — Millimeters (Inches)								
Tape Size	D ₀	D ₁ Minimum Note 1	E ₁	P ₀	P ₂	R Reference Note 2	S ₁ Minimum Note 3	T Maximum	T ₁ Maximum
8 mm		1.0 (0.039)				25.0 (0.984)			
12 mm	1.5 +0.10/-0.0 (0.059 +0.004/-0.0)	1.0	1.75 ±0.10 (0.069 ±0.004)	4.0 ±0.10 (0.157 ±0.004)	2.0 ±0.05 (0.079 ±0.002)	30	0.600 (0.024)	0.600 (0.024)	0.100 (0.004)
16 mm		(0.059)	159)			(1.181)			
		1	Variable Dime	ensions — Mill	limeters (Inch	nes)			
Tape Size	Pitch	B ₁ Maximum Note 4	E ₂ Minimum	F	P ₁	T ₂ Maximum	W Maximum	A ₀ ,B ₀	& K ₀
8 mm	Single (4 mm)	4.35 (0.171)	6.25 (0.246)	3.5 ±0.05 (0.138 ±0.002)	4.0 ±0.10 (0.157 ±0.004)	2.5 (0.098)	8.3 (0.327)		
12 mm	Single (4 mm) and double (8 mm)	8.2 (0.323)	10.25 (0.404)	5.5 ±0.05 (0.217 ±0.002)	8.0 ±0.10 (0.315 ±0.004)	4.6 (0.181)	12.3 (0.484)	Not	e 5
		12.1	14.25	7.5 ±0.05	12.0 ±0.10	4.6	16.3		

- 1. The embossment hole location shall be measured from the sprocket hole controlling the location of the embossment. Dimensions of the embossment location and the hole location shall be applied independently of each other.
- 2. The tape with or without components shall pass around R without damage (see Figure 6.)
- 3. If $S_1 < 1.0$ mm, there may not be enough area for a cover tape to be properly applied (see EIA Standard 481, paragraph 4.3, section b.)
- 4. B, dimension is a reference dimension for tape feeder clearance only.
- 5. The cavity defined by A_{α} , B_{α} and K_{α} shall surround the component with sufficient clearance that:
 - (a) the component does not protrude above the top surface of the carrier tape.
 - (b) the component can be removed from the cavity in a vertical direction without mechanical restriction, after the top cover tape has been removed.
 - (c) rotation of the component is limited to 20° maximum for 8 and 12 mm tapes and 10° maximum for 16 mm tapes (see Figure 3.)
 - (d) lateral movement of the component is restricted to 0.5 mm maximum for 8 and 12 mm wide tape and to 1.0 mm maximum for 16 mm tape (see Figure 4.)
 - (e) for KPS product, A_0 and B_0 are measured on a plane 0.3 mm above the bottom of the pocket.
 - (f) see addendum in EIA Standard 481 for standards relating to more precise taping requirements.



Figure 2 - Punched (Paper) Carrier Tape Dimensions




Table 7 - Punched (Paper) Carrier Tape Dimensions

Metric will govern

	Constant Dimensions — Millimeters (Inches)							
Tape Size	D _o	E ₁	P ₀	P ₂	T ₁ Maximum	G Minimum	R Reference Note 2	
8 mm	1.5 +0.10 -0.0 (0.059 +0.004 -0.0)	1.75 ±0.10 (0.069 ±0.004)	4.0 ±0.10 (0.157 ±0.004)	2.0 ±0.05 (0.079 ±0.002)	0.10 (0.004) maximum	0.75 (0.030)	25 (0.984)	
	Variable Dimensions — Millimeters (Inches)							
Tape Size	Pitch	E2 Minimum	F	P ₁	T Maximum	W Maximum	$A_0^{}B_0^{}$	
8 mm	Half (2 mm)	6.25	3.5 ±0.05	2.0 ±0.05 (0.079 ±0.002)	1.1	8.3 (0.327)	Note 1	
8 mm	Single (4 mm)	(0.246)	(0.246) (0.138 ±0.002)	4.0 ±0.10 (0.157 ±0.004)	(0.098)	8.3 (0.327)	Note 1	

- 1. The cavity defined by A_{n} , B_{n} and T shall surround the component with sufficient clearance that:
 - a) the component does not protrude beyond either surface of the carrier tape.
 - b) the component can be removed from the cavity in a vertical direction without mechanical restriction, after the top cover tape has been removed.
 - c) rotation of the component is limited to 20° maximum (see Figure 3.)
 - d) lateral movement of the component is restricted to 0.5 mm maximum (see Figure 4.)
 - e) see addendum in EIA Standard 481 for standards relating to more precise taping requirements.
- 2. The tape with or without components shall pass around R without damage (see Figure 6.)



Packaging Information Performance Notes

- 1. Cover Tape Break Force: 1.0 kg minimum.
- 2. Cover Tape Peel Strength: The total peel strength of the cover tape from the carrier tape shall be:

Tape Width	Peel Strength
8 mm	0.1 to 1.0 newton (10 to 100 gf)
12 and 16 mm	0.1 to 1.3 newton (10 to 130 gf)

The direction of the pull shall be opposite the direction of the carrier tape travel. The pull angle of the carrier tape shall be 165° to 180° from the plane of the carrier tape. During peeling, the carrier and/or cover tape shall be pulled at a velocity of 300 ±10 mm/minute.

3. Labeling: Bar code labeling (standard or custom) shall be on the side of the reel opposite the sprocket holes. *Refer to EIA Standards 556 and 624*.

Figure 3 - Maximum Component Rotation




Figure 4 - Maximum Lateral Movement




Figure 5 - Bending Radius






Figure 6 - Reel Dimensions



Note: Drive spokes optional; if used, dimensions B and D shall apply.

Table 8 - Reel Dimensions

Metric will govern

	Constant Dimensions — Millimeters (Inches)						
Tape Size	A	B Minimum	С	D Minimum			
8 mm	178 ±0.20						
12 mm	(7.008 ±0.008) or	1.5 (0.059)	13.0 +0.5/-0.2 (0.521 +0.02/-0.008)	20.2 (0.795)			
16 mm	330 ±0.20 (13.000 ±0.008)	,	,	, ,			
	Variable	Dimensions — Millimeter	rs (Inches)				
Tape Size	N Minimum	W_1	W ₂ Maximum	W_3			
8 mm		8.4 +1.5/-0.0 (0.331 +0.059/-0.0)	14.4 (0.567)				
12 mm	50 (1.969)	12.4 +2.0/-0.0 (0.488 +0.078/-0.0)	18.4 (0.724)	Shall accommodate tape width without interference			
16 mm		16.4 +2.0/-0.0 (0.646 +0.078/-0.0)	22.4 (0.882)				



Figure 7 - Tape Leader & Trailer Dimensions




Figure 8 – Maximum Camber





Application Guide

Solder Fluxes and Cleaning

The use of water-soluble fluxes provides advantages of excellent solderability due to high activation. However, these fluxes contain organic acids that can induce arcing under high DC or AC voltages. Notable problem areas are underneath the MLCC where flux can be trapped between the ceramic material and PCB. It is therefore critical that PCBs are properly cleaned to remove all flux residue to maintain reliability.

Coating for High Voltage MLCCs


For MLCC ratings ≥1500V, it is recommended to apply a conformal coating to MLCC to prevent surface arcing. To reduce possibility of inducing cracks in the MLCC, select a coating with thermal expansions close to that of the MLCC.

Dielectric	CTE (ppm/°C)
Class II BaTiO₃	10.7
Class I CaZrO₃	9.8

Slits in PCB

It is recommended to apply a slit in the PCB under the MLCC to improve washing of flux residue that may get trapped underneath. In some cases, it is not possible to slit entirely through the PCB due to underlying metal planes. It is also acceptable to apply a recessed slit under the MLCC which will also promote cleaning.

- Recommended for case sizes ≥1206
- The width (w) of the slit should be 1mm
- Length of the slit should be as short as possible to prevent damaging the MLCC due to mechanical stress of the PCB.
- Slits also reduce the risk of solder balls under MLCC which decreased the creepage distance.




Solder Resist

If a slit cannot be applied as above, it is recommended to not use solder resist directly under the MLCC. The use of solder resist material reduces the distance between MLCC ceramic material and PCB thus making it difficult to clean.

Solder Balls

Improper reflow techniques and/or improper washing can induce solder balls under or adjacent to the MLCC. Solder balls reduce the creepage distance between the MLCC terminations and increase the risk of arcing or damage to the ceramic material. To reduce the risk of solder balls:

- Follow KEMET's solder recommendations as outlined in the datasheet.
- If performing a cleaning procedure, properly clean the PCB per KEMET's cleaning recommendations.
- Add slit to the PCB as shown above.





KEMET Electronics Corporation Sales Offices

For a complete list of our global sales offices, please visit www.kemet.com/sales.

Disclaimer

YAGEO Corporation and its affiliates do not recommend the use of commercial or automotive grade products for high reliability applications or manned space flight.

All product specifications, statements, information and data (collectively, the "Information") in this datasheet are subject to change. The customer is responsible for checking and verifying the extent to which the Information contained in this publication is applicable to an order at the time the order is placed. All Information given herein is believed to be accurate and reliable, but it is presented without guarantee, warranty, or responsibility of any kind, expressed or implied.

Statements of suitability for certain applications are based on KEMET Electronics Corporation's ("KEMET") knowledge of typical operating conditions for such applications, but are not intended to constitute – and KEMET specifically disclaims – any warranty concerning suitability for a specific customer application or use. The Information is intended for use only by customers who have the requisite experience and capability to determine the correct products for their application. Any technical advice inferred from this Information or otherwise provided by KEMET with reference to the use of KEMET's products is given gratis, and KEMET assumes no obligation or liability for the advice given or results obtained.

Although KEMET designs and manufactures its products to the most stringent quality and safety standards, given the current state of the art, isolated component failures may still occur. Accordingly, customer applications which require a high degree of reliability or safety should employ suitable designs or other safeguards (such as installation of protective circuitry or redundancies) in order to ensure that the failure of an electrical component does not result in a risk of personal injury or property damage.

Although all product-related warnings, cautions and notes must be observed, the customer should not assume that all safety measures are indicated or that other measures may not be required.

Mouser Electronics

Authorized Distributor

Click to View Pricing, Inventory, Delivery & Lifecycle Information:

KEMET:

```
C1812C102MGRACTU C2225C102KZRACTU C0805C271KDRACTU C0805C121KCRACTU
C1206C122KDRACTU C1206C222KCRACTU C1206C222KDRACTU C1206C471KGRACTU C1206C472KCRACTU
 C1206C682KCRACTU C1210C332KDRACTU C1808C102KZRACTU C1812C101KDRACTU
C1210C221KCRACTU C1206C331KCRACTU C1210C473KCRACTU C1206C102KCRACTU C1210C102KGRACTU
 C1808C102MGRALTU C1206C101KGRALTU C1206C102KGRALTU C1206C472KDRALTU C1808C153KDRALTU
 C1808C471KHRALTU C1825C154KCRALTU C1825C562KGRALTU C1206C332KDRACTU C1825C202JHRACTU
 C1206C102KCRALTU C1206C102KDRALTU C1206C103KCRALTU C1210C102KCRALTU C1210C102KDRALTU
 C1210C102KGRALTU C1808C103KDRALTU C1812C102KHRALTU C1812C103KDRALTU C1812C223KDRALTU
 C1210C102MGRACTU C1812C102KCRACTU C2225C104KCRACTU C2225C103MGRACTU
C1206C221KDRALTU C0805C222KCRACTU C0805C332KCRACTU C0805C102MDRACTU C0805C102KDRACTU
 C2220C221KGRACTU C1210C153KCRACTU C1210C153KDRACTU C1812C153KDRACTU
C1206C471KCRACTU C1812C330KDRACTU C1812C332KGRACTU C1206C102JGRACTU C1206C102MGRACTU
 C1206C103MCRACTU C1206C122KCRACTU C1206C151KGRACTU C1206C153KCRACTU
C1206C392KCRACTU C1206C471KDRACTU C1210C103JDRALTU C1210C103KDRALTU C1210C153KCRAC
C1210C182JGRACTU C1210C222JGRACTU C1210C222KDRACTU C1210C222KGRACTU C1808C101KGRACTU
 C1808C102MGRACTU C1808C153KDRACTU C1808C221KHRACTU C1808C272KGRACTU
C1808C330MHRACTU C1808C472MFRACTU C1812C102MDRACTU C1812C183KDRACTU C1812C221JGRACTU
 C1812C221MGRACTU C1812C222KDRACTU C1812C333KCRACTU C1812C392KGRACTU
C1812C392MGRACTU C1812C471KGRACTU C1812C471MGRACTU C1812C561KHRACTU C1812C682KFRACTU
 C1812C683KCRACTU C1825C154KCRACTU C1825C222KHRACTU C1825C473KDRACTU
C1825C822KGRACTU C2220C473KDRACTU C2220C822KGRACTU C2220C822MGRACTU C2225C123KGRACTU
 C2225C563KDRACTU C2225C563MDRACTU C2225C623KDRACTU
```