




Figure 1. Lattice thermal conductivity of CoSb_3 as a function of the number of supercells used in the machine learning model (green circles) and the root mean square error of the forces for each model (blue circles). Dashed green lines represent the lattice thermal conductivity calculated with LDA and PBE functionals using the traditional approach in Ref [5]. Lattice parameters for CoSb_3 , LDA: 8.92 Å, PBE: 9.11 Å, PBE+D3: 9.03 Å, experimental: 9.04 Å. Experimental values reported for CoSb_3 lattice thermal conductivity are around 10 W/(m K).