

Quality Inspection Report (Inprocess Inspection)

Report No	QIRI20253636	Select the Appropriate Inspection Stage / Process							
Date	12-07-2025	Inspection of Blanks (Punched)							
Production Order	PR025-0928	FLATTENING SECTION X-X							
Item Code	KR DB 22	COINING							
Product Description	SLIT ANGLED DB 2.2 mm								
DHR No	20251683								
Batch No	PU0206/2025	, , , , , , , , , , , , , , , , , , ,							
Reference Drawing	SECPL/KD22/04								

SI.N o.	Parameter	Requirement	Instrument Used	Setup Approval (Actual Readings/Observation)											
				1	2	3	4	5	6	7	8	9	10	(Complied / Not Complied)	Remarks
Α	Wire Diameter	0.80 ± 0.005 mm	DM .	0.801	0.803	0.805	0.805	0.803	0.803	0.804	208.0	0.803	0.804	Compleed	
F(B)	Width of the flat	2.30 ± 0.10 mm	DVC	2.31	2.29	2.24	2.32	2.33	2.35	2.29	2.33	2.36	2.35	Compled	
F(E)	Thickness of the flat	0.22 ± 0.01 mm	DM "	0,221	0,219	0.223	0.225	0.225	0.226	0.222	0.219	0.217	0.220	Complied	
C(B)	Width of the blank	2.40 ± 0.10 mm	DVC	2.39	2.42	2.46	2.41	2.39	2.44	2.45	2.42	2.41	2,46	Complied	
CICI	Cutting length of the blank (LHS)	3.50 ± 0.20 mm	DVC	3.51		3,59					3.51			Compled	J
	Cutting length of the blank (RHS)	3.50 ± 0.20 mm	DVC	3,52	3.51	3,55	3,56	3.52	3.53	3.54	3.56	3,52	3,57	Complied	2
	Pre notch length	23.40 ± 0.50 mm	DVC	23,49	23.36	23.42	23,46	23.52	23.56	23.46	23,55	23, 42	23.44	Compled	
C(F)	Flash land thickness	0.05 ± 0.01 mm	DM ,	0.051	0.052	0.055	0.049	0,053	0.056	0.051	0.056	0.053	0.057	Compfied	
C(G)	Blank thickness	0.23 ± 0.01 mm	DM			1							1	Complied	
C(H)	Depth Marking	2.30 ± 0.10 mm	DVC		4			2.37			00.3			Complied	
*	Surface Finish	Deffects Free	Microscope	OK	op	OK	OK	OK	ok	OK	OK	OK	OK	Compled	
Insp	nspected By (Name) LAKSHMI						S	ignature	(with da	te)	(SO)	12-04-	2025.		

Format No: SECPL_FM_043, Rev.00

Effective Date: 28-04-2023



Quality Inspection Report (Inprocess Inspection)

SI.N o.	Parameter	Date and Time	Instrument Used	Inprocess Samples Inspection (Put "v" - Complied and "X "- Not Complied										Inspected by		
				1	2	3	4	5	6	7	8	9	10	(Signature)	ure) Remarks	
		12-07-2025 02:00 PM				V	V	4	~					(SOL)		
				~	~					-	~			7		
		03:00 PM	_			-	~		-	-	~	1		ECIL		
					<u></u>				~		~			A		
	W4 09; #0	-	-							~			COL			
								-	V		~			(
1.	Width of the flat		DVC		/	\ \ \ \ \ \ \ \ \ \ \ \ \ \ \ \ \ \ \			~					de		
2.	Thickness of the flat	05:00 PM	DM	~							~	-		30th	<u>\$</u>	
3. 4.	Width of the blank Cutting length of the blank		DVC		_					-		-				
5.	Pre notch length	06100 PM	DVC						-		-	+-	_	Par		
6.	Blank Thickness	OO (OO PIC)	DM											0/		
7.	Depth Marking	7.117.0	DVC VISUAL/MICROS	./				. /						1		
8.	Visual Checks	14-07-2025 9:40 AM	COPE											(CON)		
		м х - 1 - 1			./									7		
					~								1.7 =			
	100				/	~		0								
	and the second	r fr. v	. 18		/			~			·					
	1577 . 117		1 8			/					_			2		
	Episanto (A. A.	10:10 AM.		~			~					-		GOV		
ample Inspected Quantity 200 PCS. Accepted Batch Qua						antity 4656 PCS			S, Remarks					•		
efect	s Observed (Type)	_														
Post Quality Inspection Result						Inspected By (Name)			LAKSHMI			Approved By (Name)		ne) MURIC	MURIGESHAPPA R	
Batch conform to the requirement and approved						Signature			100 Ut-04-2025.			Signature		icit	OKO.	
Batch do not conform to the requirement and not approved							e		100	4-07	μ.	with dat	:e		14-01-20X	

Format No: SECPL_FM_043, Rev.00