

## Labor Werkstofftechnik

07.09.2023

Serie	R <sub>p0.2</sub> MPa	R <sub>m</sub>	A <sub>25 mm</sub>
n = 5	MPa	MPa	%
X	157	346	23,2
s	5	15	1,5
ν [%]	3,27	4,20	6,46