

GROUP OF TESTING LABORATORIES GRYFITLAB

ul. Prosta 2, Łozienica, 72-100 Goleniów tel. (091) 431 82 42, fax (091) 418 97 57, kom. 607-900-481 www.gryfitlab.com, e-mail: contact@gryfitlab.com

Evidence of performance Airborne sound insulation of building components

Test Report

No. GLA-1288.11/16

Client

PRESS GLASS S.A.

Nowa Wieś ul. Kopalniana 9 42-262 Poczesna

Product:	Insulating glass unit			
Construction:	10/14/16,76			
Designation:	FL 10/14/VSG (TH1,1 8/0,76 PVB/FL 8) kl.1/B/1 Ar			
Dimension:	1230mm x 1480mm			
Gas filing:	Argon			
Cross-section:	10 14 16,76			

Rating	R _w (C; C _{tr})	STC	ОІТС
Basis	PN-EN ISO 717-1: 2013	ASTM E413-10	ASTM E1332-10
Value	43 (-2; -4) dB	43 dB	37dB

Łozienica, 8.12..2016

PhD Krzysztof Mech
Head of Acoustics Laboratory