

GROUP OF TESTING LABORATORIES GRYFITLAB

ul. Prosta 2, Łozienica, 72-100 Goleniów tel. (091) 431 82 42, fax (091) 418 97 57, kom. 607-900-481 www.gryfitlab.com, e-mail: contact@gryfitlab.com

Evidence of performance Airborne sound insulation of building components

Test Report

No. GLA-1288.4/16

Client

PRESS GLASS S.A.

Nowa Wieś ul. Kopalniana 9 42-262 Poczesna

Product:	Insulating glass unit		
Construction:	6/12/4/12/4		
Designation:	TH1,1 6/12/FL 4/12/TH1,1 4 Ar		
Dimension:	1230mm x 1480mm		
Gas filing:	Argon		
Cross-section:	6 12 4 12 4		

Rating	R _w (C; C _{tr})	STC	ОІТС
Basis	PN-EN ISO 717-1: 2013	ASTM E413-10	ASTM E1332-10
Value	36 (-2; -6) dB	36 dB	27 dB

Łozienica, 23.11.2016

PhD Krzysztof Mech Head of Acoustics Laboratory