

GROUP OF TESTING LABORATORIES GRYFITLAB

ul. Prosta 2, Łozienica, 72-100 Goleniów tel. (091) 431 82 42, fax (091) 418 97 57, kom. 607-900-481 www.gryfitlab.com, e-mail: contact@gryfitlab.com

Evidence of performance Airborne sound insulation building components

Test Report No. GLA-1255.3/16

Client

PRESS GLASS S.A.

Nowa Wieś ul. Kopalniana 9 42-262 Poczesna

Product:	Insulating glass unit			
Construction:	8 / 12 / 6 / 12 / 55.2			
Designation:	FL 8 / 12+Ar / FL 6 / 12+Ar / Laminated glass 55.2 class P2A			
Dimension:	1230mm x 1480mm			
Gas filing:	Argon			
Cross-section:	8 12 6 12 10,76			

Rating	R _w (C; C _{tr})	STC	ОІТС
Basis	PN-EN ISO 717-1: 2013	ASTM E413-10	ASTM E1332-10
Value	43 (-2; -6) dB	43 dB	34 dB

Łozienica, 05.05.2016

PhD Krzysztof Mech
Head of Acoustics Laboratory