

GROUP OF TESTING LABORATORIES GRYFITLAB

ul. Prosta 2, Łozienica, 72-100 Goleniów tel. (091) 431 82 42, fax (091) 418 97 57, kom. 607-900-481 www.gryfitlab.com, e-mail: contact@gryfitlab.com

Evidence of performance Airborne sound insulation of building components

Test Report

No. GLA-1288.6/16

Client

PRESS GLASS S.A.

Nowa Wieś

ul. Kopalniana 9

42-262 Poczesna

Product:	Insulating glass unit		
Construction:	12,76/12/8,76		
Designation:	66.2 kl.P2A/12/44.2 TH1,1 kl.P2A Ar		
Dimension:	1230mm x 1480mm		
Gas filing:	Argon		
Cross-section:	12,76 12 8,76		

Rating	R _w (C; C _{tr})	STC	ОІТС
Basis	PN-EN ISO 717-1: 2013	ASTM E413-10	ASTM E1332-10
Value	43 (-2; -6) dB	43 dB	34 dB

Łozienica, 25.11.2016

PhD Krzysztof Mech
Head of Acoustics Laboratory