

## **GROUP OF TESTING LABORATORIES GRYFITLAB**

ul. Prosta 2, Łozienica, 72-100 Goleniów tel. (091) 431 82 42, fax (091) 418 97 57, kom. 607-900-481 www.gryfitlab.com, e-mail: contact@gryfitlab.com

## **Evidence of performance Airborne sound insulation building components**

Test Report No. GLA-1255.1/16

Client:

PRESS GLASS S.A.

Nowa Wieś ul. Kopalniana 9 42-262 Poczesna

Product:	Insulating glass unit		
Construction:	33.1 / 12 / 33.1		
Designation:	Laminated glass 33.1 class 2B2 / 12+Ar / Laminated glass 33.1 class 2B2		
Dimension:	1230mm x 1480mm		
Gas filing:	Argon		
Cross-section:	6,38 12 6,38		

Rating	R <sub>w</sub> (C; C <sub>tr</sub> )	STC	ОІТС
Basis	PN-EN ISO 717-1: 2013	ASTM E413-10	ASTM E1332-10
Value	35 (-2; -6) dB	35 dB	27 dB

Łozienica, 27.04.2016

PhD Krzysztof Mech
Head of Acoustics Laboratory