

GROUP OF TESTING LABORATORIES GRYFITLAB

ul. Prosta 2, Łozienica, 72-100 Goleniów tel. (091) 431 82 42, fax (091) 418 97 57, kom. 607-900-481 www.gryfitlab.com, e-mail: contact@gryfitlab.com

Evidence of performance Airborne sound insulation building components

Test Report

No. GLA-1255.4/16

Client

PRESS GLASS S.A.

Nowa Wieś ul. Kopalniana 9

42-262 Poczesna

Product:	Insulating glass unit			
Construction:	4 / 12 / 4 /12 / 33.1			
Designation:	FL 4 / 12+Ar / FL 4 / 12+Ar / Laminated glass 33.1 class 2B2			
Dimension:	1230mm x 1480mm			
Gas filing:	Argon			
Cross-section:	4 12 4 12 6,38			

Rating	R _w (C; C _{tr})	STC	ОІТС
Basis	PN-EN ISO 717-1: 2013	ASTM E413-10	ASTM E1332-10
Value	35 (-1; -6) dB	35 dB	26 dB

Łozienica, 05.05.2016

PhD Krzysztof Mech Head of Acoustics Laboratory