

GROUP OF TESTING LABORATORIES GRYFITLAB

ul. Prosta 2, Łozienica, 72-100 Goleniów tel. (091) 431 82 42, fax (091) 418 97 57, kom. 607-900-481 www.gryfitlab.com, e-mail: contact@gryfitlab.com

Evidence of performance Airborne sound insulation building components

Test Report
Opinion from the scope of sound insulation

No. GLA-1239/15 E

No. GLA - 1239 - O/15 E

Client:

PRESS GLASS S.A.

Nowa Wieś ul. Kopalniana 9 42-262 Poczesna

Product:	Insulating glass unit		
Construction:	8/20/55.2		
Designation:	FL8mm/20+Ar/VSG10,76mm (FL5mm/0,76PVB/FL5mm)		
Dimension:	1230mm x 1480mm		
Gas filing:	Argon		
Cross-section:	8 20 5 5 0.76mm		

Rating	R _w (C; C _{tr})	STC	ОІТС
Basis	PN-EN ISO 717-1: 2013	ASTM E413-10	ASTM E1332-10
Value	42 (-2; -5) dB	42 dB	34 dB

Łozienica, 04.03.2016

PhD Krzysztof Mech
Head of Acoustics Laboratory