

GROUP OF TESTING LABORATORIES GRYFITLAB

ul. Prosta 2, Łozienica, 72-100 Goleniów tel. (091) 431 82 42, fax (091) 418 97 57, kom. 607-900-481 www.gryfitlab.com, e-mail: contact@gryfitlab.com

Evidence of performance Airborne sound insulation of building components

Test Report

No. GLA-1277.4/16

Client

PRESS GLASS S.A.

Nowa Wieś

ul. Kopalniana 9

42-262 Poczesna

Product:	Insulating glass unit			
Construction:	4/12/4/12/4			
Designation:	TH1,1 4 / 12 / FL 4 / 12 / TH1,1 4 Ar			
Dimension:	1230mm x 1480mm			
Gas filing:	Argon			
Cross-section:	4 12 4 12 4			

Rating	R _w (C; C _{tr})	STC	ОІТС
Basis	PN-EN ISO 717-1: 2013	ASTM E413-10	ASTM E1332-10
Value	33 (-2; -5) dB	33 dB	25 dB

Łozienica, 26.08.2016

PhD Krzysztof Mech
Head of Acoustics Laboratory