

GROUP OF TESTING LABORATORIES GRYFITLAB

ul. Prosta 2, Łozienica, 72-100 Goleniów tel. (091) 431 82 42, fax (091) 418 97 57, kom. 607-900-481 www.gryfitlab.com, e-mail: contact@gryfitlab.com

Evidence of performance Airborne sound insulation building components

Test Report

No. GLA-1255.5/16

Client

PRESS GLASS S.A.

Nowa Wieś ul. Kopalniana 9

42-262 Poczesna

Product:	Insulating glass unit			
Construction:	44.2 / 12 / 6 / 12 / 44.2			
Designation:	Laminated glass 44.2 class P2A / 12+Ar / FL 6 / 12+Ar / Laminated glass 44.2 class P2A			
Dimension:	1230mm x 1480mm			
Gas filing:	Argon			
Cross-section:	8,76 12 6 12 8,76			

Rating	R _w (C; C _{tr})	STC	ОІТС
Basis	PN-EN ISO 717-1: 2013	ASTM E413-10	ASTM E1332-10
Value	40 (-3; -8) dB	39 dB	29 dB

Łozienica, 05.05.2016

Head of Acoustics Laboratory