# **Evidence of Performance**

Airborne sound insulation of building elements

Test report 163 34476/Z5e

This is a translation of the test report 163 34476/Z5 of 15<sup>th</sup> November 2007.



Client

Press Glas S.A. Nowa Wies Kopalniana 9

42-262 Poczesna Poland

Product Isolation glass unit

Designation Float 6 mm / 16 / 55.2 Thermofloat Ar.

Size (w × h) 1230 mm × 1480 mm

Construction 6/16/10 LG

Gas filling Argon

Area related weight 40,4 kg/m²

Weighted sound reduction index  $R_w$ Spectrum adaptation terms C and  $C_{tr}$ 




 $R_w(C; C_{tr}) = 40 (-1;-4) \text{ dB}$ 

Basis

EN ISO 140-1:1997+A1:2004 EN 20140-3 :1995+A1:2004 EN ISO 717-1 : 1996+A1:2006

### Representation



#### Informations for use

This test report may be used to validate the sound reduction of a building element.

Validity for germany:

 $R_{\text{w}}$  corresponds to  $R_{\text{w,P}}$  for DIN 4109 Annex 1 table 40

## Validity

The data and results given relate solely to the described, tested object.

Testing the acoustic properties does not allow any statement to be made on further characteristics of the present structure which could define performance and quality.

# Notes on publication

The **ift** Guidance Sheet "Conditions and Guidance for the use of **ift** Test Documents" applies.

The cover sheet can be used as a summary.

### Contents

This test report includes 6 pages

- Test specimen
- 2 Test procedure
- 3 Test results
- 4 Instructions for use Data sheet (1 page)

**ift** Rosenheim 22<sup>nd</sup> November 2007

Special items

Dr. Joachim Hessinger, Dipl.-Phys. Head of test laboratory ift centre for acoustic

Bernd Saß, Dipl.-Ing. (FH) vice head of test laboratory ift centre for acoustic

